



552 Academy Avenue  
Providence, RI 02908

**401-521-6300**

[www.provwater.com](http://www.provwater.com)

June 24, 2013

June Swallow, PE  
Chief, Drinking Water Quality  
R.I. Department of Health  
Cannon Building, Room 209  
Three Capitol Hill  
Providence, R.I. 02908-5097

RE: pH Transition Implementation Plan  
Philip J. Holton Water Purification Plant  
May 2013 Monthly Report  
PWSID 1592024

The Hon. Angel Taveras  
*Mayor*

Boyce Spinelli  
*General Manager*

Dear Ms. Swallow:

BOARD OF DIRECTORS

Brett P. Smiley  
*Chairman*

Joseph D. Cataldi  
*Vice Chairman*

Michael L. Pearis  
*Ex-Officio*

Michael A. Solomon  
*City Council President*

Michael J. Correia  
*City Councilman*

Andy M. Andujar  
*Member*

Joan S. Badway  
*Member*

Carissa R. Richard  
*Secretary*

William E. O'Gara, Esq.  
*Legal Advisor*

Providence Water is pleased to submit the attached May 2013 Monthly Report. The format of the Monthly Report continues to follow the outline of RIDOH's December 6, 2012 letter. Providence Water continues to work closely with certain members of the Expert Panel.

The commencement of the full pilot Unidirectional Flushing (UDF) Program began on June 10. Smaller, more isolated UDFs have been on-going. Under the Water Main Replacement Program, three contractors were awarded contracts for the 2013 construction season, extending into 2014. These contractors have begun work in the Hope and Wayland Sections of Providence, and in the Edgewood Section of Cranston.

Should you have any questions, please feel free to contact me at 521-6300, Ext. 7291 or [ggiasson@provwater.com](mailto:ggiasson@provwater.com).

Respectfully,  
PROVIDENCE WATER SUPPLY BOARD

Gregg Giasson, PE  
Senior Director of Operations

Attachment: May 2013 Monthly Report

cc: Clay Commons	Peter LePage	Steve Soito, PE
Boyce Spinelli	Steve Santaniello	Fred Crosby
Joseph Spremulli	Rich Razza	Mike Covellone
Ricky Caruolo	Paul Gadoury, PE	John Phillips, PE

Member  
Rhode Island Water Works Assn.  
New England Water Works Assn.  
American Water Works Assn.  
Water Research Foundation

An EPA WaterSense Partner

[Only Tap Water Delivers](#)



**pH Transition Implementation Plan  
Philip J. Holton Water Purification Plant  
Monthly Report  
May 2013**

This Monthly Report follows the outline of the RIDOH December 6, 2012 letter requesting monthly updates on all activity related to corrosion control.

**1. pH Transition**

The initial transition to a higher pH began on Wednesday, February 6, 2013.

The second and final transition to the higher pH of 10.2 began on Monday, March 25, 2013 and the CO<sub>2</sub> dose was terminated.

During May, the Treatment Plant Effluent and Academy Avenue pH and Alkalinity had the following values:

	Effluent Water		Academy Avenue	
	<u>pH (SU)</u>	<u>T. Alkalinity (mg/l)</u>	<u>pH (SU)</u>	<u>T. Alkalinity (mg/l)</u>
Min.	10.24	15.00	10.10	13.70
Max.	10.43	16.60	10.32	19.10
Avg.	10.33	15.61	10.18	14.58

See Attachment No. 1 - May pH and Alkalinity Data Tables.

## **2. Special Sampling Studies of Lead Service Line**

### **A. Sequential and LSL Sampling & Testing**

The Post-CCTC sampling began on February 11, and continues based on the approved Protocol.

Sampling data received to date extends through the end of May.

See Attachment No. 2 - Samples from Lead Service Line, for the eight participant site/address test results, for essentially all metals.

### **B. PRS Stations' Monitoring (Academy Ave., Brown University, Commercial Building)**

The PRS Stations sampling and testing that was resumed at the end of January continues.

### **C. Virginia Tech (VT) Pipe Loop Rigs (Academy Ave., Water Treatment Plant)**

Sampling and testing continues on the VT Rigs that were placed back in service the last week in February. The intention continues to sample and test once per month.

## **3. Special Sampling Studies - TCR Sites, LCR Sites, WTP Finished Water**

### **A. Special Total Coliform Rule (TCR) Sites (4)**

Four TCR sites were chosen for ease of sampling and their dispersed geographical locations. The additional sampling and testing that began at these sites on February 1, continues once every two weeks.

### **B. Lead and Copper Rule (LCR) Sites**

The additional testing of the LCR sites (100) during the normal 6 month semesters that began in December 2012, continues. The additional tests being conducted, as requested by the Expert Panel, are for Dissolved Lead, Total Iron, and Total Zinc.

### **C. Total Coliform Rule (TCR) Sites (44)**

The added Turbidity testing continues.

#### D. WTP Finished Water Sampling

The addition of Oxygen Reduction Potential (ORP) to the typical daily analyses of the finished water, continues with weekly field tests and laboratory tests every 8 weeks Post-CCTC.

#### 4. Experimental Pipe Loops

The sixteen, two (2) foot lead service line samples, ready for future insertion into the pipe loops, continue to be conditioned by hand using the manual fill and dump method. This is being accomplished twice per week, with Total Lead tests done once per week. This fill and dump method will be employed while the pipe loop racks are being fabricated. The best eight samples, based on Total Lead tests, will be inserted into the loops for further conditioning.

The wood frame work of the pipe loop support system is being fabricated. PVC pipe, fittings, valves, and tanks were ordered.

Discussions are ongoing with the Expert Panel members on the conduct of the lead pipe conditioning. As per the Expert Panel's report, further consultation with the Panel is warranted once the current data is analyzed to determine what future experiments/pilot studies may be warranted.

May 2013

pH Alkalinity Data

Date	Effluent Water		Academy Ave., Tap	
	pH SU	T. Alk. mg/l	pH SU	T. Alk. mg/l
5/1/2013	10.32	15.00	10.13	13.70
5/2/2013	10.32	15.00	10.14	13.80
5/3/2013	10.34	15.00	10.18	14.00
5/4/2013	10.35	16.10		
5/5/2013				
5/6/2013	10.34	15.30	10.16	13.70
5/7/2013	10.32	15.00	10.17	14.00
5/8/2013	10.30	15.00	10.16	14.20
5/9/2013	10.32	15.30	10.17	14.00
5/10/2013	10.29	15.70	10.19	14.60
5/11/2013	10.32	15.50		
5/12/2013				
5/13/2013	10.30	15.30	10.10	19.10
5/14/2013	10.37	16.50	10.17	14.20
5/15/2013	10.40	16.00	10.23	14.60
5/16/2013	10.43	16.20	10.32	15.40
5/17/2013	10.41	16.60	10.29	17.80
5/18/2013	10.34	15.80		
5/19/2013				
5/20/2013			10.22	14.30
5/21/2013	10.28	15.40	10.18	14.30
5/22/2013	10.24	15.90	10.17	14.10
5/23/2013	10.35	15.70	10.18	14.00
5/24/2013	10.31	15.40	10.15	14.00
5/25/2013	10.40	15.90		
5/26/2013				
5/27/2013				
5/28/2013	10.38	16.00	10.18	14.30
5/29/2013	10.32	15.60	10.13	14.10
5/30/2013	10.32	15.30	10.18	14.20
5/31/2013	10.28	15.80	10.18	14.40
Minimum	10.24	15.00	10.10	13.70
Maximum	10.43	16.60	10.32	19.10
Average	10.33	15.61	10.18	14.58

## Loc #1, 57 Holburn Ave

Date: 1/4/13; inside faucet

E301238

Flow rate = 1.49 gpm

pH = 9.33 / 9.53

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0052	0.0010	0.20	0.051	0.0520	0.0100	0.0051	0.0048	0.0710
2	#02, 1/2 Liter	0.0028	0.0010	0.19	0.051	0.0430	0.0110	0.0051	0.0038	0.0071
3	#03, 1 Liter	0.0010	0.0010	0.22	0.051	0.0110	0.0026	0.0051	0.0071	0.0051
4	#04, 1 Liter	0.0010	0.0010	0.23	0.051	0.0110	0.0021	0.0051	0.0073	0.0062
5	#05, 1 Liter	0.0012	0.0010	0.22	0.051	0.0082	0.0023	0.0051	0.0071	0.0051
6	#06, 1 Liter	0.0012	0.0010	0.23	0.051	0.0078	0.0021	0.0051	0.0073	0.0040
7	#07, 3 min 1 Liter	0.0010	0.0010	0.22	0.051	0.0120	0.0025	0.0051	0.0070	0.0072

Date: 1/18/13; outside spigot

E301D07

Flow rate = 1.69 gpm

pH = 9.61 / 9.90

temp = 18.9 / 7.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	1.3000	0.0440	0.43	0.065	0.4100	0.0480	0.056	0.0150	0.6000
2	#02, 1/2 Liter	0.0045	0.0010	0.21	0.051	0.0160	0.0031	0.0051	0.0042	0.0095
3	#03, 1 Liter	0.0100	0.0010	0.20	0.051	0.0093	0.0026	0.0051	0.0040	0.0250
4	#04, 1 Liter	0.0260	0.0019	0.21	0.051	0.0076	0.0019	0.0051	0.0047	0.0280
5	#05, 1 Liter	0.0190	0.0013	0.21	0.051	0.0044	0.0016	0.0051	0.0050	0.0290
6	#06, 1 Liter	0.0180	0.0045	0.22	0.067	0.0032	0.0015	0.0051	0.0058	0.0250
7	#07, 1 Liter	0.0042	0.0010	0.24	0.083	0.0026	0.0015	0.0051	0.0075	0.0190
8	#08, 3 min 1 Liter	0.0010	0.0010	0.24	0.064	0.0010	0.0010	0.0051	0.0076	0.0210

Date: 1/22/13; outside spigot

E301F54

Flow rate = 1.75 gpm

pH = 9.61 / 9.89

temp = 15.2 / 6.4

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	<b>0.2600</b>	0.0023	<b>0.30</b>	0.051	<b>0.3200</b>	<b>0.0150</b>	<b>0.0084</b>	<b>0.0084</b>	<b>0.4400</b>
2	#02 1 Liter	0.0150	0.0024	<b>0.24</b>	0.051	<b>0.0100</b>	0.0024	0.0051	0.0038	0.0056
3	#03 1 Liter	0.0180	0.0031	<b>0.24</b>	0.051	0.0037	<b>0.0031</b>	0.0051	0.0042	0.0061
4	#04 1 Liter	0.0230	<b>0.0041</b>	<b>0.24</b>	0.051	0.0022	0.0014	0.0051	0.0042	<b>0.0073</b>
5	#05 1 Liter	<b>0.0260</b>	<b>0.0044</b>	0.22	0.051	0.0021	0.0017	0.0051	0.0051	0.0051
6	#06 1 Liter	0.0024	0.0010	0.23	0.051	0.0015	0.0010	0.0051	0.0070	0.0051
7	#07 3 min 1 Liter	0.0010	0.0010	0.23	0.051	0.0010	0.0010	0.0051	<b>0.0071</b>	0.0051

Date: 1/25/13; outside spigot

E301H01

Flow rate = 2.52 gpm

pH = 9.55

temp = 16.9 / 17.1

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	<b>0.035</b>	0.001	0.21	0.051	<b>0.0170</b>	<b>0.0027</b>	0.0051	0.0045	0.0051
2	#02 1 Liter	<b>0.110</b>	<b>0.051</b>	0.20	0.051	<b>0.0100</b>	0.0016	0.0051	0.0045	0.0051
3	#03 1 Liter	0.030	<b>0.020</b>	0.21	0.051	0.0038	<b>0.0036</b>	0.0051	0.0052	0.0051
4	#04 1 Liter	0.014	0.009	0.20	0.051	0.0031	0.0021	0.0051	0.0053	0.0051
5	#05 1 Liter	0.012	0.004	0.21	0.051	0.0027	0.0031	0.0051	0.0060	0.0051
6	#06 1 Liter	0.009	0.005	<b>0.22</b>	0.051	0.0023	0.0011	0.0051	<b>0.0068</b>	0.0051
7	#07 3 min 1 Liter	0.001	0.001	<b>0.22</b>	<b>0.057</b>	0.0010	0.0010	0.0051	<b>0.0068</b>	0.0051

**Date: 1/30/13; outside spigot****E301K64**

Flow rate = 2.36 gpm

pH = 9.61 / 9.80

temp = 17.5 / 10.4

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	<b>0.0300</b>	0.0013	<b>0.2800</b>	0.0510	<b>0.0220</b>	<b>0.0140</b>	0.0051	0.0043	0.0068
2	#02 1 Liter	0.0240	<b>0.0042</b>	0.2600	0.0510	<b>0.0072</b>	<b>0.0032</b>	0.0051	0.0041	0.0120
3	#03 1 Liter	<b>0.0860</b>	<b>0.0056</b>	0.2700	0.0530	0.0027	0.0011	0.0051	0.0046	<b>0.0140</b>
4	#04 1 Liter	0.0170	0.0024	0.2600	0.0510	0.0016	0.0010	0.0051	0.0056	0.0120
5	#05 1 Liter	0.0120	0.0037	0.2700	<b>0.0810</b>	0.0013	0.0016	0.0051	0.0068	<b>0.0140</b>
6	#06 1 Liter	0.0038	0.0010	<b>0.2800</b>	0.0540	0.0010	0.0010	0.0051	<b>0.0080</b>	0.0096
7	#07 3 min 1 Liter	0.0010	0.0010	<b>0.3000</b>	<b>0.0740</b>	0.0010	0.0010	0.0051	<b>0.0086</b>	0.0096

**Date: 2/11/13; inside faucet****E302596**

Flow rate = 1.30 gpm

pH = 9.65 / 9.81

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0049</b>	0.001	<b>0.22</b>	0.051	<b>0.032</b>	<b>0.011</b>	0.0051	0.005	0.009
2	#02, 1 Liter	0.003	0.001	0.2	0.051	0.0011	0.0011	0.0051	<b>0.0057</b>	<b>0.01</b>
3	#03, 3 min 1 Liter	0.001	0.001	0.2	0.051	0.001	0.001	0.0051	<b>0.0063</b>	0.016

**Date: 2/13/13; outside spigot****E302953**

Flow rate = 2.56 gpm

pH = 9.61 / 9.79

temp = 15 / 7.3

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.026</b>	0.001	0.26	0.051	<b>0.017</b>	<b>0.0034</b>	0.0051	0.0043	0.0075
2	#02, 1 Liter	0.021	<b>0.0032</b>	0.3	<b>0.078</b>	0.0036	0.0012	0.0051	0.0057	<b>0.012</b>
3	#03, 3 min 1 Liter	0.0036	0.001	<b>0.44</b>	<b>0.076</b>	0.001	0.001	0.0051	<b>0.012</b>	0.0084



**Date: 2/20/13; outside spigot****E302E21**

Flow rate = 2.22 gpm

pH = 9.77 / 9.94

temp = 15.4 / 8.0

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0095	0.0010	<b>0.2500</b>	0.0510	<b>0.0250</b>	<b>0.0027</b>	0.0051	0.0058	0.0053
2	#02, 1 Liter	<b>0.0120</b>	0.0010	<b>0.2500</b>	0.0510	0.0027	0.0010	0.0051	0.0062	<b>0.0120</b>
3	#03, 3 min 1 Liter	0.0010	0.0010	<b>0.2500</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0072</b>	0.0092

**Date: 2/21/13; inside faucet****E302E20**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0210</b>	<b>0.0011</b>	<b>0.3100</b>	0.0510	<b>0.0270</b>	<b>0.0056</b>	0.0051	<b>0.0083</b>	<b>0.0550</b>
2	#02, 1 Liter	0.0081	0.0010	0.1800	0.0510	0.0035	0.0012	0.0051	0.0061	0.0250
3	#03, 3 min 1 Liter	0.0045	0.0010	0.2000	0.0510	0.0013	0.0010	0.0051	0.0077	0.0140

**Date: 3/1/13; inside faucet****E303079**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		<b>0.0030</b>	0.0010	0.2400	0.0510	<b>0.0200</b>	<b>0.0080</b>	0.0051	0.0047	<b>0.0680</b>
2		0.0027	0.0010	0.2400	0.0510	0.0075	0.0031	0.0051	0.0051	0.0140
3		0.0010	0.0010	<b>0.2500</b>	<b>0.0580</b>	0.0010	0.0010	0.0051	<b>0.0070</b>	0.0110

**Date: 3/6/13; outside faucet****E303572**

ATP = 646 ME/mL

Flow rate = 2.24 gpm

pH = 9.83 / 9.94

temp = 17 / 8.5

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0150	0.0010	<b>0.4100</b>	0.0510	<b>0.0140</b>	<b>0.0067</b>	0.0051	0.0069	0.0056
2		<b>0.0170</b>	<b>0.0018</b>	0.4000	<b>0.0720</b>	0.0052	0.0015	0.0051	<b>0.0094</b>	<b>0.0120</b>
3		0.0010	0.0010	0.3100	0.0510	0.0010	0.0010	0.0051	<b>0.0094</b>	0.0110

**Date: 3/7/13; inside faucet**

**E303571**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0052	0.0010	<b>0.2300</b>	0.0510	<b>0.0340</b>	<b>0.0120</b>	0.0051	0.0049	0.0140
2	<b>0.0053</b>	0.0010	0.1800	0.0510	0.0016	0.0010	0.0051	0.0049	<b>0.0150</b>
3	0.0010	0.0010	0.2100	0.0510	0.0018	0.0010	0.0051	<b>0.0070</b>	0.0140

**Date: 4/2/13; inside faucet**

**E304162**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0035	0.0010	0.1200	0.0510	<b>0.0140</b>	<b>0.0057</b>		0.0026	0.0051
2	<b>0.0092</b>	0.0010	0.1300	0.0510	0.0010	0.0010		0.0032	<b>0.0110</b>
3	0.0010	0.0010	<b>0.1400</b>	0.0510	0.0010	0.0010		<b>0.0040</b>	<b>0.0110</b>

**Date: 4/9/13; outside faucet**

**E304758**

ATP = 1542

Flow rate = 2.17 gpm

pH = 10.0 / 10.11

temp = 13.4 / 10.0

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0110	0.0010	0.1600	0.0510	<b>0.0090</b>	<b>0.0026</b>		0.0037	0.0072
2	<b>0.0370</b>	<b>0.0016</b>	0.1700	0.0510	0.0054	0.0016		0.0038	<b>0.0120</b>
3	0.0013	0.0010	<b>0.1800</b>	0.0510	0.0010	0.0010		<b>0.0048</b>	0.0093

**Date: 5/6/13; outside faucet****E305476**

ATP = ???

Flow rate = 1.6 gpm

pH = 10.10 / 10.06

temp = 12.3 / 11.8

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0087</b>	<b>0.0016</b>	<b>0.1600</b>	0.0510	<b>0.0320</b>	<b>0.0048</b>		0.0065	0.0051
2	0.0062	0.0010	0.1500	0.0510	0.0017	0.0010		<b>0.0075</b>	<b>0.0140</b>
3	0.0014	0.0010	0.1500	0.0510	0.0010	0.0010		0.0069	0.0120

**Date: 5/14/13; inside faucet****E305C71**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0130</b>	<b>0.0016</b>	0.1100	0.0510	<b>0.0069</b>	<b>0.0035</b>		0.0039	0.0051
2	0.0076	0.0010	0.1900	0.0510	0.0031	0.0010		0.0080	0.0051
3	0.0037	0.0010	<b>0.2100</b>	0.0510	0.0018	0.0010		<b>0.0110</b>	<b>0.0055</b>

**Loc #2 26 Keith Avenue**

Two largest concentrations

Below quantitation limits

**Sample date 1/8/2013; Outside spigot; E301631**

Flow rate = 1.63 gpm

pH = 9.42 / 9.53

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0095	0.0016	0.100	0.051	<b>0.0430</b>	<b>0.0110</b>	0.0051	0.0038	<b>0.0590</b>
2	#02, 1/2 Liter	0.0067	0.0010	0.150	0.051	0.0110	<b>0.0045</b>	0.0051	0.0039	<b>0.0180</b>
3	#03, 1 Liter	0.0370	0.0050	0.150	0.051	0.0073	0.0031	0.0051	0.0042	0.0063
4	#04, 1 Liter	0.0530	<b>0.0098</b>	<b>0.160</b>	0.051	0.0021	0.0010	0.0051	0.0046	0.0051
5	#05, 1 Liter	<b>0.0550</b>	0.0058	<b>0.160</b>	0.051	0.0011	0.0010	0.0051	<b>0.0048</b>	0.0051
6	#06, 1 Liter	<b>0.0580</b>	<b>0.0093</b>	0.150	0.051	0.0010	0.0010	0.0051	<b>0.0048</b>	0.0051
7	#07, 1 Liter	0.0170	0.0023	0.110	0.051	0.0010	0.0010	0.0051	0.0042	0.0051
8	#08, 3 min 1 Liter	0.0033	0.0010	0.093	0.051	<b>0.0130</b>	0.0041	0.0051	0.0032	0.0062

**Sample date 1/9/2013; Inside faucet; E301690**

Flow rate = 2.10 gpm

pH = 9.46 / 9.54

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0036	0.0010	<b>0.140</b>	0.051	<b>0.0160</b>	<b>0.0059</b>	0.0051	0.0032	<b>0.0470</b>
2	#02, 1/2 Liter	0.0048	0.0010	0.120	0.051	<b>0.0092</b>	0.0034	0.0051	0.0030	<b>0.0240</b>
3	#03, 1 Liter	0.0051	0.0010	<b>0.130</b>	0.051	0.0076	0.0032	0.0051	0.0036	0.0220
4	#04, 1 Liter	0.0046	0.0010	0.110	0.051	0.0074	0.0032	0.0051	0.0032	0.0170
5	#05, 1 Liter	0.0220	0.0033	0.110	0.051	0.0073	<b>0.0037</b>	0.0051	<b>0.0036</b>	0.0062
6	#06, 1 Liter	0.0260	0.0019	0.100	0.051	0.0037	0.0018	0.0051	<b>0.0038</b>	0.0060
7	#07, 1 Liter	<b>0.0270</b>	<b>0.0041</b>	0.096	0.051	0.0015	0.0011	0.0051	0.0031	0.0051
8	#08, 1 Liter	<b>0.0280</b>	<b>0.0039</b>	0.097	0.051	0.0013	0.0011	0.0051	0.0034	0.0052
9	#09, 3 min 1 Liter	0.0080	0.0010	0.100	0.051	0.0016	0.0014	0.0051	0.0032	0.0055

**Sample date 1/16/2013; Outside spigot; E301C03**

Flow rate = 1.57 gpm

pH = 9.60 / 9.69

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0078	0.0019	0.061	0.051	0.0370	<b>0.0130</b>	0.0051	0.0025	<b>0.0490</b>
2	#02, 1/2 Liter	0.0068	0.0010	0.094	0.051	0.0130	<b>0.0048</b>	0.0051	0.0022	0.0200
3	#03, 1 Liter	0.0320	0.0066	0.085	0.051	0.0055	0.0030	0.0051	0.0020	0.0051
4	#04, 1 Liter	<b>0.0380</b>	<b>0.0068</b>	0.085	0.051	0.0011	0.0012	0.0051	0.0020	0.0051
5	#05, 1 Liter	<b>0.0400</b>	<b>0.0091</b>	0.084	0.051	0.0013	0.0010	0.0051	0.0020	<b>0.0250</b>
6	#06, 1 Liter	0.0370	0.0066	0.085	0.051	0.0011	0.0010	0.0051	0.0020	0.0051
7	#07, 1 Liter	0.0065	0.0011	<b>0.100</b>	0.051	0.0010	0.0010	0.0051	<b>0.0026</b>	0.0051
8	#08, 3 min 1 Liter	0.0013	0.0010	<b>0.100</b>	0.051	0.0010	0.0010	0.0051	<b>0.0028</b>	0.0051

**Sample date 1/23/2013; Outside spigot; E301G29**

Flow rate = 1.46 gpm

pH = 9.70 / 9.81

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0089	0.0010	<b>0.120</b>	0.051	<b>0.0280</b>	<b>0.0048</b>	0.0051	<b>0.0023</b>	<b>0.0860</b>
2	#02, 1/2 Liter	0.0120	0.0032	0.092	0.051	<b>0.0210</b>	<b>0.0054</b>	0.0051	0.0020	<b>0.0410</b>
3	#03, 1 Liter	0.0170	<b>0.0050</b>	<b>0.098</b>	0.051	0.0051	0.0011	0.0051	<b>0.0021</b>	0.0320
4	#04, 1 Liter	<b>0.0180</b>	0.0020	0.090	0.051	0.0021	0.0015	0.0051	0.0020	0.0051
5	#05, 1 Liter	<b>0.0200</b>	<b>0.0070</b>	0.091	0.051	0.0010	0.0010	0.0051	0.0020	0.0051
6	#06, 1 Liter	0.0068	0.0015	0.095	0.051	0.0010	0.0010	0.0051	0.0023	0.0051
7	#07, 3 min 1 Liter	0.0012	0.0010	<b>0.098</b>	0.051	0.0010	0.0010	0.0051	0.0026	0.0051

**Sample date 1/30/2013; Outside spigot;****E301K65**

Flow rate = 1.59 gpm

pH = 9.66 / 9.73

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0090	0.0010	<b>0.1100</b>	0.0510	<b>0.0160</b>	<b>0.0074</b>	0.0051	0.0020	<b>0.0750</b>
2	#02, 1 Liter	0.0330	<b>0.0110</b>	0.0970	0.0510	<b>0.0072</b>	<b>0.0039</b>	0.0051	0.0020	0.0150
3	#03, 1 Liter	0.0430	<b>0.0110</b>	0.0940	0.0510	0.0014	0.0014	0.0051	0.0020	<b>0.0180</b>
4	#04, 1 Liter	<b>0.0450</b>	0.0100	0.0950	0.0510	0.0016	0.0017	0.0051	0.0020	0.0140
5	#05, 1 Liter	<b>0.0460</b>	0.0100	0.0940	0.0510	0.0010	0.0018	0.0051	0.0020	0.0110
6	#06, 1 Liter	0.0098	0.0028	<b>0.1100</b>	0.0510	0.0010	0.0012	0.0051	<b>0.0033</b>	0.0120
7	#07, 3 min 1 Liter	0.0012	0.0010	<b>0.1100</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0033</b>	0.0099

**Sample date 2/12/2013; Inside spigot; E302848**

Flow rate = 1.77 gpm

pH = 9.48 / 9.56

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.005	0.001	<b>0.11</b>	0.051	<b>0.0092</b>	<b>0.0046</b>	0.0051	0.0025	<b>0.027</b>
2	#02, 1 Liter	<b>0.027</b>	<b>0.0058</b>	0.07	0.051	0.001	0.001	0.0051	0.002	0.011
3	#03, 3 min 1 Liter	0.001	0.001	<b>0.11</b>	<b>0.058</b>	0.001	0.001	0.0051	<b>0.0031</b>	0.009
4	#04, 3 min 1 Liter	0.001	0.001	<b>0.11</b>	0.051	0.001	0.001	0.0051	<b>0.0033</b>	0.0051

**Sample date 2/13/2013; Outside spigot; E302952**

Flow rate = 1.70 gpm

pH = 9.56 / 9.66

temp = 12.7 / 7.7

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	<b>0.062</b>	0.0024	<b>0.19</b>	0.051	<b>0.02</b>	<b>0.0075</b>	0.0051	<b>0.0053</b>	<b>0.053</b>
2	#02, 1 Liter	0.031	<b>0.0053</b>	0.086	0.051	0.001	0.001	0.0051	0.0023	0.0091
3	#03, 3 min 1 Liter	0.001	0.001	0.089	0.051	0.001	0.0012	0.0051	0.0022	0.0086
4	#04, 3 min 1 Liter	0.001	0.001	0.089	0.051	0.001	0.001	0.0051	0.0022	0.0085

**Sample date 2/21/2013; Outside spigot; E302E17**

Flow rate = 2.30 gpm

pH = 9.93 / 10.02

temp = 10.2 / 8.2

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0120	0.0010	0.0920	0.0510	<b>0.0140</b>	<b>0.0061</b>	0.0051	0.0020	0.0120
2	#02, 1 Liter	<b>0.0270</b>	0.0010	0.0980	0.0510	0.0012	0.0010	0.0051	0.0022	<b>0.0140</b>
3	#03, 3 min 1 Liter	0.0010	0.0010	<b>0.1400</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0040</b>	0.0110
4	#04, 3 min 1 Liter	0.0010	0.0010	<b>0.1300</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0039</b>	0.0087

**Sample date 2/20/2013; Inside spigot; E302D40**

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0110	0.0010	0.1500	0.0510	<b>0.0011</b>	0.0010	0.0051	0.0039	0.0051
2	#02, 1 Liter	<b>0.0130</b>	<b>0.0017</b>	0.1500	0.0510	0.0010	0.0010	0.0051	0.0040	<b>0.0120</b>
3	#03, 3 min 1 Liter	0.0022	0.0010	<b>0.1600</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0043</b>	0.0110
4	#04, 3 min 1 Liter	0.0014	0.0010	<b>0.1600</b>	0.0510	0.0010	0.0010	0.0051	0.0041	0.0120

**Sample date 2/26/2013; Inside spigot; E302H07**

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1		<b>0.0018</b>	0.001	0.14	0.051	0.001	0.001	0.0051	0.0036	0.0051
2		0.0014	0.001	0.14	0.051	0.001	0.001	0.0051	0.0037	<b>0.0099</b>
3		0.0013	0.001	0.14	0.051	0.001	0.001	0.0051	<b>0.0039</b>	0.0095
4		0.0011	0.001	<b>0.15</b>	0.051	0.001	0.001	0.0051	0.0037	<b>0.0099</b>

**Sample date 2/27/2013; Outside spigot; E302159**

ATP = 104 ME/mL

Flow rate = 1.93 gpm pH = 9.78 / 9.96

temp = 13.4 / 9.6

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0049	0.0010	0.0790	0.0510	<b>0.0160</b>	<b>0.0069</b>	0.0051	0.0020	0.0092
2	<b>0.0290</b>	<b>0.0042</b>	0.0760	0.0510	0.0011	0.0010	0.0051	0.0020	0.0097
3	0.0010	0.0010	<b>0.0880</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0023</b>	<b>0.0120</b>
4	0.0010	0.0010	<b>0.0880</b>	0.0510	0.0010	0.0010	0.0051	0.0022	0.0088

**Sample date 3/5/2013; Inside spigot; E303294**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0260</b>	<b>0.0064</b>	0.0640	0.0510	<b>0.0013</b>	<b>0.0011</b>	0.0051	0.0020	0.0051
2	0.0014	0.0010	0.1200	0.0510	0.0010	0.0010	0.0051	0.0032	0.0090
3	0.0012	0.0010	<b>0.1300</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0034</b>	<b>0.0098</b>
4	0.0011	0.0010	<b>0.1300</b>	0.0510	0.0010	0.0010	0.0051	<b>0.0034</b>	<b>0.0100</b>

**Sample date 3/6/2013; Outside spigot; E303574**

ATP = 427 ME/mL

Flow rate = 2.04 gpr pH = 9.77 / 9.86

temp = 13.6 / 10.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0076	0.0016	<b>0.0610</b>	0.0510	<b>0.0120</b>	<b>0.0069</b>	0.0051	0.0020	0.0100
2	<b>0.0270</b>	<b>0.0079</b>	0.0570	0.0510	0.0011	0.0010	0.0051	0.0020	0.0110
3	0.0011	0.0010	0.0730	0.0510	0.0010	0.0010	0.0051	0.0020	0.0099
4	0.0012	0.0010	0.0710	0.0510	0.0010	0.0010	0.0051	0.0020	<b>0.0250</b>



**Sample date 4/2/2013; Inside spigot; E304160**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0032</b>	0.001	0.088	0.051	0.001	0.001		0.002	0.0051
2	0.0015	0.001	0.086	0.051	0.001	0.001		0.002	<b>0.011</b>
3	0.0014	0.001	<b>0.089</b>	0.051	0.001	0.001		<b>0.0023</b>	<b>0.011</b>

**Sample date 4/9/2013; Outside spigot;**

ATP = 3268 ME/ml

**E304A24**

Flow rate = 2.08 gpr pH = 9.76 / 9.85

temp = 18.3 / 17.2

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0130	0.0010	<b>0.0940</b>	0.0510	<b>0.0150</b>	<b>0.0061</b>		<b>0.0027</b>	<b>0.0240</b>
2	<b>0.0220</b>	<b>0.0092</b>	0.0530	0.0510	0.0057	0.0040		0.0020	0.0160
3	0.0016	0.0010	0.0540	0.0510	0.0010	0.0010		0.0020	0.0110

**Sample date 5/7/2013; Outside spigot;**

ATP = ??? ME/ml

**E305641**

Flow rate = 1.76 gpr pH = 9.86 / 9.80

temp = 20.4 / 18.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0081	0.0010	<b>0.0600</b>	0.0510	<b>0.0082</b>	<b>0.0048</b>		0.0024	<b>0.0120</b>
2	<b>0.0400</b>	<b>0.0089</b>	0.0590	0.0510	0.0012	0.0011		<b>0.0027</b>	0.0051
3	0.0027	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

**Sample date 5/14/2013; Inside spigot; E305D55**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0310</b>	<b>0.0120</b>	0.0510	0.0510	<b>0.0019</b>	<b>0.0017</b>		0.0020	<b>0.0066</b>
2	0.0058	0.0011	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051
3	0.0028	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

**Loc #3, 32 Lorimer Ave**

Two largest concentrations

Below quantitation limits

**Date: 1/10/13; outside spigot**

**E301770**

Flow rate = 2.04 gpm

pH = 9.50 / 9.63

		Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	Result	0.0140	0.0050	0.051	0.051	<b>0.0160</b>	0.0060	0.0051	0.0020	<b>0.1300</b>
2	#02, 1/2 Liter	Result	0.0230	0.0014	<b>0.220</b>	0.051	0.0100	<b>0.0071</b>	0.0051	<b>0.0058</b>	<b>0.2000</b>
3	#03, 1 Liter	Result	0.0240	0.0042	0.200	0.051	<b>0.0360</b>	<b>0.0120</b>	0.0051	<b>0.0042</b>	0.0280
4	#04, 1 Liter	Result	<b>0.0850</b>	<b>0.0100</b>	<b>0.210</b>	0.051	0.0064	0.0027	0.0051	<b>0.0042</b>	0.0230
5	#05, 1 Liter	Result	<b>0.0870</b>	<b>0.0100</b>	<b>0.210</b>	0.051	0.0019	0.0014	0.0051	0.0041	0.0220
6	#06, 1 Liter	Result	0.0470	0.0052	0.190	0.051	0.0018	0.0012	0.0051	0.0036	0.0220
7	#07, 1 Liter	Result	0.0049	0.0010	0.058	0.051	0.0012	0.0010	0.0051	0.0020	0.0220
8	#08, 3 min 1 Liter	Result	0.0023	0.0010	0.053	0.051	0.0010	0.0010	0.0051	0.0020	0.0210

**Date: 1/11/13; outside spigot**

**E301806**

Flow rate = 2.03 gpm

pH = 9.50 / 9.56

		Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	Result	0.0160	0.0054	0.051	0.051	<b>0.0120</b>	<b>0.0080</b>	0.0051	0.0020	<b>0.1100</b>
2	#02, 1/2 Liter	Result	0.0120	0.0020	<b>0.052</b>	0.051	<b>0.0120</b>	0.0068	0.0051	0.0020	<b>0.1000</b>
3	#03, 1 Liter	Result	0.0210	0.0099	0.051	0.051	<b>0.0250</b>	<b>0.0140</b>	0.0051	0.0020	0.0280
4	#04, 1 Liter	Result	<b>0.0520</b>	<b>0.0230</b>	<b>0.053</b>	0.051	0.0041	0.0032	0.0051	0.0020	0.0220
5	#05, 1 Liter	Result	<b>0.0500</b>	<b>0.0210</b>	0.051	0.051	0.0018	0.0016	0.0051	0.0020	0.0250
6	#06, 1 Liter	Result	0.0220	0.0025	0.150	0.051	0.0017	0.0012	0.0051	0.0042	0.0230
7	#07, 1 Liter	Result	0.0040	0.0010	0.150	0.051	0.0012	0.0010	0.0051	<b>0.0048</b>	0.0190
8	#08, 3 min 1 Liter	Result	0.0025	0.0010	0.140	0.051	0.0010	0.0010	0.0051	<b>0.0049</b>	0.0230

Date: 1/14/13; inside faucet

E301A06

Flow rate = 1.75 gpm

pH = 9.17 / 9.31

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01, 1/2 Liter	Result	0.0120	0.0036	0.074	0.051	<b>0.0450</b>	<b>0.0240</b>	0.0051	<b>0.0026</b>	0.0290
2 #02, 1/2 Liter	Result	0.0170	0.0012	<b>0.088</b>	0.051	<b>0.0320</b>	0.0140	0.0051	<b>0.0026</b>	<b>0.0490</b>
3 #03, 1 Liter	Result	0.0180	0.0054	<b>0.084</b>	0.051	0.0300	<b>0.0150</b>	0.0051	0.0022	<b>0.0330</b>
4 #04, 1 Liter	Result	0.0370	0.0130	0.076	0.051	0.0190	0.0095	0.0051	0.0020	0.0210
5 #05, 1 Liter	Result	<b>0.0700</b>	<b>0.0240</b>	0.082	0.051	0.0042	0.0026	0.0051	0.0021	0.0180
6 #06, 1 Liter	Result	<b>0.0640</b>	<b>0.0180</b>	0.074	0.051	0.0028	0.0018	0.0051	0.0020	0.0160
7 #07, 1 Liter	Result	0.0140	0.0042	0.054	0.051	0.0023	0.0018	0.0051	0.0024	0.0160
8 #08, 3 min 1 Liter	Result	0.0026	0.0015	0.051	0.051	0.0020	0.0017	0.0051	0.0020	0.0170

Date: 1/22/13; outside spigot

E301F55

Flow rate = 2.66 gpm

pH = 9.74 / 9.76

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01 1/2 Liter	Result	0.0290	0.0034	<b>0.130</b>	0.051	<b>0.0210</b>	<b>0.0080</b>	0.0051	<b>0.0040</b>	<b>0.5600</b>
2 #02 1 Liter	Result	0.0230	0.0120	0.051	0.051	<b>0.0200</b>	<b>0.0150</b>	0.0051	0.0020	<b>0.0200</b>
3 #03 1 Liter	Result	<b>0.0450</b>	<b>0.0220</b>	0.051	0.051	0.0048	0.0047	0.0051	0.0020	0.0140
4 #04 1 Liter	Result	<b>0.0390</b>	<b>0.0190</b>	0.051	0.051	0.0023	0.0018	0.0051	0.0020	0.0140
5 #05 1 Liter	Result	0.0120	0.0027	<b>0.072</b>	0.051	0.0017	0.0016	0.0051	0.0020	0.0099
6 #06 1 Liter	Result	0.0035	0.0010	0.065	0.051	0.0014	0.0011	0.0051	0.0020	0.0067
7 #07 3 min 1 Liter	Result	0.0022	0.0010	0.064	0.051	0.0010	0.0010	0.0051	0.0020	0.0051

Date: 1/24/13; outside spigot

E301G88

Flow rate = 2.21 gpm

pH = 9.64

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01 1/2 Liter	Result	0.0150	0.0028	0.056	0.051	<b>0.0310</b>	<b>0.0150</b>	0.0051	0.0020	<b>0.0710</b>
2 #02 1 Liter	Result	<b>0.0370</b>	0.0200	0.051	0.051	<b>0.0170</b>	<b>0.0120</b>	0.0051	0.0020	<b>0.0090</b>
3 #03 1 Liter	Result	<b>0.0500</b>	<b>0.0390</b>	0.051	0.051	0.0029	0.0020	0.0051	0.0020	0.0051
4 #04 1 Liter	Result	0.0350	<b>0.0250</b>	0.053	0.051	0.0021	0.0018	0.0051	0.0020	0.0051
5 #05 1 Liter	Result	0.0085	0.0015	<b>0.070</b>	0.051	0.0016	0.0014	0.0051	0.0020	0.0051
6 #06 1 Liter	Result	0.0032	0.0020	0.060	0.051	0.0016	0.0012	0.0051	0.0020	0.0051
7 #07 3 min 1 Liter	Result	0.0021	0.0014	<b>0.062</b>	0.051	0.0012	0.0015	0.0051	0.0020	0.0051

Date: 2/11/13; inside faucet

E302695

Flow rate = 1.72 gpm

pH = 9.32 / 9.43

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01, 1/2 Liter		0.016	0.0041	0.051	0.051	<b>0.031</b>	<b>0.016</b>	0.0051	0.002	<b>0.019</b>
2 #02, 1 Liter		<b>0.044</b>	<b>0.016</b>	0.051	0.051	0.0029	0.0021	0.0051	0.002	0.01
3 #03, 3 min 1 Liter		0.0023	0.001	<b>0.063</b>	0.051	0.0014	0.0013	0.0051	0.002	0.0092

Date: 2/14/13; outside spigot

E302A39

Flow rate = 2.04 gpm

pH = 9.46 / 9.69

temp = 13.5 / 10.2

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01, 1/2 Liter		0.0340	0.0043	<b>0.1600</b>	0.0510	<b>0.0150</b>	<b>0.0049</b>	0.0051	<b>0.0029</b>	<b>1.4000</b>
2 #02, 1 Liter		<b>0.0480</b>	<b>0.0150</b>	0.0510	0.0510	0.0020	0.0017	0.0051	0.0020	0.0160
3 #03, 3 min 1 Liter		0.0018	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0110

Date: 2/18/13; inside faucet

E302C09

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01, 1/2 Liter	0.0210	0.0076	0.0580	0.0510	<b>0.0230</b>	<b>0.0140</b>	0.0051	0.0020	<b>0.0170</b>	
2 #02, 1 Liter	<b>0.0500</b>	<b>0.0220</b>	<b>0.0680</b>	0.0510	0.0031	0.0022	0.0051	0.0020	0.0120	
3 #03, 3 min 1 Liter	0.0020	0.0010	0.0510	0.0510	0.0012	0.0010	0.0051	0.0020	0.0093	

Date: 2/22/13; outside spigot

E302F62

Flow rate = 2.82 gpm

pH = 9.69 / 9.77

temp = 23.5 / 11.3

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01, 1/2 Liter	0.0240	0.0022	<b>0.0860</b>	0.0510	<b>0.0160</b>	<b>0.0110</b>	0.0051	<b>0.0024</b>	<b>0.6800</b>	
2 #02, 1 Liter	<b>0.0300</b>	<b>0.0086</b>	0.0510	0.0510	0.0025	0.0022	0.0051	0.0020	0.0210	
3 #03, 3 min 1 Liter	0.0018	0.0010	0.0620	0.0510	0.0010	0.0012	0.0051	0.0020	0.0150	

Date: 2/25/13; outside spigot

E302H06

Flow rate = 2.89 gpm

pH = 9.87 / 9.91

temp = 15.9 / 10.5

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1	0.0130	0.0068	<b>0.0560</b>	0.0510	<b>0.0097</b>	<b>0.0053</b>	0.0051	0.0020	<b>0.3000</b>	
2	<b>0.0460</b>	<b>0.0180</b>	0.0510	0.0510	0.0019	0.0018	0.0051	0.0020	0.0150	
3	0.0017	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0120	

Date: 2/28/13; inside faucet

E303075

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1	0.0096	0.0044	0.0510	0.0510	<b>0.0280</b>	<b>0.0180</b>	0.0051	0.0020	<b>0.0160</b>	
2	<b>0.0370</b>	<b>0.0170</b>	0.0510	0.0510	0.0025	0.0018	0.0051	0.0020	0.0140	
3	0.0019	0.0010	0.0510	0.0510	0.0011	0.0010	0.0051	0.0020	0.0092	

**Date: 3/4/13; outside spigot****E303295**

ATP = 582 ME/mL

Flow rate = 3.12 gpm

pH = 9.82 / 9.94

temp = 12.8 / 9.1

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0093	0.0022	0.0540	0.0510	<b>0.0230</b>	<b>0.0140</b>	0.0051	0.0020	<b>0.1100</b>
2	<b>0.0370</b>	<b>0.0180</b>	0.0510	0.0510	0.0020	0.0016	0.0051	0.0020	0.0230
3	0.0017	0.0010	<b>0.0550</b>	0.0510	0.0010	0.0010	0.0051	0.0020	0.0130

**Date: 3/7/13; inside spigot****E303641**

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	<b>0.0100</b>	<b>0.0045</b>	0.0510	0.0510	<b>0.0240</b>	<b>0.0160</b>	0.0051	0.0020	0.0180
2	0.0063	0.0010	0.1200	0.0510	0.0016	0.0012	0.0051	0.0025	<b>0.0310</b>
3	0.0120	0.0010	<b>17.0000</b>	<b>0.2100</b>	0.0110	0.0089	0.0050	<b>0.1800</b>	0.0280

**Date: 3/8/13; inside spigot****E303642**

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0079	0.0035	<b>0.0590</b>	0.0510	<b>0.0170</b>	<b>0.0120</b>		0.0020	<b>0.0140</b>
2	<b>0.0430</b>	<b>0.0210</b>	0.0510	0.0510	0.0024	0.0010		0.0020	0.0094
3	0.0024	0.0010	0.0530	0.0510	0.0013	0.0010		0.0020	0.0110

**Date: 4/2/13; outside faucet****E304340**

ATP = 1782 ME/mL

Flow rate = 2.04 gpm

pH = 9.18 / 9.19

temp = 12.9 / 11.1

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	<b>0.0910</b>	<b>0.0073</b>	<b>0.8500</b>	0.0510	<b>0.0280</b>	<b>0.0054</b>		<b>0.0110</b>	<b>1.8000</b>
2	0.0420	0.0250	0.0510	0.0510	0.0018	0.0014		0.0020	0.0240
3	0.0025	0.0012	0.0510	0.0510	0.0010	0.0010		0.0020	0.0110

**Date: 5/7/13; outside faucet**

**E305743**

ATP = ??? ME/mL

Flow rate = 2.77 gpm

pH = 9.86 / 9.93

temp = 22.4 / 19.0

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0270	0.0022	<b>0.1100</b>	0.0510	<b>0.0087</b>	<b>0.0035</b>		<b>0.0024</b>	<b>2.5000</b>
2	<b>0.0750</b>	<b>0.0410</b>	0.0510	0.0510	0.0021	0.0015		0.0020	0.0480
3	0.0048	0.0016	0.0510	0.0510	0.0010	0.0010		0.0020	0.0057

**Date: 5/15/13; inside spigot**

**E305F21**

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0100	0.0040	0.0510	0.0510	<b>0.0087</b>	<b>0.0058</b>		0.0020	<b>0.0120</b>
2	<b>0.0820</b>	<b>0.0520</b>	0.0510	0.0510	0.0023	0.0015		0.0020	0.0051
3	0.0058	0.0027	0.0510	0.0510	0.0016	0.0017		0.0020	0.0051

**Loc #4, 56 Gentian Ave**

**Two largest concentrations**

Below quantitation limits

**Date: 1/15/13; inside faucet**

**E301A44**

Flow rate = 1.48 gpm

pH = 9.50 / 9.59

Sample#:		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0077	<b>0.0019</b>	0.051	0.051	<b>0.0220</b>	0.0150	0.0051	0.002	0.0220
2	#02, 1/2 Liter	<b>0.0080</b>	<b>0.0025</b>	0.051	0.051	0.0120	0.0088	0.0051	0.002	0.0051
3	#03, 1 Liter	0.0055	0.0010	<b>0.120</b>	0.051	<b>0.0140</b>	0.0059	0.0051	0.002	<b>0.0240</b>
4	#04, 1 Liter	<b>0.0081</b>	0.0012	<b>0.130</b>	0.051	0.0052	0.0034	0.0051	0.002	0.0190
5	#05, 1 Liter	0.0042	0.0012	0.051	0.051	0.0024	0.0018	0.0051	0.002	<b>0.0300</b>
6	#06, 1 Liter	0.0021	0.0010	0.051	0.051	0.0024	0.0020	0.0051	0.002	0.0200
7	#07, 1 Liter	0.0019	0.0010	0.051	0.051	0.0021	0.0021	0.0051	0.002	0.0180
8	#08, 1 Liter	0.0013	0.0010	0.051	0.051	0.0012	0.0012	0.0051	0.002	0.0180
9	#09, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0220
10	#10, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0150

**Date: 1/17/13; outside spigot**

**E301C76**

Flow rate = 1.30 gpm

pH = 9.84 / 9.91

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#02, 1/2 Liter	<b>0.0150</b>	<b>0.0078</b>	0.051	0.051	<b>0.0043</b>	<b>0.0031</b>	0.0051	0.002	0.0080
2	#03, 1 Liter	<b>0.0039</b>	<b>0.0016</b>	0.051	0.051	<b>0.0028</b>	<b>0.0024</b>	0.0051	0.002	0.0190
3	#04, 1 Liter	0.0034	0.0010	0.051	0.051	0.0017	0.0016	0.0051	0.002	0.0170
4	#05, 1 Liter	0.0019	0.0010	0.051	0.051	0.0011	0.0010	0.0051	0.002	<b>0.0310</b>
5	#06, 1 Liter	0.0015	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0170
6	#07, 1 Liter	0.0016	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0170
7	#08, 1 Liter	0.0014	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	<b>0.0220</b>
8	#09, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0160
9	#10, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0051



Date: 1/23/13; outside spigot

E301G28

Flow rate = 1.38 gpm

pH = 9.61 / 9.75

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0170</b>	<b>0.0055</b>	0.051	0.051	<b>0.0090</b>	<b>0.0054</b>	0.0051	0.002	0.0051
2	#02, 1 Liter	0.0086	<b>0.0033</b>	0.051	0.051	<b>0.0052</b>	<b>0.0034</b>	0.0051	0.002	<b>0.0091</b>
3	#03, 1 Liter	<b>0.0110</b>	0.0030	0.051	0.051	0.0018	0.0013	0.0051	0.002	0.0051
4	#04, 1 Liter	0.0036	0.0010	0.051	0.051	0.0014	0.0011	0.0051	0.002	0.0051
5	#05, 1 Liter	0.0016	0.0010	0.051	0.051	0.0013	0.0010	0.0051	0.002	0.0051
6	#06, 1 Liter	0.0014	0.0010	0.051	0.051	0.0012	0.0010	0.0051	0.002	0.0051
7	#07, 1 Liter	0.0014	0.0010	0.051	0.051	0.0010	0.0011	0.0051	0.002	0.0051
8	#08, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051
9	#09, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051

Date: 1/25/13; outside spigot

E301H02

Flow rate = 1.52 gpm

pH = 9.66 / 9.79

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0084	0.0019	0.051	0.051	<b>0.0200</b>	<b>0.0080</b>	0.0051	0.002	<b>0.0300</b>
2	#02, 1 Liter	<b>0.0110</b>	<b>0.0030</b>	0.051	0.051	<b>0.0120</b>	<b>0.0062</b>	0.0051	0.002	<b>0.0330</b>
3	#03, 1 Liter	<b>0.0180</b>	<b>0.0038</b>	0.051	0.051	0.0022	0.0016	0.0051	0.002	0.0051
4	#04, 1 Liter	0.0044	0.0010	0.051	0.051	0.0016	0.0013	0.0051	0.002	0.0051
5	#05, 1 Liter	0.0016	0.0010	0.051	0.051	0.0016	0.0018	0.0051	0.002	0.0051
6	#06, 1 Liter	0.0014	0.0010	0.051	0.051	0.0013	0.0013	0.0051	0.002	0.0051
7	#07, 1 Liter	0.0014	0.0010	0.051	0.051	0.0022	0.0023	0.0051	0.002	0.0051
8	#08, 1 Liter	0.0014	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0051
9	#09, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051

Date: 1/28/13; outside spigot

E301H38

Flow rate = 1.57 gpm

pH = 9.52 / 9.72

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0230	0.0077	0.055	0.051	0.0250	0.0200	0.0051	0.002	0.0051
2	#02, 1 Liter	0.0180	0.0100	0.051	0.051	0.0170	0.0140	0.0051	0.002	0.0190
3	#03, 1 Liter	0.0300	0.0160	0.051	0.051	0.0030	0.0025	0.0051	0.002	0.0051
4	#04, 1 Liter	0.0063	0.0020	0.051	0.051	0.0022	0.0015	0.0051	0.002	0.0051
5	#05, 1 Liter	0.0017	0.0010	0.051	0.051	0.0016	0.0014	0.0051	0.002	0.0051
6	#06, 1 Liter	0.0015	0.0012	0.051	0.051	0.0019	0.0016	0.0051	0.002	0.0051
7	#07, 1 Liter	0.0014	0.0010	0.051	0.051	0.0012	0.0010	0.0051	0.002	0.0051
8	#08, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051
9	#09, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0051

Date: 2/11/13; outside faucet

E302594

Flow rate = 1.82 gpm

pH = 9.74 / 9.78

temp = 3.4 / 2.8

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0041	0.001	0.051	0.051	0.0055	0.0034	0.0051	0.002	0.0051
2	#02, 1 Liter **	0.0013	0.001	0.051	0.051	0.0012	0.0012	0.0051	0.002	0.0088
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0087

Date: 2/12/13; inside spigot

E302694

Flow rate = 1.90 gpm

pH = 9.71 / 9.72

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.011	0.001	0.055	0.051	0.0045	0.0025	0.0051	0.002	0.0051
2	#02, 1 Liter **	0.0013	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0096
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0092

**Date: 2/18/13; inside faucet****E302A72**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0100</b>	<b>0.0022</b>	0.0510	0.0510	<b>0.0061</b>	<b>0.0041</b>	0.0051	0.0020	0.0051
2	#02, 1 Liter **	0.0012	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	<b>0.0086</b>
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0083

**Date: 2/19/13; outside spigot****E302C07**

Flow rate = 0.88 gpm

pH = 9.75 / 9.82

temp =10.2 / 6.7

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0110</b>	<b>0.0020</b>	0.0510	0.0510	<b>0.0045</b>	<b>0.0022</b>	0.0051	0.0020	0.0056
2	#02, 1 Liter **	0.0018	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	<b>0.0096</b>
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0091

**Date: 2/25/13; outside spigot****E302G22**

Flow rate = 1.21 gpm

pH = 9.82 / 9.97

temp =13.9 / 8.9

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		<b>0.0100</b>	<b>0.0039</b>	0.0510	0.0510	<b>0.0098</b>	<b>0.0089</b>	0.0051	0.0020	0.0051
2		<b>0.0100</b>	0.0014	0.0510	0.0510	0.0014	0.0020	0.0051	0.0020	<b>0.0094</b>
3		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	<b>0.0093</b>

**Date: 2/26/13; inside faucet****E302H08**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		<b>0.011</b>	0.0031	0.051	0.051	<b>0.01</b>	<b>0.0069</b>	0.0051	0.002	0.0051
2		0.007	<b>0.0034</b>	0.051	0.051	0.0014	0.0013	0.0051	0.002	<b>0.0093</b>
3		0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0075

Date: 3/4/13; outside spigot

E303185

ATP = 256 ME/mL

Flow rate = 1.15 gpm

pH = 9.90 / 9.99

temp = 10.2 / 8.4

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0080	0.0050	0.0510	0.0510	<b>0.0120</b>	<b>0.0092</b>	0.0051	0.0020	0.0060
2	<b>0.0120</b>	<b>0.0060</b>	0.0510	0.0510	0.0016	0.0014	0.0051	0.0020	<b>0.0120</b>
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0089

Date: 3/5/13; inside faucet

E303293

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0096</b>	<b>0.0037</b>	0.0510	0.0510	<b>0.0150</b>	<b>0.0100</b>	0.0051	0.0020	0.0051
2	0.0093	0.0032	0.0510	0.0510	0.0018	0.0019	0.0051	0.0020	<b>0.0120</b>
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0091

Date: 4/2/13; outside faucet

E304159

ATP = 145 ME/mL

Flow rate = 1.33 gpm

pH = 10.12 / 9.80

temp = 9.7 / 7.6

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0027	0.0010	0.0510	0.0510	<b>0.0044</b>	<b>0.0033</b>		0.0020	0.0150
2	<b>0.0059</b>	<b>0.0026</b>	0.0510	0.0510	0.0010	0.0010		0.0020	0.0120
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	<b>0.0180</b>

Date: 4/8/13; inside faucet

E304643

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0110</b>	<b>0.0052</b>	0.0510	0.0510	0.0093	0.0071		0.0020	0.0051
2	0.0079	0.0038	0.0510	0.0510	<b>0.0098</b>	<b>0.0072</b>		0.0020	<b>0.0140</b>
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0110

**Date: 5/9/13; outside faucet**

**E305879**

ATP = ??? ME/mL

Flow rate = 1.38 gpm

pH = 9.91 / 10.0

temp = 17.5 / 14.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0094	0.0051	0.0510	0.0510	<b>0.0097</b>	<b>0.0072</b>		0.0020	<b>0.0074</b>
2	<b>0.0260</b>	<b>0.0150</b>	0.0510	0.0510	0.0014	0.0012		0.0020	0.0051
3	0.0023	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

**Date: 5/15/13; inside faucet**

**E305D56**

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

1	0.0098	0.0026	0.0510	0.0510	<b>0.0100</b>	<b>0.0061</b>		0.0020	0.0051
2	<b>0.0380</b>	<b>0.0130</b>	0.0520	0.0510	0.0016	0.0013		0.0020	0.0051
3	0.0023	0.0010	<b>0.0720</b>	0.0510	0.0010	0.0010		<b>0.0023</b>	0.0051

**Loc # 5, 42 Harkness Street**

Two largest concentrations

Below quantitation limits

**Date: 1/8/13; outside spigot**

**E301630**

Flow rate = pH = 9.66 / 9.79

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0110	0.0065	0.051	0.051	<b>0.0470</b>	<b>0.0330</b>	0.0051	<b>0.0036</b>	0.0180
2	#02, 1/2 Liter	0.0083	0.0039	0.051	0.051	<b>0.0690</b>	<b>0.0290</b>	0.0051	<b>0.0034</b>	0.0067
3	#03, 1 Liter	0.0038	0.0023	0.051	0.051	0.0460	0.0280	0.0051	0.0027	<b>0.0270</b>
4	#04, 1 Liter	<b>0.0220</b>	<b>0.0150</b>	0.051	0.051	0.0059	0.0046	0.0051	0.0022	<b>0.0190</b>
5	#05, 1 Liter	<b>0.0150</b>	<b>0.0093</b>	0.051	0.051	0.0021	0.0019	0.0051	0.0020	0.0051
6	#06, 3 min 1 Liter	0.0019	0.0010	0.051	0.051	0.0059	0.0043	0.0051	0.0020	0.0051

**Date: 1/9/13; outside spigot**

**E301689**

Flow rate = 2.20 gpm pH = 9.44 / 9.57

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0150</b>	0.0061	0.051	0.051	<b>0.1000</b>	<b>0.0300</b>	0.0051	0.0020	<b>0.0150</b>
2	#02, 1/2 Liter	0.0067	0.0017	0.051	0.051	<b>0.0460</b>	<b>0.0240</b>	0.0051	0.0020	0.0051
3	#03, 1 Liter	<b>0.0150</b>	<b>0.0088</b>	0.051	0.051	0.0140	0.0099	0.0051	0.0020	<b>0.0730</b>
4	#04, 1 Liter	<b>0.0330</b>	<b>0.0190</b>	0.051	0.051	0.0021	0.0016	0.0051	0.0020	0.0058
5	#05, 1 Liter	0.0047	0.0010	0.051	0.051	0.0014	0.0012	0.0051	<b>0.0041</b>	0.0051
6	#06, 3 min 1 Liter	0.0017	0.0010	0.051	0.051	0.0031	0.0019	0.0051	<b>0.0042</b>	0.0062

**Date: 1/23/13; inside faucet****E301G27**

Flow rate = 0.99 gpm

pH = 9.43 / 9.40

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0028	0.0010	0.051	0.051	0.0099	0.0091	0.0051	0.0020	<b>0.0540</b>
2	#02, 1 Liter	0.0026	0.0012	0.051	0.051	0.0130	0.0094	0.0051	0.0020	<b>0.0560</b>
3	#03, 1 Liter	0.0029	0.0017	0.051	0.051	<b>0.0200</b>	<b>0.0160</b>	0.0051	0.0020	0.0160
4	#04, 1 Liter	0.0084	0.0026	0.051	0.051	<b>0.0150</b>	<b>0.0100</b>	0.0051	0.0020	0.0480
5	#05, 1 Liter	<b>0.0280</b>	<b>0.0170</b>	0.051	0.051	0.0034	0.0028	0.0051	0.0020	0.0160
6	#06, 1 Liter	<b>0.0096</b>	<b>0.0028</b>	<b>0.055</b>	0.051	0.0018	0.0015	0.0051	<b>0.0026</b>	0.0051
7	#07, 3 min 1 Liter	0.0010	0.0010	<b>0.064</b>	0.051	0.0010	0.0010	0.0051	<b>0.0029</b>	0.0051

**Date: 1/25/13; outside spigot****E301G94**

Flow rate = 3.31 gpm

pH = 9.37 / 9.63

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0360</b>	<b>0.0100</b>	<b>0.120</b>	0.051	<b>0.0230</b>	<b>0.0110</b>	0.0051	0.0023	<b>0.0910</b>
2	#02, 1 Liter	<b>0.0220</b>	<b>0.0074</b>	<b>0.094</b>	0.051	<b>0.0046</b>	0.0024	0.0051	0.0030	0.0051
3	#03, 1 Liter	0.0013	0.0010	0.065	0.051	0.0027	<b>0.0025</b>	0.0051	<b>0.0032</b>	0.0051
4	#04, 1 Liter	0.0011	0.0010	0.064	0.051	0.0020	0.0012	0.0051	<b>0.0031</b>	0.0051
5	#05, 3 min 1 Liter	0.0010	0.0010	0.058	0.051	0.0010	0.0010	0.0051	<b>0.0031</b>	0.0051

**Date: 1/30/13; outside spigot****E301J95**

Flow rate = 2.95 gpm

pH = 9.25 / 9.61

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0150</b>	0.0023	<b>0.0520</b>	0.0510	<b>0.0940</b>	<b>0.0300</b>	0.0051	0.0020	0.0092
2	#02, 1 Liter	0.0120	<b>0.0059</b>	0.0510	0.0510	<b>0.0460</b>	<b>0.0200</b>	0.0051	0.0020	<b>0.0780</b>
3	#03, 1 Liter	<b>0.0300</b>	<b>0.0160</b>	0.0510	0.0510	0.0033	0.0028	0.0051	0.0020	<b>0.0160</b>
4	#04, 1 Liter	0.0057	0.0010	0.0510	0.0510	0.0022	0.0027	0.0051	0.0020	0.0110
5	#05, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0014	0.0051	0.0020	0.0130

**Date: 2/13/13; inside spigot****E302845**

Flow rate = 1.00 gpm

pH = 9.49 / 9.48

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0021	0.001	0.051	0.051	<b>0.011</b>	<b>0.0072</b>	0.0051	0.002	<b>0.055</b>
2	#02, 1 Liter	<b>0.02</b>	<b>0.0087</b>	0.051	0.051	0.0072	0.004	0.0051	0.002	0.046
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.002	0.0012	0.0051	0.002	0.011

**Date: 2/15/13; outside spigot****E302A02**

Flow rate = 2.51 gpm

pH = 9.56 / 9.70

temp = 18.0 / 14.5

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.016	0.0021	0.051	0.051	<b>0.75</b>	<b>0.038</b>	0.0051	0.002	0.01
2	#02, 1 Liter	<b>0.024</b>	<b>0.014</b>	0.051	0.051	0.0093	0.0059	0.0051	0.002	<b>0.041</b>
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0091

**Date: 2/22/13; outside spigot****E302F63**

Flow rate = 3.06 gpm

pH = 9.59 / 9.86

temp = 15.4 / 10.1

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0100	0.0030	0.0510	0.0510	<b>0.1300</b>	<b>0.0520</b>	0.0051	0.0020	0.0088
2	#02, 1 Liter	<b>0.0240</b>	<b>0.0140</b>	0.0510	0.0510	0.0069	0.0038	0.0051	<b>0.0046</b>	<b>0.0590</b>
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0011	0.0051	0.0020	0.0092

**Date: 2/27/13; outside spigot****E302I27**

ATP = 95 ME/mL

Flow rate = 3.01 gpm

pH = 9.67 / 9.87

temp = 16.6 / 10.3

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0036	0.0010	0.0510	0.0510	<b>0.0830</b>	<b>0.0260</b>	0.0051	0.0020	0.0063
2		<b>0.0240</b>	<b>0.0130</b>	0.0510	0.0510	0.0030	0.0020	0.0051	0.0020	<b>0.0140</b>
3		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	<b>0.0030</b>	0.0097



**Date: 3/1/13; inside spigot**

**E303080**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0016	0.0010	0.0510	<b>0.0081</b>	<b>0.0059</b>	0.0510	0.0051	0.0020	<b>0.0640</b>
2	<b>0.0190</b>	<b>0.0130</b>	0.0510	0.0079	0.0040	0.0510	0.0051	0.0020	0.0510
3	0.0010	0.0010	0.0510	0.0023	0.0011	0.0510	0.0051	0.0020	0.0099

**Date: 3/6/13; outside spigot**

**E303459**

ATP = 345 ME/mL      Flow rate = 3.73 gpm      pH = 9.72 / 9.87      temp = 16.3 / 10.9

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0170	0.0013	<b>0.0680</b>	0.0510	<b>0.0960</b>	<b>0.0240</b>	0.0051	0.0020	0.0110
2	<b>0.0240</b>	<b>0.0140</b>	0.0510	0.0510	0.0058	0.0045	0.0051	0.0020	<b>0.0160</b>
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

**Date: 3/8/13; inside spigot**

**E303639**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0016	0.0010	0.0510	0.0510	<b>0.0073</b>	<b>0.0056</b>	0.0051	0.0020	<b>0.0610</b>
2	<b>0.0180</b>	<b>0.0120</b>	0.0510	0.0510	0.0041	0.0030	0.0051	0.0020	0.0480
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

**Date: 4/8/13; outside spigot**

**E304642**

ATP = 1904 ME/mL      Flow rate = 2.91 gpm      pH = 10.02 / 10.16      temp = 13.8 / 12.2

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0200	0.0047	0.0510	0.0510	<b>2.9000</b>	<b>0.3800</b>		0.0020	0.0200
2	<b>0.0270</b>	<b>0.0180</b>	0.0510	0.0510	0.0250	0.0120		0.0020	<b>0.0330</b>
3	0.0011	0.0010	0.0510	0.0510	0.0014	0.0011		0.0020	0.0091

**Date: 4/12/13; inside spigot**

**E304A65**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	<b>0.0029</b>	<b>0.0014</b>	0.0510	0.0510	0.0072	0.0058		0.0020	<b>0.0370</b>
2	0.0025	0.0010	0.0510	0.0510	<b>0.0190</b>	<b>0.0060</b>		0.0020	0.0180
3	0.0016	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0110

**Date: 5/7/13; outside spigot**

**E305644**

ATP = ??? ME/mL

Flow rate = 3.09 gpm

pH = 10.05 / 9.69

temp = 12.0 / 11.2

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0170	0.0023	<b>0.8300</b>	0.0510	<b>0.1600</b>	<b>0.0240</b>		<b>0.0040</b>	<b>0.0090</b>
2	<b>0.0710</b>	<b>0.0270</b>	0.0790	0.0510	0.0039	0.0026		0.0020	0.0051
3	0.0060	0.0012	0.3200	0.0510	0.0017	0.0010		0.0034	0.0051

**Date: 5/14/13; inside spigot**

**E305C74**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0019	0.0012	0.0510	0.0510	<b>0.0039</b>	<b>0.0033</b>		0.0020	<b>0.0560</b>
2	<b>0.0280</b>	<b>0.0200</b>	0.0510	0.0510	0.0025	0.0019		0.0020	0.0170
3	0.0019	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

**Loc #6, 104 Shaw Ave**

Two largest concentrations

Below quantitation limits

**Date: 1/11/13; inside faucet**

**E301808**

Flow rate = 1.30 gpm

pH = 9.43 / 9.60

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	
									Zinc	
1	#01, 1/2 Liter	<b>0.0780</b>	0.0042	0.16	0.051	<b>0.3200</b>	0.0160	0.0051	0.0025	<b>3.3000</b>
2	#02, 1/2 Liter	0.0085	0.0010	0.12	0.051	<b>0.0570</b>	0.0190	0.0051	0.0020	<b>0.0900</b>
3	#03, 1 Liter	0.0086	0.0021	0.11	0.051	0.0550	<b>0.0250</b>	0.0051	0.0020	0.0350
4	#04, 1 Liter	0.0092	0.0023	0.11	0.051	0.0460	<b>0.0220</b>	0.0051	0.0020	0.0160
5	#05, 1 Liter	0.0250	0.0055	0.10	0.051	0.0290	0.0130	0.0051	0.0020	0.0150
6	#06, 1 Liter	0.0360	0.0043	0.11	0.051	0.0140	0.0062	0.0051	0.0020	0.0140
7	#07, 1 Liter	0.0510	0.0087	0.11	0.051	0.0064	0.0029	0.0051	0.0020	0.0340
8	#08, 1 Liter	<b>0.0580</b>	<b>0.0090</b>	0.12	0.051	0.0032	0.0017	0.0051	0.0020	0.0210
9	#09, 1 Liter	<b>0.0580</b>	<b>0.0088</b>	0.14	0.051	0.0034	0.0018	0.0051	0.0020	0.0280
10	#10, 1 Liter	0.0500	0.0065	0.20	0.051	0.0026	0.0014	0.0051	0.0020	0.0060
11	#11, 1 Liter	0.0310	0.0035	0.24	0.051	0.0024	0.0022	0.0051	0.0031	0.0220
12	#12, 1 Liter	0.0100	0.0011	<b>0.29</b>	0.051	0.0021	0.0014	0.0051	<b>0.0042</b>	0.0210
13	#13, 3 min 1 Liter	0.0026	0.0010	<b>0.30</b>	<b>0.058</b>	0.0015	0.0010	0.0051	<b>0.0044</b>	0.0240

**Date: 1/17/13; outside spigot**

**E301C78**

Flow rate = 1.80 gpm

pH = 9.61 / 9.78

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	
									Zinc	
1	#02, 1/2 Liter	0.0078	0.0014	<b>0.36</b>	0.051	<b>0.1000</b>	<b>0.0300</b>	0.0051	<b>0.0033</b>	0.0068
2	#03, 1 Liter	0.0072	0.0032	0.18	<b>0.062</b>	<b>0.0580</b>	<b>0.0350</b>	0.0051	0.0021	0.0051
3	#04, 1 Liter	0.0072	0.0029	0.13	0.051	0.0430	0.0250	0.0051	0.0020	0.0051
4	#05, 1 Liter	0.0082	0.0037	0.13	<b>0.051</b>	0.0470	0.0290	0.0051	0.0020	0.0051
5	#06, 1 Liter	0.0120	0.0014	0.12	0.051	0.0230	0.0100	0.0051	0.0020	<b>0.0210</b>
6	#07, 1 Liter	0.0450	0.0077	0.11	0.051	0.0071	0.0036	0.0051	0.0020	0.0051
7	#08, 1 Liter	0.0550	0.0140	0.12	0.051	0.0036	0.0022	0.0051	0.0020	0.0051
8	#09, 1 Liter	<b>0.0600</b>	<b>0.0190</b>	0.12	0.051	0.0031	0.0020	0.0051	0.0020	0.0200
9	#10, 1 Liter	<b>0.0570</b>	<b>0.0200</b>	0.12	0.051	0.0028	0.0019	0.0051	0.0020	<b>0.0240</b>
10	#11, 1 Liter	0.0240	0.0070	0.21	0.057	0.0025	0.0014	0.0051	0.0030	0.0051
11	#12, 3 min 1 Liter	0.0024	0.0010	<b>0.25</b>	0.051	0.0013	0.0010	0.0051	<b>0.0041</b>	0.0051

**Date: 1/22/13; outside spigot**

**E301F56**

Flow rate = 1.15 gpm                      pH = 9.55 / 9.74

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	<b>0.1400</b>	0.0024	<b>1.40</b>	<b>0.078</b>	<b>0.1400</b>	<b>0.0310</b>	<b>0.015</b>	<b>0.0065</b>	<b>0.0470</b>
2	#02 1 Liter	0.0100	0.0031	<b>0.32</b>	0.062	<b>0.0610</b>	<b>0.0260</b>	0.0051	0.0025	0.0220
3	#03 1 Liter	0.0059	0.0011	<b>0.32</b>	0.058	0.0220	0.0077	0.0051	0.0034	<b>0.0260</b>
4	#04 1 Liter	0.0046	0.0026	0.31	<b>0.074</b>	0.0150	0.0066	0.0051	<b>0.0037</b>	0.0200
5	#05 1 Liter	0.0049	0.0010	0.30	0.051	0.0110	0.0037	0.0051	0.0033	0.0051
6	#06 1 Liter	0.0130	0.0027	0.30	0.056	0.0058	0.0025	0.0051	0.0035	0.0240
7	#07 1 Liter	0.0240	<b>0.0070</b>	0.30	0.082	0.0036	0.0023	0.0051	0.0034	0.0200
8	#08 1 Liter	<b>0.0260</b>	0.0049	0.29	0.051	0.0025	0.0017	0.0051	0.0035	0.0150
9	#09 1 Liter	<b>0.0260</b>	<b>0.0066</b>	0.29	0.068	0.0025	0.0020	0.0051	0.0034	0.0180
10	#10 1 Liter	0.0210	0.0048	0.27	0.057	0.0022	0.0017	0.0051	0.0034	0.0051
11	#11 3 min 1 Liter	0.0025	0.0010	0.24	0.072	0.0014	0.0010	0.0051	0.0033	0.0051

**Date: 1/24/13; outside spigot**

**E301G91**

Flow rate = 1.12 gpm                      pH = 9.68 / 9.86

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	<b>0.0900</b>	0.0010	<b>3.20</b>	0.051	<b>0.1900</b>	0.0087	0.005	<b>0.0220</b>	<b>0.0680</b>
2	#02 1 Liter	0.0160	0.0031	<b>0.47</b>	<b>0.086</b>	<b>0.0710</b>	0.0310	0.0051	<b>0.0045</b>	<b>0.0250</b>
3	#03 1 Liter	0.0110	0.0039	0.18	0.063	0.0570	<b>0.0290</b>	0.0051	0.0022	0.0120
4	#04 1 Liter	0.0110	0.0056	0.17	<b>0.074</b>	0.0560	<b>0.0360</b>	0.0051	0.0020	0.0091
5	#05 1 Liter	0.0140	0.0061	0.15	0.058	0.0400	0.0250	0.0051	0.0020	0.0053
6	#06 1 Liter	0.0420	0.0080	0.14	0.051	0.0160	0.0095	0.0051	0.0020	0.0051
7	#07 1 Liter	0.0810	0.0160	0.14	0.051	0.0060	0.0041	0.0051	0.0020	0.0051
8	#08 1 Liter	<b>0.0900</b>	<b>0.0210</b>	0.14	0.051	0.0035	0.0025	0.0051	0.0020	0.0051
9	#09 1 Liter	<b>0.0940</b>	0.0140	0.14	0.051	0.0033	0.0019	0.0051	0.0020	0.0051
10	#10 1 Liter	0.0740	<b>0.0260</b>	0.16	0.051	0.0049	0.0031	0.0051	0.0020	0.0051
11	#11 3 min 1 Liter	0.0026	0.0010	0.24	0.051	0.0013	0.0011	0.0051	0.0030	0.0051

**Date: 1/29/13; outside spigot****E301173**

Flow rate = 1.35 gpm      pH = 9.62 / 9.85

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	
									Zinc	
1	#01 1/2 Liter	0.0620	0.0010	<b>1.60</b>	0.051	<b>0.1400</b>	0.0110	0.005	<b>0.0081</b>	<b>0.0260</b>
2	#02 1 Liter	0.0450	0.0044	<b>0.55</b>	<b>0.064</b>	<b>0.1000</b>	<b>0.0300</b>	0.0051	<b>0.0043</b>	<b>0.0260</b>
3	#03 1 Liter	0.0170	0.0047	0.24	<b>0.066</b>	0.0610	<b>0.0370</b>	0.0051	0.0022	0.0140
4	#04 1 Liter	0.0240	0.0043	0.20	0.053	0.0620	0.0270	0.0051	0.0021	0.0160
5	#05 1 Liter	0.0220	0.0049	0.16	0.051	0.0420	0.0160	0.0051	0.0020	0.0130
6	#06 1 Liter	0.0510	0.0100	0.15	0.051	0.0150	0.0056	0.0051	0.0021	0.0120
7	#07 1 Liter	0.0770	0.0150	0.12	0.051	0.0049	0.0021	0.0051	0.0020	0.0150
8	#08 1 Liter	<b>0.0850</b>	<b>0.0180</b>	0.13	0.051	0.0033	0.0020	0.0051	0.0020	0.0095
9	#09 1 Liter	<b>0.0860</b>	<b>0.0160</b>	0.13	0.051	0.0033	0.0019	0.0051	0.0020	0.0090
10	#10 1 Liter	0.0590	0.0120	0.18	0.051	0.0028	0.0015	0.0051	0.0026	0.0100
11	#11 3 min 1 Liter	0.0025	0.0010	0.29	0.056	0.0013	0.0010	0.0051	0.0046	0.0085

**Date: 2/14/13; inside faucet****E302954**

Flow rate = 1.24 gpm      pH = 9.60 / 9.70

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	
									Zinc	
1	#01, 1/2 Liter	0.0089	0.001	0.12	0.051	<b>0.059</b>	<b>0.017</b>	0.0051	0.002	0.0051
2	#02, 1 Liter	<b>0.045</b>	<b>0.0043</b>	0.11	0.051	0.003	0.0029	0.0051	0.002	<b>0.01</b>
3	#03, 3 min 1 Liter	0.0023	0.001	<b>0.23</b>	<b>0.053</b>	0.0015	0.001	0.0051	<b>0.0039</b>	0.0091

**Date: 2/15/13; outside spigot****E302999**

Flow rate = 1.15 gpm      pH = 9.60 / 9.72

temp = 15.5 / 12.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	
									Zinc	
1	#01, 1/2 Liter	0.0180	0.0012	<b>1.5000</b>	0.0510	<b>0.1200</b>	<b>0.0220</b>	0.0050	<b>0.0056</b>	<b>0.0150</b>
2	#02, 1 Liter	<b>0.0560</b>	<b>0.0110</b>	0.1200	0.0510	0.0053	0.0030	0.0051	0.0020	0.0120
3	#03, 3 min 1 Liter	0.0021	0.0010	0.2700	0.0510	0.0013	0.0012	0.0051	0.0033	0.0087

**Date: 2/19/13; outside spigot****E302C08**

Flow rate = 1.08 gpm

pH = 9.67 / 9.78

temp = 15.4 / 12.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.015	0.0028	<b>0.71</b>	<b>0.057</b>	<b>0.13</b>	<b>0.032</b>	0.005	<b>0.0031</b>	0.0062
2	#02, 1 Liter	<b>0.039</b>	<b>0.01</b>	0.091	0.051	0.0046	0.0025	0.0051	0.002	<b>0.0091</b>
3	#03, 3 min 1 Liter	0.003	0.001	0.24	0.056	0.002	0.001	0.0051	<b>0.0031</b>	0.0085

**Date: 2/22/13; inside faucet****E302F61**

Flow rate = 1.24 gpm

pH = 9.60 / 9.70

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0100	<b>0.0038</b>	0.0930	0.0510	<b>0.0470</b>	<b>0.0260</b>	0.0051	0.0020	0.0051
2	#02, 1 Liter	<b>0.0280</b>	0.0035	0.1600	0.0510	0.0026	0.0012	0.0051	0.0024	<b>0.0110</b>
3	#03, 3 min 1 Liter	0.0021	0.0010	<b>0.2400</b>	<b>0.0580</b>	0.0014	0.0010	0.0051	<b>0.0036</b>	0.0100

**Date: 2/25/13; outside spigot****E302G21**

Flow rate = 1.03 gpm

pH = 9.79 / 9.95

temp = 15.2 / 12.2

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0081	0.0010	<b>0.7000</b>	0.0510	<b>0.1100</b>	<b>0.0170</b>	0.0050	<b>0.0028</b>	0.0070
2		<b>0.0240</b>	<b>0.0022</b>	0.1200	0.0510	0.0044	0.0028	0.0051	0.0020	<b>0.0095</b>
3		0.0019	0.0019	0.1500	<b>0.0580</b>	0.0013	0.0015	0.0051	0.0025	0.0092

Date: 2/28/13; inside faucet

E303078

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0160	0.0026	<b>0.0970</b>	0.0510	<b>0.0380</b>	<b>0.0150</b>	0.0051	0.0020	0.0051
2	<b>0.0340</b>	<b>0.0110</b>	0.0910	0.0510	0.0030	0.0020	0.0051	0.0020	<b>0.0110</b>
3	0.0022	0.0010	0.1400	0.0510	0.0014	0.0010	0.0051	<b>0.0021</b>	0.0100

Date: 3/4/13; inside faucet

E303184

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0066	0.0030	0.0840	0.0510	<b>0.0440</b>	<b>0.0270</b>	0.0051	0.0020	0.0066
2	<b>0.0480</b>	<b>0.0190</b>	0.0780	0.0510	0.0032	0.0023	0.0051	0.0020	<b>0.0120</b>
3	0.0023	0.0010	<b>0.2300</b>	0.0510	0.0015	0.0010	0.0051	<b>0.0033</b>	0.0100

Date: 3/6/13; outside spigot

E303460

ATP = 437 ME/mL

Flow rate = 1.31 gpm

pH = 9.83 / 9.96

temp = 14.8 / 11.3

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0079	0.0010	<b>1.3000</b>	0.0510	<b>0.1400</b>	<b>0.0180</b>	0.0050	<b>0.0043</b>	<b>0.0240</b>
2	<b>0.0140</b>	<b>0.0029</b>	0.1600	0.0510	0.0028	0.0019	0.0051	0.0025	0.0110
3	0.0020	0.0010	0.2200	0.0510	0.0012	0.0010	0.0051	0.0033	0.0097

Date: 4/4/13; inside faucet

E304399

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0071	0.0010	0.1100	0.0510	<b>0.0280</b>	<b>0.0140</b>		0.0020	0.0051
2	<b>0.0370</b>	<b>0.0045</b>	0.1400	0.0510	0.0020	0.0012		0.0020	<b>0.0100</b>
3	0.0035	0.0010	<b>0.2000</b>	0.0510	0.0011	0.0010		0.0020	<b>0.0100</b>

**Date: 4/10/13; outside spigot****E304901**

ATP = 1453 ME/mL      Flow rate = 1.66 gpm      pH = 9.97 / 10.15      temp = 16.3 / 11.6

<b>ppm</b>	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	

1	0.0140	<b>0.0038</b>	<b>1.1000</b>	<b>0.1500</b>	<b>0.2800</b>	<b>0.0590</b>		<b>0.1200</b>	0.0062
2	<b>0.0170</b>	0.0034	0.1400	0.0510	0.0026	0.0016		0.0020	0.0095
3	0.0034	0.0010	0.1800	0.0510	0.0015	0.0011		0.0020	<b>0.0130</b>

**Date: 5/7/13; outside spigot****E305643**

ATP = ??? ME/mL      Flow rate = 1.44 gpm      pH = 9.96 / 9.41      temp = 18.5 / 15.9

<b>ppm</b>	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	

1	<b>0.0160</b>	<b>0.0088</b>	0.0510	0.0510	<b>0.0220</b>	<b>0.0095</b>		0.0020	<b>0.0150</b>
2	0.0024	0.0010	0.0510	0.0510	0.0047	0.0025		0.0020	0.0051
3	0.0017	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

**Date: 5/14/13; inside faucet****E305C69**

<b>ppm</b>	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	

1	0.0120	0.0038	0.0760	0.0510	<b>0.0250</b>	<b>0.0130</b>		0.0020	0.0051
2	<b>0.0820</b>	<b>0.0300</b>	0.0680	0.0510	0.0019	0.0014		0.0020	0.0051
3	0.0072	0.0016	<b>0.0900</b>	0.0510	0.0012	0.0010		0.0020	0.0051



**Loc #7, 183 Laurel Hill Ave**

Two largest concentrations

Below quantitation limits

**Date: 1/15/13; inside faucet**

**E301A41**

Flow rate = 1.24 gpm

pH = 9.29 / 9.33

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
2	#02, 1/2 Liter	0.0068	0.0010	<b>0.097</b>	0.051	<b>0.0400</b>	<b>0.0160</b>	0.0051	<b>0.0030</b>	0.0085
3	#03, 1 Liter	0.0042	0.0010	<b>0.095</b>	0.051	0.0280	0.0150	0.0051	<b>0.0028</b>	0.0200
4	#04, 1 Liter	0.0044	0.0011	0.092	0.051	<b>0.0310</b>	<b>0.0160</b>	0.0051	<b>0.0028</b>	0.0210
5	#05, 1 Liter	0.0054	0.0013	0.090	0.051	0.0300	0.0140	0.0051	0.0027	0.0220
6	#06, 1 Liter	0.0078	0.0019	<b>0.095</b>	0.051	0.0190	0.0098	0.0051	0.0027	<b>0.0370</b>
7	#07, 1 Liter	<b>0.0370</b>	0.0044	0.092	0.051	0.0060	0.0035	0.0051	0.0023	<b>0.0300</b>
8	#08, 1 Liter	<b>0.0480</b>	<b>0.0097</b>	0.090	0.051	0.0028	0.0019	0.0051	0.0024	0.0180
9	#09, 1 Liter	0.0200	<b>0.0064</b>	0.058	0.051	0.0021	0.0020	0.0051	0.0020	0.0180
10	#10, 3 min 1 Liter	0.0013	0.0010	0.051	0.051	0.0013	0.0021	0.0051	0.0020	0.0180

**Date: 1/18/13; outside spigot**

**E301D06**

Flow rate = 1.49 gpm

pH = 9.59 / 9.72

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0030	0.0010	0.051	0.051	<b>0.0300</b>	<b>0.0200</b>	0.0051	0.0020	0.0069
2	#02, 1 Liter	0.0034	0.0030	0.051	0.051	<b>0.0310</b>	<b>0.0220</b>	0.0051	0.0020	0.0051
3	#03, 1 Liter	0.0051	0.0029	0.051	0.051	<b>0.0300</b>	0.0180	0.0051	0.0020	<b>0.0340</b>
4	#04, 1 Liter	0.0096	0.0052	0.051	0.051	0.0200	0.0120	0.0051	0.0020	<b>0.0420</b>
5	#05, 1 Liter	<b>0.0280</b>	<b>0.0160</b>	0.051	0.051	0.0044	0.0040	0.0051	0.0020	0.0290
6	#06, 1 Liter	<b>0.0330</b>	<b>0.0150</b>	0.051	0.051	0.0020	0.0019	0.0051	0.0020	0.0220
7	#07, 1 Liter	0.0100	0.0037	0.051	0.051	0.0015	0.0014	0.0051	0.0020	0.0170
8	#08, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0190

**Date: 1/24/13; outside spigot E301G89**

Flow rate = 1.56 gpm pH = 9.61 / 9.70

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0120	0.0033	0.051	0.051	<b>0.0360</b>	<b>0.0180</b>	0.0051	0.0020	<b>0.0460</b>
2	#02, 1 Liter	0.0054	0.0030	0.051	0.051	<b>0.0230</b>	<b>0.0180</b>	0.0051	0.0020	<b>0.0210</b>
3	#03, 1 Liter	0.0110	0.0067	0.051	0.051	0.0110	0.0085	0.0051	0.0020	0.0150
4	#04, 1 Liter	<b>0.0200</b>	<b>0.0130</b>	0.051	0.051	0.0040	0.0034	0.0051	0.0020	0.0051
5	#05, 1 Liter	<b>0.0150</b>	<b>0.0079</b>	0.051	0.051	0.0019	0.0019	0.0051	0.0020	0.0051
6	#06, 1 Liter	0.0056	0.0014	0.051	0.051	0.0012	0.0014	0.0051	0.0020	0.0051
7	#07, 1 Liter	0.0024	0.0010	0.051	0.051	0.0016	0.0015	0.0051	0.0020	0.0051
8	#08, 3 min 1 Liter	0.0011	0.0010	0.051	0.051	0.0010	0.0014	0.0051	0.0020	0.0051

**Date: 1/25/13; outside spigot E301H00**

Flow rate = 2.82 gpm pH = 9.78 / 9.97

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		<b>Lead</b>	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0068	0.0013	0.055	0.051	<b>0.0550</b>	<b>0.0260</b>	0.0051	0.0020	<b>0.0420</b>
2	#02, 1 Liter	0.0057	0.0025	0.051	0.051	<b>0.0320</b>	<b>0.0230</b>	0.0051	0.0020	0.0160
3	#03, 1 Liter	0.0190	<b>0.0088</b>	0.051	0.051	0.0190	0.0120	0.0051	0.0020	<b>0.0200</b>
4	#04, 1 Liter	<b>0.0370</b>	<b>0.0160</b>	0.051	0.051	0.0050	0.0037	0.0051	0.0020	0.0120
5	#05, 1 Liter	<b>0.0280</b>	0.0079	0.051	0.051	0.0019	0.0017	0.0051	0.0020	0.0051
6	#06, 1 Liter	0.0100	0.0023	0.051	0.051	0.0014	0.0012	0.0051	0.0020	0.0051
7	#07, 1 Liter	0.0018	0.0010	0.051	0.051	0.0012	0.0010	0.0051	0.0020	0.0051
8	#08, 3 min 1 Liter	0.0011	0.0010	0.051	0.051	0.0010	0.0011	0.0051	0.0020	0.0051

**Date: 1/30/13; outside spigot E301J96**

Flow rate = 2.38 gpm pH = 9.58 / 9.68

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0031	0.0010	0.051	0.051	<b>0.0370</b>	<b>0.0220</b>	0.0051	0.0020	0.0092
2	#02, 1 Liter	0.0035	0.0015	0.051	0.051	<b>0.0380</b>	<b>0.0200</b>	0.0051	0.0020	0.0140
3	#03, 1 Liter	0.0043	0.0017	0.051	0.051	0.0320	0.0180	0.0051	0.0020	0.0140
4	#04, 1 Liter	0.0070	0.0030	0.051	0.051	0.0200	0.0120	0.0051	0.0020	<b>0.0450</b>
5	#05, 1 Liter	<b>0.0300</b>	<b>0.0130</b>	0.051	0.051	0.0035	0.0026	0.0051	0.0020	<b>0.0190</b>
6	#06, 1 Liter	<b>0.0330</b>	<b>0.0130</b>	0.051	0.051	0.0020	0.0031	0.0051	0.0020	0.0110
7	#07, 1 Liter	0.0057	0.0013	0.051	0.051	0.0013	0.0014	0.0051	0.0020	0.0110
8	#08, 3 min 1 Liter	0.0010	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0099

**Date: 2/11/13; inside faucet E302596**

Flow rate = 1.22 gpm pH = 9.43 / 9.51

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0095	0.0043	0.051	0.051	<b>0.03</b>	<b>0.02</b>	0.0051	0.002	0.007
2	#02, 1 Liter	<b>0.03</b>	<b>0.014</b>	0.051	0.051	0.0043	0.0031	0.0051	0.002	<b>0.018</b>
3	#03, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.0012	0.0011	0.0051	0.002	0.0089

**Date: 2/12/13; outside spigot E302693**

Flow rate = 2.26 gpm pH = 9.54 / 9.60 temp = 13.7 / 11.5

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0032	0.001	0.051	0.051	<b>0.05</b>	<b>0.025</b>	0.0051	0.002	0.012
2	#02, 1 Liter	<b>0.027</b>	<b>0.01</b>	0.051	0.051	0.0039	0.0032	0.0051	0.002	<b>0.016</b>
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0094

**Date: 2/18/13; inside faucet****E302A73**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0036	0.0020	0.0510	0.0510	<b>0.0380</b>	<b>0.0260</b>	0.0051	0.0020	0.0053
2	#02, 1 Liter	<b>0.0320</b>	<b>0.0130</b>	0.0510	0.0510	0.0047	0.0039	0.0051	0.0020	<b>0.0220</b>
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0012	0.0010	0.0051	0.0020	0.0093

**Date: 2/20/13; outside spigot****E302D42**

Flow rate = 2.26 gpm

pH = 9.69 / 9.81

temp = 11.8 / 9.0

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0041	0.0010	0.0510	0.0510	<b>0.0350</b>	<b>0.0190</b>	0.0051	0.0020	0.0110
2	#02, 1 Liter	<b>0.0230</b>	<b>0.0098</b>	0.0510	0.0510	0.0024	0.0018	0.0051	0.0020	<b>0.0190</b>
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	<b>0.0022</b>	0.0110

**Date: 2/25/13; inside faucet****E302G20**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0032	0.0018	0.0510	<b>0.0430</b>	<b>0.0340</b>	0.0510	0.0051	0.0020	0.0063
2		<b>0.0160</b>	<b>0.0097</b>	0.0510	0.0093	0.0080	0.0510	0.0051	0.0020	<b>0.0250</b>
3		0.0010	0.0010	0.0510	0.0011	0.0010	<b>0.0540</b>	0.0051	<b>0.0022</b>	0.0100

**Date: 2/26/13; outside spigot****E302H05**

Flow rate = 2.26 gpm

pH = 9.81 / 9.90

temp = 11.5 / 7.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0026	0.0010	0.0510	0.0510	<b>0.0360</b>	<b>0.0200</b>	0.0051	0.0020	<b>0.0200</b>
2		<b>0.0260</b>	<b>0.0110</b>	0.0510	0.0510	0.0035	0.0026	0.0051	0.0020	0.0099
3		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0093

**Date: 3/4/13; inside faucet**

**E303186**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0040	0.0018	0.0510	0.0510	<b>0.0320</b>	<b>0.0190</b>	0.0051	0.0020	0.0076
2	<b>0.0200</b>	<b>0.0089</b>	0.0510	0.0510	0.0048	0.0034	0.0051	0.0020	<b>0.0180</b>
3	0.0011	0.0010	0.0510	0.0510	0.0012	0.0010	0.0051	0.0020	0.0099

**Date: 3/5/13; outside spigot**

**E303292**

ATP = 475 ME/mL

Flow rate = 2.54 gpm

pH = 9.96 / 10.03

temp = 10.3 / 8.7

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0036	0.0016	0.0510	0.0510	<b>0.0510</b>	<b>0.0300</b>	0.0051	0.0020	<b>0.0190</b>
2	<b>0.0180</b>	<b>0.0110</b>	0.0510	0.0510	0.0055	0.0048	0.0051	0.0020	0.0170
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0096

**Date: 4/1/13; inside faucet**

**E304163**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0085	0.0023	0.0510	0.0510	<b>0.0160</b>	<b>0.0130</b>		0.0020	0.0060
2	<b>0.0210</b>	<b>0.0130</b>	0.0510	0.0510	0.0028	0.0022		0.0020	<b>0.0170</b>
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0120

**Date: 4/8/13; outside spigot**

**E304641**

ATP = 1042 ME/mL

Flow rate = 2.10 gpm

pH = 10.22 / 10.22

temp = 13.2 / 12.0

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0032	0.0014	0.0510	0.0510	<b>0.0054</b>	<b>0.0042</b>		0.0020	<b>0.0460</b>
2	<b>0.0071</b>	<b>0.0045</b>	0.0510	0.0510	0.0015	0.0015		0.0020	0.0120
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0097

**Date: 5/7/13; outside spigot****E305642**

ATP = ??? ME/mL

Flow rate = 2.10 gpm

pH = 9.99 / 9.99

temp = 13.9 / 15.4

	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	<b>0.0042</b>	0.0010	0.0510	0.0510	<b>0.0210</b>	<b>0.0110</b>		0.0020	<b>0.0120</b>
2	0.0035	<b>0.0011</b>	0.0510	0.0510	0.0150	0.0096		0.0020	0.0051
3	0.0022	0.0010	<b>0.0650</b>	0.0510	0.0010	0.0010		0.0020	0.0051

**Date: 5/15/13; inside faucet****E305D58**

	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0057	0.0027	0.0560	0.0510	<b>0.0190</b>	<b>0.0120</b>		0.0020	0.0072
2	<b>0.0330</b>	<b>0.0230</b>	0.0510	0.0510	0.0029	0.0024		0.0020	<b>0.0095</b>
3	0.0028	0.0010	0.0510	0.0510	0.0011	0.0010		0.0020	0.0051

**Loc #8, 70 Sandringham Ave**

Two largest concentrations

Below quantitation limits

**Date: 1/10/13; inside faucet**

**E301688**

Flow rate = 1.49 gpm

pH = 9.33 / 9.53

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0110	0.0011	<b>0.230</b>	0.051	<b>0.0780</b>	<b>0.0140</b>	0.0051	<b>0.0089</b>	<b>0.0730</b>
2	#02, 1/2 Liter	0.0073	0.0010	<b>0.160</b>	0.051	0.0095	0.0045	0.0051	0.0056	0.0710
3	#03, 1 Liter	0.0086	0.0014	0.140	0.051	<b>0.0130</b>	<b>0.0063</b>	0.0051	0.0050	<b>0.1000</b>
4	#04, 1 Liter	0.0100	0.0014	0.150	0.051	0.0098	0.0047	0.0051	<b>0.0058</b>	0.0660
5	#05, 1 Liter	0.0310	0.0060	0.120	0.051	0.0041	0.0025	0.0051	0.0041	0.0150
6	#06, 1 Liter	<b>0.0600</b>	<b>0.0077</b>	0.140	0.051	0.0015	0.0010	0.0051	0.0045	0.0055
7	#07, 1 Liter	<b>0.0480</b>	<b>0.0073</b>	0.150	0.051	0.0028	0.0029	0.0051	0.0050	0.0051
8	#08, 1 Liter	0.0260	0.0030	0.170	0.051	0.0020	0.0011	0.0051	0.0057	0.0059
9	#09, 3 min 1 Liter	0.0082	0.0010	0.083	0.051	0.0450	0.0019	0.0051	0.0028	0.0580

**Date: 1/11/13; outside spigot**

**E301807**

Flow rate = 1.74 gpm

pH = 9.62 / 9.73

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	<b>0.0430</b>	0.0059	<b>0.150</b>	0.051	<b>0.1500</b>	<b>0.0390</b>	<b>0.0052</b>	<b>0.0043</b>	<b>0.7800</b>
2	#02, 1/2 Liter	0.0099	0.0026	0.051	0.051	<b>0.0120</b>	<b>0.0074</b>	0.0051	0.0020	<b>0.0390</b>
3	#03, 1 Liter	0.0390	<b>0.0170</b>	0.051	0.051	0.0038	0.0024	0.0051	0.0020	0.0270
4	#04, 1 Liter	<b>0.0460</b>	<b>0.0230</b>	0.051	0.051	0.0020	0.0016	0.0051	0.0020	0.0190
5	#05, 1 Liter	0.0310	0.0110	0.051	0.051	0.0023	0.0017	0.0051	0.0020	0.0210
6	#06, 1 Liter	0.0093	0.0016	<b>0.070</b>	0.051	0.0016	0.0010	0.0051	0.0027	0.0190
7	#07, 3 min 1 Liter	0.0016	0.0010	0.062	0.051	0.0010	0.0010	0.0051	<b>0.0032</b>	0.0051

## Date: 1/15/13; outside spigot

E301A48

Flow rate = 1.54 gpm      pH = 9.48 / 9.60

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0140	0.0071	<b>0.056</b>	0.051	<b>0.0660</b>	<b>0.0420</b>	0.0051	<b>0.0026</b>	<b>0.0380</b>
2	#02, 1/2 Liter	0.0083	0.0016	<b>0.056</b>	0.051	<b>0.0120</b>	<b>0.0079</b>	0.0051	<b>0.0021</b>	<b>0.0550</b>
3	#03, 1 Liter	0.0270	<b>0.0130</b>	0.051	0.051	0.0036	0.0033	0.0051	0.0020	0.0210
4	#04, 1 Liter	<b>0.0420</b>	<b>0.0240</b>	0.051	0.051	0.0012	0.0012	0.0051	0.0020	0.0260
5	#05, 1 Liter	<b>0.0300</b>	<b>0.0130</b>	0.051	0.051	0.0020	0.0016	0.0051	0.0020	0.0180
6	#06, 1 Liter	0.0120	0.0041	0.051	0.051	0.0012	0.0010	0.0051	0.0020	0.0170
7	#07, 3 min 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0150

## Date: 1/17/13; outside spigot

E301C74

Flow rate = 1.69 gpm      pH = 9.63 / 9.80

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#02, 1/2 Liter	0.0089	0.0012	<b>0.063</b>	0.051	<b>0.0120</b>	<b>0.0075</b>	0.0051	<b>0.0037</b>	<b>0.0470</b>
2	#03, 1 Liter	0.0270	0.0140	0.051	0.051	<b>0.0040</b>	<b>0.0039</b>	0.0051	0.0020	<b>0.0290</b>
3	#04, 1 Liter	<b>0.0420</b>	<b>0.0250</b>	0.051	0.051	0.0014	0.0013	0.0051	0.0020	0.0051
4	#05, 1 Liter	<b>0.0300</b>	<b>0.0150</b>	0.051	0.051	0.0017	0.0015	0.0051	0.0020	0.0051
5	#06, 1 Liter	0.0100	0.0052	0.051	0.051	0.0011	0.0013	0.0051	0.0020	0.0170
6	#07, 3 min 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0160

## Date: 1/18/13; outside spigot

E301D08

Flow rate = 1.86 gpm      pH = 9.60 / 9.82

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0088	0.0028	0.051	0.051	<b>0.0140</b>	<b>0.0066</b>	0.0051	0.0020	<b>0.0400</b>
2	#02, 1 Liter	<b>0.0330</b>	<b>0.0200</b>	0.051	0.051	<b>0.0036</b>	<b>0.0024</b>	0.0051	0.0020	<b>0.0280</b>
3	#03, 1 Liter	<b>0.0400</b>	<b>0.0230</b>	0.051	0.051	0.0019	0.0015	0.0051	0.0020	0.0051
4	#04, 1 Liter	0.0260	0.0100	0.051	0.051	0.0018	0.0014	0.0051	0.0020	0.0051
5	#05, 1 Liter	0.0067	0.0029	0.051	0.051	0.0012	0.0011	0.0051	0.0020	0.0210
6	#06, 3 min 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0200



**Date: 2/12/13; inside spigot**

**E302846**

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0072	0.0015	<b>0.056</b>	0.051	<b>0.01</b>	<b>0.0059</b>	0.0051	0.002	<b>0.075</b>
2	#02, 1 Liter	<b>0.047</b>	<b>0.016</b>	0.051	0.051	0.0052	0.0028	0.0051	0.002	0.016
3	#03, 3 min 1 Liter	0.0013	0.001	0.051	0.051	0.0023	0.001	0.0051	0.002	0.011
4	#04, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.012

**Date: 2/13/13; outside spigot**

**E302846**

Flow rate = 2.24 gpm

pH = 9.69 / 9.78

temp = 10.3 / 8.7

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.034	0.003	<b>0.077</b>	0.051	<b>0.025</b>	<b>0.022</b>	0.0051	0.002	<b>0.24</b>
2	#02, 1 Liter	<b>0.043</b>	<b>0.019</b>	0.051	0.051	0.002	0.0015	0.0051	0.002	0.014
3	#03, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0084
4	#04, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.009

**Date: 2/21/13; inside spigot**

**E302E19**

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0044	0.0010	<b>0.0560</b>	0.0510	<b>0.0088</b>	<b>0.0052</b>	0.0051	0.0020	<b>0.0530</b>
2	#02, 1 Liter	<b>0.0310</b>	<b>0.0087</b>	0.0520	0.0510	0.0066	0.0022	0.0051	0.0020	0.0210
3	#03, 3 min 1 Liter	0.0012	0.0010	0.0550	0.0510	0.0010	0.0010	0.0051	0.0028	0.0110
4	#04, 3 min 1 Liter	0.0010	0.0010	0.0520	0.0510	0.0010	0.0010	0.0051	<b>0.0029</b>	0.0110

**Date: 2/20/13; outside spigot****E302E22**

Flow rate = 2.26 gpm

pH = 9.79 / 9.86

temp = 9.7 / 7.3

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0140	0.0010	<b>0.0900</b>	0.0510	<b>0.0220</b>	<b>0.0066</b>	0.0051	0.0020	<b>0.0880</b>
2	#02, 1 Liter	<b>0.0440</b>	<b>0.0130</b>	0.0510	0.0510	0.0014	0.0013	0.0051	0.0020	0.0110
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0110
4	#04, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

**Date: 2/27/13; inside spigot****E302I58**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0048	0.0016	0.0510	0.0510	<b>0.0100</b>	<b>0.0057</b>	0.0051	0.0020	<b>0.0800</b>
2		<b>0.0320</b>	<b>0.0150</b>	0.0510	0.0510	0.0022	0.0014	0.0051	0.0020	0.0140
3		0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0140
4		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0099

**Date: 2/28/13; outside spigot****E303077**

ATP = 96 ME/mL

Flow rate = 1.04 gpm

pH = 9.71 / 9.85

temp = 15.2 / 9.4

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0065	0.0014	0.0510	0.0510	<b>0.0110</b>	<b>0.0068</b>	0.0051	0.0020	<b>0.0440</b>
2		<b>0.0350</b>	<b>0.0150</b>	0.0510	0.0510	0.0014	0.0011	0.0051	0.0020	0.0100
3		0.0012	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0093
4		0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0086

**Date: 3/5/13; outside spigot****E303456**

ATP = 214 ME/mL

Flow rate = 1.87 gpm

pH = 9.85 / 10.02

temp = 14.4 / 9.3

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0099	0.0023	<b>0.0580</b>	0.0510	<b>0.0210</b>	<b>0.0110</b>	0.0051	0.0020	0.0970
2	<b>0.0390</b>	<b>0.0180</b>	0.0510	0.0510	0.0017	0.0012	0.0051	0.0020	<b>0.1900</b>
3	0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0087
4	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0090

**Date: 3/6/13; inside spigot****E303458**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0029	0.0010	0.0510	0.0510	<b>0.0073</b>	<b>0.0056</b>	0.0051	0.0020	<b>0.0520</b>
2	<b>0.0230</b>	<b>0.0140</b>	0.0510	0.0510	0.0038	0.0019	0.0051	0.0020	0.0140
3	0.0012	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0096
4	0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

**Date: 4/9/13; outside spigot****E304A25**

ATP = 4312 ME/mL

Flow rate = 1.71 gpm

pH = 9.45 / 9.54

temp = 18.6 / 14.1

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0170	0.0026	0.0510	0.0510	<b>0.0083</b>	<b>0.0058</b>		0.0020	<b>0.0520</b>
2	<b>0.0340</b>	<b>0.0220</b>	0.0510	0.0510	0.0012	0.0011		0.0020	0.0084
3	0.0017	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0070

**Date: 4/12/13; inside spigot****E304A66**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0016	0.0012	0.0510	0.0510	<b>0.0061</b>	<b>0.0050</b>		0.0020	<b>0.0380</b>
2	<b>0.0260</b>	<b>0.0190</b>	0.0510	0.0510	0.0028	0.0024		0.0020	0.0320
3	0.0014	0.0010	<b>0.0550</b>	0.0510	0.0015	0.0010		0.0020	0.0110

**Date: 5/8/13; outside spigot****E305880**

ATP = ????

Flow rate = 1.51 gpm

pH = 9.97 / 10.03

temp = 19.5 / 15.4

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0110	0.0019	<b>0.1000</b>	0.0510	<b>0.0093</b>	<b>0.0045</b>		<b>0.0021</b>	<b>0.5400</b>
2	<b>0.0440</b>	<b>0.0310</b>	0.0510	0.0510	0.0011	0.0010		0.0020	0.0100
3	0.0031	0.0015	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

**Date: 5/15/13; inside spigot****E305D57**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0033	0.0015	0.0510	0.0510	<b>0.0060</b>	<b>0.0041</b>		0.0020	<b>0.0360</b>
2	<b>0.0290</b>	<b>0.0200</b>	0.0510	0.0510	0.0044	0.0021		0.0020	0.0074
3	0.0029	0.0016	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051