



552 Academy Avenue
Providence, RI 02908

401-521-6300

www.provwater.com

July 26, 2013

June Swallow, PE
Chief, Drinking Water Quality
R.I. Department of Health
Cannon Building, Room 209
Three Capitol Hill
Providence, R.I. 02908-5097

The Hon. Angel Taveras
Mayor

Boyce Spinelli
General Manager

RE: pH Transition Implementation Plan
Philip J. Holton Water Purification Plant
June 2013 Monthly Report
PWSID 1592024

Dear Ms. Swallow:

Providence Water is pleased to submit the attached June 2013 Monthly Report. The format of the Monthly Report continues to follow the outline of RIDOH's December 6, 2012 letter. We continue to be in consultation with Expert Panel members and, as you know, teleconference meetings with members of the Expert Panel were held on June 20th and July 24th that included RIDOH and Providence Water personnel.

Should you have any questions, please feel free to contact me at (401) 521-6300, Ext. 7291 or ggiasson@provwater.com.

Respectfully,
PROVIDENCE WATER SUPPLY BOARD

Gregg Giasson, PE
Senior Director of Operations

Attachment: June 2013 Monthly Report

cc: Clay Commons	Peter LePage	Steve Soito, PE
Boyce Spinelli	Steve Santaniello	Fred Crosby
Joseph Spremulli	Rich Razza	Mike Covellone
Ricky Caruolo	Paul Gadoury, PE	John Phillips, PE

BOARD OF DIRECTORS

Brett P. Smiley
Chairman

Joseph D. Cataldi
Vice Chairman

Michael L. Pearis
Ex-Officio

Michael A. Solomon
City Council President

Michael J. Correia
City Councilman

Andy M. Andujar
Member

Joan S. Badway
Member

Carissa R. Richard
Secretary

William E. O'Gara, Esq.
Legal Advisor

Member

Rhode Island Water Works Assn.

New England Water Works Assn.

American Water Works Assn.

Water Research Foundation

An EPA WaterSense Partner

Only Tap Water Delivers



**pH Transition Implementation Plan
Philip J. Holton Water Purification Plant
Monthly Report
June 2013**

1. pH Transition

The initial transition to a higher pH began on Wednesday, February 6, 2013.

The second and final transition to the higher pH of 10.2 began on Monday, March 25, 2013 and the CO₂ dose was terminated.

During June, the Treatment Plant Effluent and Academy Avenue pH and Alkalinity had the following values:

	Effluent Water		Academy Avenue	
	<u>pH (SU)</u>	<u>T. Alkalinity (mg/l)</u>	<u>pH (SU)</u>	<u>T. Alkalinity (mg/l)</u>
Min.	10.21	16.10	10.10	14.80
Max.	10.42	18.40	10.21	16.60
Avg.	10.31	17.27	10.16	15.69

See Attachment No. 1 - June pH and Alkalinity Data Tables.

2. Special Sampling Studies of Lead Service Line

A. Sequential and LSL Sampling & Testing

The Post-CCTC sampling began on February 11, and continues based on the approved Protocol.

Sampling data received to date extends through the end of June.

See Attachment No. 2 - Samples from Lead Service Line, for the eight participant site/address test results, for essentially all metals.

- B. PRS Stations' Monitoring (Academy Ave., Brown University, Commercial Building)

The PRS Stations sampling and testing that was resumed at the end of January continues.

- C. Virginia Tech (VT) Pipe Loop Rigs (Academy Ave., Water Treatment Plant)

Sampling and testing continues on the VT Rigs that were placed back in service the last week in February. The intention continues to sample and test once per month.

3. Special Sampling Studies - TCR Sites, LCR Sites, WTP Finished Water

- A. Special Total Coliform Rule (TCR) Sites (4)

Four TCR sites were chosen for ease of sampling and their dispersed geographical locations. The additional sampling and testing that began at these sites on February 1, 2013 continues once every two weeks.

- B. Lead and Copper Rule (LCR) Sites

The additional testing of the LCR sites (100) during the normal 6 month semesters that began in December 2012, continues. The additional tests being conducted, as requested by the Expert Panel, are for Dissolved Lead, Total Iron, and Total Zinc.

- C. Total Coliform Rule (TCR) Sites (44)

The added Turbidity testing continues.

- D. WTP Finished Water Sampling

The addition of Oxygen Reduction Potential (ORP) to the typical daily analyses of the finished water, continues with weekly field tests and laboratory tests every 8 weeks Post-CCTC.

4. Experimental Pipe Loops

The sixteen, two (2) foot lead service line samples, ready for future insertion into the pipe loops, continue to be conditioned by hand using the manual fill and dump method. This is being accomplished twice per week, with Total Lead tests done once per week. This fill and dump method will be employed while the pipe loop racks are being fabricated. The best eight samples, based on Total Lead tests, will be inserted into the loops for further conditioning.

The wood frame work of the pipe loop support system is complete. All material is on-site including the 100 gal. tanks. All salvageable material has been taken from the Bath Street Pumping Station loop racks e.g. pumps, throttling valves etc. The new pipe loops are now being fabricated on the wood framework. Everything will be dry fitted, and once complete and approved, will be glued.

JUNE 2013

Date	Effluent Water		Academy Ave., Tap	
	pH SU	T. Alk. mg/l	pH SU	T. Alk. mg/l
6/1/2013	10.25	16.10		
6/2/2013				
6/3/2013	10.24	16.60	10.15	14.80
6/4/2013	10.28	16.40	10.10	15.00
6/5/2013	10.32	17.00	10.13	15.20
6/6/2013	10.30	16.40	10.13	15.20
6/7/2013	10.30	16.80	10.15	15.20
6/8/2013	10.36	17.20		
6/9/2013				
6/10/2013	10.29	17.50	10.18	16.00
6/11/2013	10.27	17.10	10.16	15.70
6/12/2013	10.31	17.20	10.17	15.50
6/13/2013	10.34	17.70	10.18	15.80
6/14/2013	10.42	18.40	10.18	15.60
6/15/2013	10.37	18.00		
6/16/2013				
6/17/2013	10.32	18.10	10.12	16.10
6/18/2013	10.27	17.40	10.16	16.10
6/19/2013	10.36	18.40	10.15	15.90
6/20/2013	10.21	16.30	10.20	16.60
6/21/2013	10.30	17.30	10.15	16.10
6/22/2013	10.28	17.10		
6/23/2013				
6/24/2013	10.35	17.50	10.18	15.80
6/25/2013	10.33	17.40	10.18	16.00
6/26/2013	10.35	17.60	10.19	15.90
6/27/2013	10.35	17.10	10.21	15.70
6/28/2013	10.34	17.20	10.12	15.60
6/29/2013	10.35	18.00		
6/30/2013				
Minimum	10.21	16.10	10.10	14.80
Maximum	10.42	18.40	10.21	16.60
Average	10.31	17.27	10.16	15.69

Loc #1, 57 Holburn Ave

Date: 1/4/13; inside faucet

E301238

Flow rate = 1.49 gpm

pH = 9.33 / 9.53

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0052	0.0010	0.20	0.051	0.0520	0.0100	0.0051	0.0048	0.0710
2	#02, 1/2 Liter	0.0028	0.0010	0.19	0.051	0.0430	0.0110	0.0051	0.0038	0.0071
3	#03, 1 Liter	0.0010	0.0010	0.22	0.051	0.0110	0.0026	0.0051	0.0071	0.0051
4	#04, 1 Liter	0.0010	0.0010	0.23	0.051	0.0110	0.0021	0.0051	0.0073	0.0062
5	#05, 1 Liter	0.0012	0.0010	0.22	0.051	0.0082	0.0023	0.0051	0.0071	0.0051
6	#06, 1 Liter	0.0012	0.0010	0.23	0.051	0.0078	0.0021	0.0051	0.0073	0.0040
7	#07, 3 min 1 Liter	0.0010	0.0010	0.22	0.051	0.0120	0.0025	0.0051	0.0070	0.0072

Date: 1/18/13; outside spigot

E301D07

Flow rate = 1.69 gpm

pH = 9.61 / 9.90

temp = 18.9 / 7.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	1.3000	0.0440	0.43	0.065	0.4100	0.0480	0.056	0.0150	0.6000
2	#02, 1/2 Liter	0.0045	0.0010	0.21	0.051	0.0160	0.0031	0.0051	0.0042	0.0095
3	#03, 1 Liter	0.0100	0.0010	0.20	0.051	0.0093	0.0026	0.0051	0.0040	0.0250
4	#04, 1 Liter	0.0260	0.0019	0.21	0.051	0.0076	0.0019	0.0051	0.0047	0.0280
5	#05, 1 Liter	0.0190	0.0013	0.21	0.051	0.0044	0.0016	0.0051	0.0050	0.0290
6	#06, 1 Liter	0.0180	0.0045	0.22	0.067	0.0032	0.0015	0.0051	0.0058	0.0250
7	#07, 1 Liter	0.0042	0.0010	0.24	0.083	0.0026	0.0015	0.0051	0.0075	0.0190
8	#08, 3 min 1 Liter	0.0010	0.0010	0.24	0.064	0.0010	0.0010	0.0051	0.0076	0.0210

Date: 1/22/13; outside spigot

E301F54

Flow rate = 1.75 gpm

pH = 9.61 / 9.89

temp = 15.2 / 6.4

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	0.2600	0.0023	0.30	0.051	0.3200	0.0150	0.0084	0.0084	0.4400
2	#02 1 Liter	0.0150	0.0024	0.24	0.051	0.0100	0.0024	0.0051	0.0038	0.0056
3	#03 1 Liter	0.0180	0.0031	0.24	0.051	0.0037	0.0031	0.0051	0.0042	0.0061
4	#04 1 Liter	0.0230	0.0041	0.24	0.051	0.0022	0.0014	0.0051	0.0042	0.0073
5	#05 1 Liter	0.0260	0.0044	0.22	0.051	0.0021	0.0017	0.0051	0.0051	0.0051
6	#06 1 Liter	0.0024	0.0010	0.23	0.051	0.0015	0.0010	0.0051	0.0070	0.0051
7	#07 3 min 1 Liter	0.0010	0.0010	0.23	0.051	0.0010	0.0010	0.0051	0.0071	0.0051

Date: 1/25/13; outside spigot

E301H01

Flow rate = 2.52 gpm

pH = 9.55

temp = 16.9 / 17.1

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	0.035	0.001	0.21	0.051	0.0170	0.0027	0.0051	0.0045	0.0051
2	#02 1 Liter	0.110	0.051	0.20	0.051	0.0100	0.0016	0.0051	0.0045	0.0051
3	#03 1 Liter	0.030	0.020	0.21	0.051	0.0038	0.0036	0.0051	0.0052	0.0051
4	#04 1 Liter	0.014	0.009	0.20	0.051	0.0031	0.0021	0.0051	0.0053	0.0051
5	#05 1 Liter	0.012	0.004	0.21	0.051	0.0027	0.0031	0.0051	0.0060	0.0051
6	#06 1 Liter	0.009	0.005	0.22	0.051	0.0023	0.0011	0.0051	0.0068	0.0051
7	#07 3 min 1 Liter	0.001	0.001	0.22	0.057	0.0010	0.0010	0.0051	0.0068	0.0051

Date: 1/30/13; outside spigot

E301K64

Flow rate = 2.36 gpm

pH = 9.61 / 9.80

temp = 17.5 / 10.4

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	0.0300	0.0013	0.2800	0.0510	0.0220	0.0140	0.0051	0.0043	0.0068
2	#02 1 Liter	0.0240	0.0042	0.2600	0.0510	0.0072	0.0032	0.0051	0.0041	0.0120
3	#03 1 Liter	0.0860	0.0056	0.2700	0.0530	0.0027	0.0011	0.0051	0.0046	0.0140
4	#04 1 Liter	0.0170	0.0024	0.2600	0.0510	0.0016	0.0010	0.0051	0.0056	0.0120
5	#05 1 Liter	0.0120	0.0037	0.2700	0.0810	0.0013	0.0016	0.0051	0.0068	0.0140
6	#06 1 Liter	0.0038	0.0010	0.2800	0.0540	0.0010	0.0010	0.0051	0.0080	0.0096
7	#07 3 min 1 Liter	0.0010	0.0010	0.3000	0.0740	0.0010	0.0010	0.0051	0.0086	0.0096

Date: 2/11/13; inside faucet

E302596

Flow rate = 1.30 gpm

pH = 9.65 / 9.81

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0049	0.001	0.22	0.051	0.032	0.011	0.0051	0.005	0.009
2	#02, 1 Liter	0.003	0.001	0.2	0.051	0.0011	0.0011	0.0051	0.0057	0.01
3	#03, 3 min 1 Liter	0.001	0.001	0.2	0.051	0.001	0.001	0.0051	0.0063	0.016

Date: 2/13/13; outside spigot

E302953

Flow rate = 2.56 gpm

pH = 9.61 / 9.79

temp = 15 / 7.3

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.026	0.001	0.26	0.051	0.017	0.0034	0.0051	0.0043	0.0075
2	#02, 1 Liter	0.021	0.0032	0.3	0.078	0.0036	0.0012	0.0051	0.0057	0.012
3	#03, 3 min 1 Liter	0.0036	0.001	0.44	0.076	0.001	0.001	0.0051	0.012	0.0084

Date: 2/20/13; outside spigot

E302E21

Flow rate = 2.22 gpm

pH = 9.77 / 9.94

temp = 15.4 / 8.0

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0095	0.0010	0.2500	0.0510	0.0250	0.0027	0.0051	0.0058	0.0053
2	#02, 1 Liter	0.0120	0.0010	0.2500	0.0510	0.0027	0.0010	0.0051	0.0062	0.0120
3	#03, 3 min 1 Liter	0.0010	0.0010	0.2500	0.0510	0.0010	0.0010	0.0051	0.0072	0.0092

Date: 2/21/13; inside faucet

E302E20

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0210	0.0011	0.3100	0.0510	0.0270	0.0056	0.0051	0.0083	0.0550
2	#02, 1 Liter	0.0081	0.0010	0.1800	0.0510	0.0035	0.0012	0.0051	0.0061	0.0250
3	#03, 3 min 1 Liter	0.0045	0.0010	0.2000	0.0510	0.0013	0.0010	0.0051	0.0077	0.0140

Date: 3/1/13; inside faucet

E303079

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0030	0.0010	0.2400	0.0510	0.0200	0.0080	0.0051	0.0047	0.0680
2		0.0027	0.0010	0.2400	0.0510	0.0075	0.0031	0.0051	0.0051	0.0140
3		0.0010	0.0010	0.2500	0.0580	0.0010	0.0010	0.0051	0.0070	0.0110

Date: 3/6/13; outside faucet**E303572**

ATP = 646 ME/mL

Flow rate = 2.24 gpm

pH = 9.83 / 9.94

temp = 17 / 8.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0150	0.0010	0.4100	0.0510	0.0140	0.0067	0.0051	0.0069	0.0056
2	0.0170	0.0018	0.4000	0.0720	0.0052	0.0015	0.0051	0.0094	0.0120
3	0.0010	0.0010	0.3100	0.0510	0.0010	0.0010	0.0051	0.0094	0.0110

Date: 3/7/13; inside faucet**E303571**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0052	0.0010	0.2300	0.0510	0.0340	0.0120	0.0051	0.0049	0.0140
2	0.0053	0.0010	0.1800	0.0510	0.0016	0.0010	0.0051	0.0049	0.0150
3	0.0010	0.0010	0.2100	0.0510	0.0018	0.0010	0.0051	0.0070	0.0140

Date: 4/2/13; inside faucet**E304162**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0035	0.0010	0.1200	0.0510	0.0140	0.0057		0.0026	0.0051
2	0.0092	0.0010	0.1300	0.0510	0.0010	0.0010		0.0032	0.0110
3	0.0010	0.0010	0.1400	0.0510	0.0010	0.0010		0.0040	0.0110

Date: 4/9/13; outside faucet**E304758**

ATP = 1542

Flow rate = 2.17 gpm

pH = 10.0 / 10.11

temp = 13.4 / 10.0

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0110	0.0010	0.1600	0.0510	0.0090	0.0026		0.0037	0.0072
2	0.0370	0.0016	0.1700	0.0510	0.0054	0.0016		0.0038	0.0120
3	0.0013	0.0010	0.1800	0.0510	0.0010	0.0010		0.0048	0.0093

Date: 5/6/13; outside faucet**E305476**

ATP = ???

Flow rate = 1.6 gpm

pH = 10.10 / 10.06

temp = 12.3 / 11.8

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0087	0.0016	0.1600	0.0510	0.0320	0.0048		0.0065	0.0051
2	0.0062	0.0010	0.1500	0.0510	0.0017	0.0010		0.0075	0.0140
3	0.0014	0.0010	0.1500	0.0510	0.0010	0.0010		0.0069	0.0120

Date: 5/14/13; inside faucet**E305C71**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0130	0.0016	0.1100	0.0510	0.0069	0.0035		0.0039	0.0051
2	0.0076	0.0010	0.1900	0.0510	0.0031	0.0010		0.0080	0.0051
3	0.0037	0.0010	0.2100	0.0510	0.0018	0.0010		0.0110	0.0055

Date: 6/7/13; inside faucet

E306706

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0047	0.0010	0.0860	0.0510	0.0039	0.0014		0.0030	0.0051
2	0.0160	0.0013	0.0800	0.0510	0.0010	0.0010		0.0030	0.0051
3	0.0025	0.0010	0.0770	0.0510	0.0010	0.0010		0.0030	0.0051

Date: 6/25/13; outside faucet

E306E33

ATP = ???

Flow rate = ?? gpm

pH =

temp =

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0069	0.0010	0.1200	0.0510	0.0130	0.0041		0.0059	0.0053
2	0.0110	0.0011	0.1200	0.0510	0.0020	0.0014		0.0056	0.0051
3	0.0028	0.0010	0.1200	0.0510	0.0010	0.0010		0.0066	0.0051

Loc #2 26 Keith Avenue

Two largest concentrations

Below quantitation limits

Sample date 1/8/2013; Outside spigot; E301631

Flow rate = 1.63 gpm

pH = 9.42 / 9.53

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0095	0.0016	0.100	0.051	0.0430	0.0110	0.0051	0.0038	0.0590
2	#02, 1/2 Liter	0.0067	0.0010	0.150	0.051	0.0110	0.0045	0.0051	0.0039	0.0180
3	#03, 1 Liter	0.0370	0.0050	0.150	0.051	0.0073	0.0031	0.0051	0.0042	0.0063
4	#04, 1 Liter	0.0530	0.0098	0.160	0.051	0.0021	0.0010	0.0051	0.0046	0.0051
5	#05, 1 Liter	0.0550	0.0058	0.160	0.051	0.0011	0.0010	0.0051	0.0048	0.0051
6	#06, 1 Liter	0.0580	0.0093	0.150	0.051	0.0010	0.0010	0.0051	0.0048	0.0051
7	#07, 1 Liter	0.0170	0.0023	0.110	0.051	0.0010	0.0010	0.0051	0.0042	0.0051
8	#08, 3 min 1 Liter	0.0033	0.0010	0.093	0.051	0.0130	0.0041	0.0051	0.0032	0.0062

Sample date 1/9/2013; Inside faucet; E301690

Flow rate = 2.10 gpm

pH = 9.46 / 9.54

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0036	0.0010	0.140	0.051	0.0160	0.0059	0.0051	0.0032	0.0470
2	#02, 1/2 Liter	0.0048	0.0010	0.120	0.051	0.0092	0.0034	0.0051	0.0030	0.0240
3	#03, 1 Liter	0.0051	0.0010	0.130	0.051	0.0076	0.0032	0.0051	0.0036	0.0220
4	#04, 1 Liter	0.0046	0.0010	0.110	0.051	0.0074	0.0032	0.0051	0.0032	0.0170
5	#05, 1 Liter	0.0220	0.0033	0.110	0.051	0.0073	0.0037	0.0051	0.0036	0.0062
6	#06, 1 Liter	0.0260	0.0019	0.100	0.051	0.0037	0.0018	0.0051	0.0038	0.0060
7	#07, 1 Liter	0.0270	0.0041	0.096	0.051	0.0015	0.0011	0.0051	0.0031	0.0051
8	#08, 1 Liter	0.0280	0.0039	0.097	0.051	0.0013	0.0011	0.0051	0.0034	0.0052
9	#09, 3 min 1 Liter	0.0080	0.0010	0.100	0.051	0.0016	0.0014	0.0051	0.0032	0.0055

Sample date 1/16/2013; Outside spigot; E301C03

Flow rate = 1.57 gpm

pH = 9.60 / 9.69

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0078	0.0019	0.061	0.051	0.0370	0.0130	0.0051	0.0025	0.0490
2	#02, 1/2 Liter	0.0068	0.0010	0.094	0.051	0.0130	0.0048	0.0051	0.0022	0.0200
3	#03, 1 Liter	0.0320	0.0066	0.085	0.051	0.0055	0.0030	0.0051	0.0020	0.0051
4	#04, 1 Liter	0.0380	0.0068	0.085	0.051	0.0011	0.0012	0.0051	0.0020	0.0051
5	#05, 1 Liter	0.0400	0.0091	0.084	0.051	0.0013	0.0010	0.0051	0.0020	0.0250
6	#06, 1 Liter	0.0370	0.0066	0.085	0.051	0.0011	0.0010	0.0051	0.0020	0.0051
7	#07, 1 Liter	0.0065	0.0011	0.100	0.051	0.0010	0.0010	0.0051	0.0026	0.0051
8	#08, 3 min 1 Liter	0.0013	0.0010	0.100	0.051	0.0010	0.0010	0.0051	0.0028	0.0051

Sample date 1/23/2013; Outside spigot; E301G29

Flow rate = 1.46 gpm

pH = 9.70 / 9.81

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0089	0.0010	0.120	0.051	0.0280	0.0048	0.0051	0.0023	0.0860
2	#02, 1/2 Liter	0.0120	0.0032	0.092	0.051	0.0210	0.0054	0.0051	0.0020	0.0410
3	#03, 1 Liter	0.0170	0.0050	0.098	0.051	0.0051	0.0011	0.0051	0.0021	0.0320
4	#04, 1 Liter	0.0180	0.0020	0.090	0.051	0.0021	0.0015	0.0051	0.0020	0.0051
5	#05, 1 Liter	0.0200	0.0070	0.091	0.051	0.0010	0.0010	0.0051	0.0020	0.0051
6	#06, 1 Liter	0.0068	0.0015	0.095	0.051	0.0010	0.0010	0.0051	0.0023	0.0051
7	#07, 3 min 1 Liter	0.0012	0.0010	0.098	0.051	0.0010	0.0010	0.0051	0.0026	0.0051

Sample date 1/30/2013; Outside spigot;

E301K65

Flow rate = 1.59 gpm

pH = 9.66 / 9.73

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0090	0.0010	0.1100	0.0510	0.0160	0.0074	0.0051	0.0020	0.0750
2	#02, 1 Liter	0.0330	0.0110	0.0970	0.0510	0.0072	0.0039	0.0051	0.0020	0.0150
3	#03, 1 Liter	0.0430	0.0110	0.0940	0.0510	0.0014	0.0014	0.0051	0.0020	0.0180
4	#04, 1 Liter	0.0450	0.0100	0.0950	0.0510	0.0016	0.0017	0.0051	0.0020	0.0140
5	#05, 1 Liter	0.0460	0.0100	0.0940	0.0510	0.0010	0.0018	0.0051	0.0020	0.0110
6	#06, 1 Liter	0.0098	0.0028	0.1100	0.0510	0.0010	0.0012	0.0051	0.0033	0.0120
7	#07, 3 min 1 Liter	0.0012	0.0010	0.1100	0.0510	0.0010	0.0010	0.0051	0.0033	0.0099

Sample date 2/12/2013; Inside spigot; E302848

Flow rate = 1.77 gpm

pH = 9.48 / 9.56

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.005	0.001	0.11	0.051	0.0092	0.0046	0.0051	0.0025	0.027
2	#02, 1 Liter	0.027	0.0058	0.07	0.051	0.001	0.001	0.0051	0.002	0.011
3	#03, 3 min 1 Liter	0.001	0.001	0.11	0.058	0.001	0.001	0.0051	0.0031	0.009
4	#04, 3 min 1 Liter	0.001	0.001	0.11	0.051	0.001	0.001	0.0051	0.0033	0.0051

Sample date 2/13/2013; Outside spigot; E302952

Flow rate = 1.70 gpm

pH = 9.56 / 9.66

temp = 12.7 / 7.7

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.062	0.0024	0.19	0.051	0.02	0.0075	0.0051	0.0053	0.053
2	#02, 1 Liter	0.031	0.0053	0.086	0.051	0.001	0.001	0.0051	0.0023	0.0091
3	#03, 3 min 1 Liter	0.001	0.001	0.089	0.051	0.001	0.0012	0.0051	0.0022	0.0086
4	#04, 3 min 1 Liter	0.001	0.001	0.089	0.051	0.001	0.001	0.0051	0.0022	0.0085

Sample date 2/21/2013; Outside spigot; E302E17

Flow rate = 2.30 gpm

pH = 9.93 / 10.02

temp = 10.2 / 8.2

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0120	0.0010	0.0920	0.0510	0.0140	0.0061	0.0051	0.0020	0.0120
2	#02, 1 Liter	0.0270	0.0010	0.0980	0.0510	0.0012	0.0010	0.0051	0.0022	0.0140
3	#03, 3 min 1 Liter	0.0010	0.0010	0.1400	0.0510	0.0010	0.0010	0.0051	0.0040	0.0110
4	#04, 3 min 1 Liter	0.0010	0.0010	0.1300	0.0510	0.0010	0.0010	0.0051	0.0039	0.0087

Sample date 2/20/2013; Inside spigot; E302D40

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0110	0.0010	0.1500	0.0510	0.0011	0.0010	0.0051	0.0039	0.0051
2	#02, 1 Liter	0.0130	0.0017	0.1500	0.0510	0.0010	0.0010	0.0051	0.0040	0.0120
3	#03, 3 min 1 Liter	0.0022	0.0010	0.1600	0.0510	0.0010	0.0010	0.0051	0.0043	0.0110
4	#04, 3 min 1 Liter	0.0014	0.0010	0.1600	0.0510	0.0010	0.0010	0.0051	0.0041	0.0120

Sample date 2/26/2013; Inside spigot; E302H07

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1		0.0018	0.001	0.14	0.051	0.001	0.001	0.0051	0.0036	0.0051
2		0.0014	0.001	0.14	0.051	0.001	0.001	0.0051	0.0037	0.0099
3		0.0013	0.001	0.14	0.051	0.001	0.001	0.0051	0.0039	0.0095
4		0.0011	0.001	0.15	0.051	0.001	0.001	0.0051	0.0037	0.0099

Sample date 2/27/2013; Outside spigot; E302159

ATP = 104 ME/mL

Flow rate = 1.93 gpm pH = 9.78 / 9.96

temp = 13.4 / 9.6

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0049	0.0010	0.0790	0.0510	0.0160	0.0069	0.0051	0.0020	0.0092
2	0.0290	0.0042	0.0760	0.0510	0.0011	0.0010	0.0051	0.0020	0.0097
3	0.0010	0.0010	0.0880	0.0510	0.0010	0.0010	0.0051	0.0023	0.0120
4	0.0010	0.0010	0.0880	0.0510	0.0010	0.0010	0.0051	0.0022	0.0088

Sample date 3/5/2013; Inside spigot; E303294

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0260	0.0064	0.0640	0.0510	0.0013	0.0011	0.0051	0.0020	0.0051
2	0.0014	0.0010	0.1200	0.0510	0.0010	0.0010	0.0051	0.0032	0.0090
3	0.0012	0.0010	0.1300	0.0510	0.0010	0.0010	0.0051	0.0034	0.0098
4	0.0011	0.0010	0.1300	0.0510	0.0010	0.0010	0.0051	0.0034	0.0100

Sample date 3/6/2013; Outside spigot; E303574

ATP = 427 ME/mL

Flow rate = 2.04 gpm pH = 9.77 / 9.86

temp = 13.6 / 10.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0076	0.0016	0.0610	0.0510	0.0120	0.0069	0.0051	0.0020	0.0100
2	0.0270	0.0079	0.0570	0.0510	0.0011	0.0010	0.0051	0.0020	0.0110
3	0.0011	0.0010	0.0730	0.0510	0.0010	0.0010	0.0051	0.0020	0.0099
4	0.0012	0.0010	0.0710	0.0510	0.0010	0.0010	0.0051	0.0020	0.0250

Sample date 4/2/2013; Inside spigot; E304160

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0032	0.001	0.088	0.051	0.001	0.001		0.002	0.0051
2	0.0015	0.001	0.086	0.051	0.001	0.001		0.002	0.011
3	0.0014	0.001	0.089	0.051	0.001	0.001		0.0023	0.011

Sample date 4/9/2013; Outside spigot;

ATP = 3268 ME/ml

E304A24

Flow rate = 2.08 gpm

pH = 9.76 / 9.85

temp = 18.3 / 17.2

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0130	0.0010	0.0940	0.0510	0.0150	0.0061		0.0027	0.0240
2	0.0220	0.0092	0.0530	0.0510	0.0057	0.0040		0.0020	0.0160
3	0.0016	0.0010	0.0540	0.0510	0.0010	0.0010		0.0020	0.0110

Sample date 5/7/2013; Outside spigot;

ATP = ??? ME/ml

E305641

Flow rate = 1.76 gpm

pH = 9.86 / 9.80

temp = 20.4 / 18.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0081	0.0010	0.0600	0.0510	0.0082	0.0048		0.0024	0.0120
2	0.0400	0.0089	0.0590	0.0510	0.0012	0.0011		0.0027	0.0051
3	0.0027	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Sample date 5/14/2013; Inside spigot; E305D55

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0310	0.0120	0.0510	0.0510	0.0019	0.0017		0.0020	0.0066
2	0.0058	0.0011	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051
3	0.0028	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Sample date 6/5/2013; Outside spigot;

ATP = ???? ME/ml

E306558

Flow rate = gpm

pH =

temp =

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0210	0.0010	0.2700	0.0510	0.0180	0.0042		0.0091	0.0320
2	0.0330	0.0130	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051
3	0.0037	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Sample date 6/25/2013; Outside spigot;

ATP = ???? ME/ml

E306D17

Flow rate = gpm

pH =

temp =

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0037	0.0010	0.0510	0.0510	0.0062	0.0034		0.0020	0.0180
2	0.0038	0.0010	0.0510	0.0510	0.0016	0.0012		0.0020	0.0091
3	0.0061	0.0026	0.0880	0.0510	0.0013	0.0011		0.0020	0.0120

Loc #3, 32 Lorimer Ave

Two largest concentrations

Below quantitation limits

Date: 1/10/13; outside spigot

E301770

Flow rate = 2.04 gpm

pH = 9.50 / 9.63

	Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
	Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1	#01, 1/2 Liter	Result	0.0140	0.0050	0.051	0.051	0.0160	0.0060	0.0051	0.0020	0.1300
2	#02, 1/2 Liter	Result	0.0230	0.0014	0.220	0.051	0.0100	0.0071	0.0051	0.0058	0.2000
3	#03, 1 Liter	Result	0.0240	0.0042	0.200	0.051	0.0360	0.0120	0.0051	0.0042	0.0280
4	#04, 1 Liter	Result	0.0850	0.0100	0.210	0.051	0.0064	0.0027	0.0051	0.0042	0.0230
5	#05, 1 Liter	Result	0.0870	0.0100	0.210	0.051	0.0019	0.0014	0.0051	0.0041	0.0220
6	#06, 1 Liter	Result	0.0470	0.0052	0.190	0.051	0.0018	0.0012	0.0051	0.0036	0.0220
7	#07, 1 Liter	Result	0.0049	0.0010	0.058	0.051	0.0012	0.0010	0.0051	0.0020	0.0220
8	#08, 3 min 1 Liter	Result	0.0023	0.0010	0.053	0.051	0.0010	0.0010	0.0051	0.0020	0.0210

Date: 1/11/13; outside spigot

E301806

Flow rate = 2.03 gpm

pH = 9.50 / 9.56

	Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
	Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1	#01, 1/2 Liter	Result	0.0160	0.0054	0.051	0.051	0.0120	0.0080	0.0051	0.0020	0.1100
2	#02, 1/2 Liter	Result	0.0120	0.0020	0.052	0.051	0.0120	0.0068	0.0051	0.0020	0.1000
3	#03, 1 Liter	Result	0.0210	0.0099	0.051	0.051	0.0250	0.0140	0.0051	0.0020	0.0280
4	#04, 1 Liter	Result	0.0520	0.0230	0.053	0.051	0.0041	0.0032	0.0051	0.0020	0.0220
5	#05, 1 Liter	Result	0.0500	0.0210	0.051	0.051	0.0018	0.0016	0.0051	0.0020	0.0250
6	#06, 1 Liter	Result	0.0220	0.0025	0.150	0.051	0.0017	0.0012	0.0051	0.0042	0.0230
7	#07, 1 Liter	Result	0.0040	0.0010	0.150	0.051	0.0012	0.0010	0.0051	0.0048	0.0190
8	#08, 3 min 1 Liter	Result	0.0025	0.0010	0.140	0.051	0.0010	0.0010	0.0051	0.0049	0.0230

Date: 1/14/13; inside faucet

E301A06

Flow rate = 1.75 gpm

pH = 9.17 / 9.31

Units		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
Parameter		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1	#01, 1/2 Liter	Result	0.0120	0.0036	0.074	0.051	0.0450	0.0240	0.0051	0.0026	0.0290
2	#02, 1/2 Liter	Result	0.0170	0.0012	0.088	0.051	0.0320	0.0140	0.0051	0.0026	0.0490
3	#03, 1 Liter	Result	0.0180	0.0054	0.084	0.051	0.0300	0.0150	0.0051	0.0022	0.0330
4	#04, 1 Liter	Result	0.0370	0.0130	0.076	0.051	0.0190	0.0095	0.0051	0.0020	0.0210
5	#05, 1 Liter	Result	0.0700	0.0240	0.082	0.051	0.0042	0.0026	0.0051	0.0021	0.0180
6	#06, 1 Liter	Result	0.0640	0.0180	0.074	0.051	0.0028	0.0018	0.0051	0.0020	0.0160
7	#07, 1 Liter	Result	0.0140	0.0042	0.054	0.051	0.0023	0.0018	0.0051	0.0024	0.0160
8	#08, 3 min 1 Liter	Result	0.0026	0.0015	0.051	0.051	0.0020	0.0017	0.0051	0.0020	0.0170

Date: 1/22/13; outside spigot

E301F55

Flow rate = 2.66 gpm

pH = 9.74 / 9.76

Units		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
Parameter		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1	#01 1/2 Liter	Result	0.0290	0.0034	0.130	0.051	0.0210	0.0080	0.0051	0.0040	0.5600
2	#02 1 Liter	Result	0.0230	0.0120	0.051	0.051	0.0200	0.0150	0.0051	0.0020	0.0200
3	#03 1 Liter	Result	0.0450	0.0220	0.051	0.051	0.0048	0.0047	0.0051	0.0020	0.0140
4	#04 1 Liter	Result	0.0390	0.0190	0.051	0.051	0.0023	0.0018	0.0051	0.0020	0.0140
5	#05 1 Liter	Result	0.0120	0.0027	0.072	0.051	0.0017	0.0016	0.0051	0.0020	0.0099
6	#06 1 Liter	Result	0.0035	0.0010	0.065	0.051	0.0014	0.0011	0.0051	0.0020	0.0067
7	#07 3 min 1 Liter	Result	0.0022	0.0010	0.064	0.051	0.0010	0.0010	0.0051	0.0020	0.0051

Date: 1/24/13; outside spigot

E301G88

Flow rate = 2.21 gpm

pH = 9.64

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01 1/2 Liter	Result	0.0150	0.0028	0.056	0.051	0.0310	0.0150	0.0051	0.0020	0.0710
2 #02 1 Liter	Result	0.0370	0.0200	0.051	0.051	0.0170	0.0120	0.0051	0.0020	0.0090
3 #03 1 Liter	Result	0.0500	0.0390	0.051	0.051	0.0029	0.0020	0.0051	0.0020	0.0051
4 #04 1 Liter	Result	0.0350	0.0250	0.053	0.051	0.0021	0.0018	0.0051	0.0020	0.0051
5 #05 1 Liter	Result	0.0085	0.0015	0.070	0.051	0.0016	0.0014	0.0051	0.0020	0.0051
6 #06 1 Liter	Result	0.0032	0.0020	0.060	0.051	0.0016	0.0012	0.0051	0.0020	0.0051
7 #07 3 min 1 Liter	Result	0.0021	0.0014	0.062	0.051	0.0012	0.0015	0.0051	0.0020	0.0051

Date: 2/11/13; inside faucet

E302695

Flow rate = 1.72 gpm

pH = 9.32 / 9.43

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01, 1/2 Liter		0.016	0.0041	0.051	0.051	0.031	0.016	0.0051	0.002	0.019
2 #02, 1 Liter		0.044	0.016	0.051	0.051	0.0029	0.0021	0.0051	0.002	0.01
3 #03, 3 min 1 Liter		0.0023	0.001	0.063	0.051	0.0014	0.0013	0.0051	0.002	0.0092

Date: 2/14/13; outside spigot

E302A39

Flow rate = 2.04 gpm

pH = 9.46 / 9.69

temp = 13.5 / 10.2

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	
1 #01, 1/2 Liter		0.0340	0.0043	0.1600	0.0510	0.0150	0.0049	0.0051	0.0029	1.4000
2 #02, 1 Liter		0.0480	0.0150	0.0510	0.0510	0.0020	0.0017	0.0051	0.0020	0.0160
3 #03, 3 min 1 Liter		0.0018	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0110

Date: 2/18/13; inside faucet

E302C09

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1 #01, 1/2 Liter	0.0210	0.0076	0.0580	0.0510	0.0230	0.0140	0.0051	0.0020	0.0170
2 #02, 1 Liter	0.0500	0.0220	0.0680	0.0510	0.0031	0.0022	0.0051	0.0020	0.0120
3 #03, 3 min 1 Liter	0.0020	0.0010	0.0510	0.0510	0.0012	0.0010	0.0051	0.0020	0.0093

Date: 2/22/13; outside spigot

E302F62

Flow rate = 2.82 gpm

pH = 9.69 / 9.77

temp = 23.5 / 11.3

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1 #01, 1/2 Liter	0.0240	0.0022	0.0860	0.0510	0.0160	0.0110	0.0051	0.0024	0.6800
2 #02, 1 Liter	0.0300	0.0086	0.0510	0.0510	0.0025	0.0022	0.0051	0.0020	0.0210
3 #03, 3 min 1 Liter	0.0018	0.0010	0.0620	0.0510	0.0010	0.0012	0.0051	0.0020	0.0150

Date: 2/25/13; outside spigot

E302H06

Flow rate = 2.89 gpm

pH = 9.87 / 9.91

temp = 15.9 / 10.5

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0130	0.0068	0.0560	0.0510	0.0097	0.0053	0.0051	0.0020	0.3000
2	0.0460	0.0180	0.0510	0.0510	0.0019	0.0018	0.0051	0.0020	0.0150
3	0.0017	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0120

Date: 2/28/13; inside faucet

E303075

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0096	0.0044	0.0510	0.0510	0.0280	0.0180	0.0051	0.0020	0.0160
2	0.0370	0.0170	0.0510	0.0510	0.0025	0.0018	0.0051	0.0020	0.0140
3	0.0019	0.0010	0.0510	0.0510	0.0011	0.0010	0.0051	0.0020	0.0092

Date: 3/4/13; outside spigot**E303295**

ATP = 582 ME/mL

Flow rate = 3.12 gpm

pH = 9.82 / 9.94

temp = 12.8 / 9.1

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0093	0.0022	0.0540	0.0510	0.0230	0.0140	0.0051	0.0020	0.1100
2	0.0370	0.0180	0.0510	0.0510	0.0020	0.0016	0.0051	0.0020	0.0230
3	0.0017	0.0010	0.0550	0.0510	0.0010	0.0010	0.0051	0.0020	0.0130

Date: 3/7/13; inside spigot**E303641**

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0100	0.0045	0.0510	0.0510	0.0240	0.0160	0.0051	0.0020	0.0180
2	0.0063	0.0010	0.1200	0.0510	0.0016	0.0012	0.0051	0.0025	0.0310
3	0.0120	0.0010	17.0000	0.2100	0.0110	0.0089	0.0050	0.1800	0.0280

Date: 3/8/13; inside spigot**E303642**

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0079	0.0035	0.0590	0.0510	0.0170	0.0120		0.0020	0.0140
2	0.0430	0.0210	0.0510	0.0510	0.0024	0.0010		0.0020	0.0094
3	0.0024	0.0010	0.0530	0.0510	0.0013	0.0010		0.0020	0.0110

Date: 4/2/13; outside faucet**E304340**

ATP = 1782 ME/mL

Flow rate = 2.04 gpm

pH = 9.18 / 9.19

temp = 12.9 / 11.1

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0910	0.0073	0.8500	0.0510	0.0280	0.0054		0.0110	1.8000
2	0.0420	0.0250	0.0510	0.0510	0.0018	0.0014		0.0020	0.0240
3	0.0025	0.0012	0.0510	0.0510	0.0010	0.0010		0.0020	0.0110

Date: 5/7/13; outside faucet**E305743**

ATP = ???? ME/mL Flow rate = 2.77 gpm pH = 9.86 / 9.93 temp = 22.4 / 19.0

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc

1	0.0270	0.0022	0.1100	0.0510	0.0087	0.0035		0.0024	2.5000
2	0.0750	0.0410	0.0510	0.0510	0.0021	0.0015		0.0020	0.0480
3	0.0048	0.0016	0.0510	0.0510	0.0010	0.0010		0.0020	0.0057

Date: 5/15/13; inside spigot**E305F21**

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc

1	0.0100	0.0040	0.0510	0.0510	0.0087	0.0058		0.0020	0.0120
2	0.0820	0.0520	0.0510	0.0510	0.0023	0.0015		0.0020	0.0051
3	0.0058	0.0027	0.0510	0.0510	0.0016	0.0017		0.0020	0.0051

Date: 6/6/13; outside faucet**E306710**

ATP = ???? ME/mL Flow rate = ?? gpm pH = temp =

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc

1	0.0270	0.0018	0.1000	0.0510	0.0071	0.0021		0.0029	1.9000
2	0.0830	0.0580	0.0510	0.0510	0.0010	0.0010		0.0020	0.0220
3	0.0067	0.0027	0.0510	0.0510	0.0010	0.0010		0.0020	0.0077

Date: 6/12/13; inside faucet**E306D18**

Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Parameter	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc

1	0.0160	0.0056	0.0510	0.0510	0.0180	0.0098		0.0020	0.0051
2	0.0230	0.0120	0.0510	0.0510	0.0019	0.0013		0.0020	0.0051
3	0.0075	0.0034	0.0510	0.0510	0.0014	0.0010		0.0020	0.0051

Loc #4, 56 Gentian Ave

Two largest concentrations

Below quantitation limits

Date: 1/15/13; inside faucet

E301A44

Flow rate = 1.48 gpm

pH = 9.50 / 9.59

Sample#:		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0077	0.0019	0.051	0.051	0.0220	0.0150	0.0051	0.002	0.0220
2	#02, 1/2 Liter	0.0080	0.0025	0.051	0.051	0.0120	0.0088	0.0051	0.002	0.0051
3	#03, 1 Liter	0.0055	0.0010	0.120	0.051	0.0140	0.0059	0.0051	0.002	0.0240
4	#04, 1 Liter	0.0081	0.0012	0.130	0.051	0.0052	0.0034	0.0051	0.002	0.0190
5	#05, 1 Liter	0.0042	0.0012	0.051	0.051	0.0024	0.0018	0.0051	0.002	0.0300
6	#06, 1 Liter	0.0021	0.0010	0.051	0.051	0.0024	0.0020	0.0051	0.002	0.0200
7	#07, 1 Liter	0.0019	0.0010	0.051	0.051	0.0021	0.0021	0.0051	0.002	0.0180
8	#08, 1 Liter	0.0013	0.0010	0.051	0.051	0.0012	0.0012	0.0051	0.002	0.0180
9	#09, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0220
10	#10, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0150

Date: 1/17/13; outside spigot

E301C76

Flow rate = 1.30 gpm

pH = 9.84 / 9.91

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#02, 1/2 Liter	0.0150	0.0078	0.051	0.051	0.0043	0.0031	0.0051	0.002	0.0080
2	#03, 1 Liter	0.0039	0.0016	0.051	0.051	0.0028	0.0024	0.0051	0.002	0.0190
3	#04, 1 Liter	0.0034	0.0010	0.051	0.051	0.0017	0.0016	0.0051	0.002	0.0170
4	#05, 1 Liter	0.0019	0.0010	0.051	0.051	0.0011	0.0010	0.0051	0.002	0.0310
5	#06, 1 Liter	0.0015	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0170
6	#07, 1 Liter	0.0016	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0170
7	#08, 1 Liter	0.0014	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0220
8	#09, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0160
9	#10, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0051

Date: 1/23/13; outside spigot

E301G28

Flow rate = 1.38 gpm

pH = 9.61 / 9.75

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0170	0.0055	0.051	0.051	0.0090	0.0054	0.0051	0.002	0.0051
2	#02, 1 Liter	0.0086	0.0033	0.051	0.051	0.0052	0.0034	0.0051	0.002	0.0091
3	#03, 1 Liter	0.0110	0.0030	0.051	0.051	0.0018	0.0013	0.0051	0.002	0.0051
4	#04, 1 Liter	0.0036	0.0010	0.051	0.051	0.0014	0.0011	0.0051	0.002	0.0051
5	#05, 1 Liter	0.0016	0.0010	0.051	0.051	0.0013	0.0010	0.0051	0.002	0.0051
6	#06, 1 Liter	0.0014	0.0010	0.051	0.051	0.0012	0.0010	0.0051	0.002	0.0051
7	#07, 1 Liter	0.0014	0.0010	0.051	0.051	0.0010	0.0011	0.0051	0.002	0.0051
8	#08, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051
9	#09, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051

Date: 1/25/13; outside spigot

E301H02

Flow rate = 1.52 gpm

pH = 9.66 / 9.79

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0084	0.0019	0.051	0.051	0.0200	0.0080	0.0051	0.002	0.0300
2	#02, 1 Liter	0.0110	0.0030	0.051	0.051	0.0120	0.0062	0.0051	0.002	0.0330
3	#03, 1 Liter	0.0180	0.0038	0.051	0.051	0.0022	0.0016	0.0051	0.002	0.0051
4	#04, 1 Liter	0.0044	0.0010	0.051	0.051	0.0016	0.0013	0.0051	0.002	0.0051
5	#05, 1 Liter	0.0016	0.0010	0.051	0.051	0.0016	0.0018	0.0051	0.002	0.0051
6	#06, 1 Liter	0.0014	0.0010	0.051	0.051	0.0013	0.0013	0.0051	0.002	0.0051
7	#07, 1 Liter	0.0014	0.0010	0.051	0.051	0.0022	0.0023	0.0051	0.002	0.0051
8	#08, 1 Liter	0.0014	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0051
9	#09, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051

Date: 1/28/13; outside spigot**E301H38**

Flow rate = 1.57 gpm

pH = 9.52 / 9.72

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0230	0.0077	0.055	0.051	0.0250	0.0200	0.0051	0.002	0.0051
2	#02, 1 Liter	0.0180	0.0100	0.051	0.051	0.0170	0.0140	0.0051	0.002	0.0190
3	#03, 1 Liter	0.0300	0.0160	0.051	0.051	0.0030	0.0025	0.0051	0.002	0.0051
4	#04, 1 Liter	0.0063	0.0020	0.051	0.051	0.0022	0.0015	0.0051	0.002	0.0051
5	#05, 1 Liter	0.0017	0.0010	0.051	0.051	0.0016	0.0014	0.0051	0.002	0.0051
6	#06, 1 Liter	0.0015	0.0012	0.051	0.051	0.0019	0.0016	0.0051	0.002	0.0051
7	#07, 1 Liter	0.0014	0.0010	0.051	0.051	0.0012	0.0010	0.0051	0.002	0.0051
8	#08, 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.002	0.0051
9	#09, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0012	0.0051	0.002	0.0051

Date: 2/11/13; outside faucet**E302594**

Flow rate = 1.82 gpm

pH = 9.74 / 9.78

temp = 3.4 / 2.8

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0041	0.001	0.051	0.051	0.0055	0.0034	0.0051	0.002	0.0051
2	#02, 1 Liter **	0.0013	0.001	0.051	0.051	0.0012	0.0012	0.0051	0.002	0.0088
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0087

Date: 2/12/13; inside spigot**E302694**

Flow rate = 1.90 gpm

pH = 9.71 / 9.72

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.011	0.001	0.055	0.051	0.0045	0.0025	0.0051	0.002	0.0051
2	#02, 1 Liter **	0.0013	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0096
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0092

Date: 2/18/13; inside faucet**E302A72**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0100	0.0022	0.0510	0.0510	0.0061	0.0041	0.0051	0.0020	0.0051
2	#02, 1 Liter **	0.0012	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0086
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0083

Date: 2/19/13; outside spigot**E302C07**

Flow rate = 0.88 gpm

pH = 9.75 / 9.82

temp = 10.2 / 6.7

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0110	0.0020	0.0510	0.0510	0.0045	0.0022	0.0051	0.0020	0.0056
2	#02, 1 Liter **	0.0018	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0096
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0091

Date: 2/25/13; outside spigot**E302G22**

Flow rate = 1.21 gpm

pH = 9.82 / 9.97

temp = 13.9 / 8.9

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0100	0.0039	0.0510	0.0510	0.0098	0.0089	0.0051	0.0020	0.0051
2		0.0100	0.0014	0.0510	0.0510	0.0014	0.0020	0.0051	0.0020	0.0094
3		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0093

Date: 2/26/13; inside faucet

E302H08

	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.011	0.0031	0.051	0.051	0.01	0.0069	0.0051	0.002	0.0051
2	0.007	0.0034	0.051	0.051	0.0014	0.0013	0.0051	0.002	0.0093
3	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0075

Date: 3/4/13; outside spigot

E303185

ATP = 256 ME/mL

Flow rate = 1.15 gpm

pH = 9.90 / 9.99

temp = 10.2 / 8.4

	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0080	0.0050	0.0510	0.0510	0.0120	0.0092	0.0051	0.0020	0.0060
2	0.0120	0.0060	0.0510	0.0510	0.0016	0.0014	0.0051	0.0020	0.0120
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0089

Date: 3/5/13; inside faucet

E303293

	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0096	0.0037	0.0510	0.0510	0.0150	0.0100	0.0051	0.0020	0.0051
2	0.0093	0.0032	0.0510	0.0510	0.0018	0.0019	0.0051	0.0020	0.0120
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0091

Date: 4/2/13; outside faucet**E304159**

ATP = 145 ME/mL

Flow rate = 1.33 gpm

pH = 10.12 / 9.80

temp = 9.7 / 7.6

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0027	0.0010	0.0510	0.0510	0.0044	0.0033		0.0020	0.0150
2	0.0059	0.0026	0.0510	0.0510	0.0010	0.0010		0.0020	0.0120
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0180

Date: 4/8/13; inside faucet**E304643**

ATP = ??? ME/mL

Flow rate = 1.38 gpm

pH = 9.91 / 10.0

temp = 17.5 / 14.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0110	0.0052	0.0510	0.0510	0.0093	0.0071		0.0020	0.0051
2	0.0079	0.0038	0.0510	0.0510	0.0098	0.0072		0.0020	0.0140
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0110

Date: 5/9/13; outside faucet**E305879**

ATP = ??? ME/mL

Flow rate = 1.38 gpm

pH = 9.91 / 10.0

temp = 17.5 / 14.5

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0094	0.0051	0.0510	0.0510	0.0097	0.0072		0.0020	0.0074
2	0.0260	0.0150	0.0510	0.0510	0.0014	0.0012		0.0020	0.0051
3	0.0023	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 5/15/13; inside faucet

E305D56

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0098	0.0026	0.0510	0.0510	0.0100	0.0061		0.0020	0.0051
2	0.0380	0.0130	0.0520	0.0510	0.0016	0.0013		0.0020	0.0051
3	0.0023	0.0010	0.0720	0.0510	0.0010	0.0010		0.0023	0.0051

Date: 6/6/13; inside faucet

E306707

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0130	0.0070	0.0510	0.0510	0.0067	0.0044		0.0020	0.0060
2	0.0220	0.0130	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051
3	0.0027	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 6/12/13; outside faucet

E306B40

ATP = ??? ME/mL

Flow rate = ?? gpm

pH = ??

temp = ??

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0260	0.0150	0.0510	0.0510	0.0070	0.0049		0.0020	0.0054
2	0.0240	0.0120	0.0510	0.0510	0.0018	0.0014		0.0020	0.0074
3	0.0032	0.0016	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Loc # 5, 42 Harkness Street

Two largest concentrations

Below quantitation limits

Date: 1/8/13; outside spigot

E301630

Flow rate = pH = 9.66 / 9.79

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0110	0.0065	0.051	0.051	0.0470	0.0330	0.0051	0.0036	0.0180
2	#02, 1/2 Liter	0.0083	0.0039	0.051	0.051	0.0690	0.0290	0.0051	0.0034	0.0067
3	#03, 1 Liter	0.0038	0.0023	0.051	0.051	0.0460	0.0280	0.0051	0.0027	0.0270
4	#04, 1 Liter	0.0220	0.0150	0.051	0.051	0.0059	0.0046	0.0051	0.0022	0.0190
5	#05, 1 Liter	0.0150	0.0093	0.051	0.051	0.0021	0.0019	0.0051	0.0020	0.0051
6	#06, 3 min 1 Liter	0.0019	0.0010	0.051	0.051	0.0059	0.0043	0.0051	0.0020	0.0051

Date: 1/9/13; outside spigot

E301689

Flow rate = 2.20 gpm pH = 9.44 / 9.57

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0150	0.0061	0.051	0.051	0.1000	0.0300	0.0051	0.0020	0.0150
2	#02, 1/2 Liter	0.0067	0.0017	0.051	0.051	0.0460	0.0240	0.0051	0.0020	0.0051
3	#03, 1 Liter	0.0150	0.0088	0.051	0.051	0.0140	0.0099	0.0051	0.0020	0.0730
4	#04, 1 Liter	0.0330	0.0190	0.051	0.051	0.0021	0.0016	0.0051	0.0020	0.0058
5	#05, 1 Liter	0.0047	0.0010	0.051	0.051	0.0014	0.0012	0.0051	0.0041	0.0051
6	#06, 3 min 1 Liter	0.0017	0.0010	0.051	0.051	0.0031	0.0019	0.0051	0.0042	0.0062

Date: 1/23/13; inside faucet**E301G27**

Flow rate = 0.99 gpm

pH = 9.43 / 9.40

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0028	0.0010	0.051	0.051	0.0099	0.0091	0.0051	0.0020	0.0540
2	#02, 1 Liter	0.0026	0.0012	0.051	0.051	0.0130	0.0094	0.0051	0.0020	0.0560
3	#03, 1 Liter	0.0029	0.0017	0.051	0.051	0.0200	0.0160	0.0051	0.0020	0.0160
4	#04, 1 Liter	0.0084	0.0026	0.051	0.051	0.0150	0.0100	0.0051	0.0020	0.0480
5	#05, 1 Liter	0.0280	0.0170	0.051	0.051	0.0034	0.0028	0.0051	0.0020	0.0160
6	#06, 1 Liter	0.0096	0.0028	0.055	0.051	0.0018	0.0015	0.0051	0.0026	0.0051
7	#07, 3 min 1 Liter	0.0010	0.0010	0.064	0.051	0.0010	0.0010	0.0051	0.0029	0.0051

Date: 1/25/13; outside spigot**E301G94**

Flow rate = 3.31 gpm

pH = 9.37 / 9.63

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0360	0.0100	0.120	0.051	0.0230	0.0110	0.0051	0.0023	0.0910
2	#02, 1 Liter	0.0220	0.0074	0.094	0.051	0.0046	0.0024	0.0051	0.0030	0.0051
3	#03, 1 Liter	0.0013	0.0010	0.065	0.051	0.0027	0.0025	0.0051	0.0032	0.0051
4	#04, 1 Liter	0.0011	0.0010	0.064	0.051	0.0020	0.0012	0.0051	0.0031	0.0051
5	#05, 3 min 1 Liter	0.0010	0.0010	0.058	0.051	0.0010	0.0010	0.0051	0.0031	0.0051

Date: 1/30/13; outside spigot**E301J95**

Flow rate = 2.95 gpm

pH = 9.25 / 9.61

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0150	0.0023	0.0520	0.0510	0.0940	0.0300	0.0051	0.0020	0.0092
2	#02, 1 Liter	0.0120	0.0059	0.0510	0.0510	0.0460	0.0200	0.0051	0.0020	0.0780
3	#03, 1 Liter	0.0300	0.0160	0.0510	0.0510	0.0033	0.0028	0.0051	0.0020	0.0160
4	#04, 1 Liter	0.0057	0.0010	0.0510	0.0510	0.0022	0.0027	0.0051	0.0020	0.0110
5	#05, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0014	0.0051	0.0020	0.0130

Date: 2/13/13; inside spigot**E302845**

Flow rate = 1.00 gpm

pH = 9.49 / 9.48

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0021	0.001	0.051	0.051	0.011	0.0072	0.0051	0.002	0.055
2	#02, 1 Liter	0.02	0.0087	0.051	0.051	0.0072	0.004	0.0051	0.002	0.046
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.002	0.0012	0.0051	0.002	0.011

Date: 2/15/13; outside spigot**E302A02**

Flow rate = 2.51 gpm

pH = 9.56 / 9.70

temp = 18.0 / 14.5

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.016	0.0021	0.051	0.051	0.75	0.038	0.0051	0.002	0.01
2	#02, 1 Liter	0.024	0.014	0.051	0.051	0.0093	0.0059	0.0051	0.002	0.041
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0091

Date: 2/22/13; outside spigot**E302F63**

Flow rate = 3.06 gpm

pH = 9.59 / 9.86

temp = 15.4 / 10.1

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0100	0.0030	0.0510	0.0510	0.1300	0.0520	0.0051	0.0020	0.0088
2	#02, 1 Liter	0.0240	0.0140	0.0510	0.0510	0.0069	0.0038	0.0051	0.0046	0.0590
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0011	0.0051	0.0020	0.0092

Date: 2/27/13; outside spigot**E302I27**

ATP = 95 ME/mL

Flow rate = 3.01 gpm

pH = 9.67 / 9.87

temp = 16.6 / 10.3

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1		0.0036	0.0010	0.0510	0.0510	0.0830	0.0260	0.0051	0.0020	0.0063
2		0.0240	0.0130	0.0510	0.0510	0.0030	0.0020	0.0051	0.0020	0.0140
3		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0030	0.0097

Date: 3/1/13; inside spigot**E303080**

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1		0.0016	0.0010	0.0510	0.0081	0.0059	0.0510	0.0051	0.0020	0.0640
2		0.0190	0.0130	0.0510	0.0079	0.0040	0.0510	0.0051	0.0020	0.0510
3		0.0010	0.0010	0.0510	0.0023	0.0011	0.0510	0.0051	0.0020	0.0099

Date: 3/6/13; outside spigot**E303459**

ATP = 345 ME/mL Flow rate = 3.73 gpm pH = 9.72 / 9.87 temp = 16.3 / 10.9

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0170	0.0013	0.0680	0.0510	0.0960	0.0240	0.0051	0.0020	0.0110
2	0.0240	0.0140	0.0510	0.0510	0.0058	0.0045	0.0051	0.0020	0.0160
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

Date: 3/8/13; inside spigot**E303639**

ATP = 345 ME/mL Flow rate = 3.73 gpm pH = 9.72 / 9.87 temp = 16.3 / 10.9

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0016	0.0010	0.0510	0.0510	0.0073	0.0056	0.0051	0.0020	0.0610
2	0.0180	0.0120	0.0510	0.0510	0.0041	0.0030	0.0051	0.0020	0.0480
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

Date: 4/8/13; outside spigot**E304642**

ATP = 1904 ME/mL Flow rate = 2.91 gpm pH = 10.02 / 10.16 temp = 13.8 / 12.2

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0200	0.0047	0.0510	0.0510	2.9000	0.3800		0.0020	0.0200
2	0.0270	0.0180	0.0510	0.0510	0.0250	0.0120		0.0020	0.0330
3	0.0011	0.0010	0.0510	0.0510	0.0014	0.0011		0.0020	0.0091

Date: 4/12/13; inside spigot**E304A65**

ATP = 345 ME/mL Flow rate = 3.73 gpm pH = 9.72 / 9.87 temp = 16.3 / 10.9

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0029	0.0014	0.0510	0.0510	0.0072	0.0058		0.0020	0.0370
2	0.0025	0.0010	0.0510	0.0510	0.0190	0.0060		0.0020	0.0180
3	0.0016	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0110

Date: 5/7/13; outside spigot**E305644**

ATP = ??? ME/mL

Flow rate = 3.09 gpm

pH = 10.05 / 9.69

temp = 12.0 / 11.2

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0170	0.0023	0.8300	0.0510	0.1600	0.0240		0.0040	0.0090
2	0.0710	0.0270	0.0790	0.0510	0.0039	0.0026		0.0020	0.0051
3	0.0060	0.0012	0.3200	0.0510	0.0017	0.0010		0.0034	0.0051

Date: 5/14/13; inside spigot**E305C74**

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

1	0.0019	0.0012	0.0510	0.0510	0.0039	0.0033		0.0020	0.0560
2	0.0280	0.0200	0.0510	0.0510	0.0025	0.0019		0.0020	0.0170
3	0.0019	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 6/4/13; outside spigot**E306286**

ATP = ??? ME/mL

Flow rate = ?? gpm

pH =

temp =

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

1	0.0099	0.0020	0.0510	0.0510	0.3300	0.0400		0.0020	0.0200
2	0.0490	0.0350	0.0510	0.0510	0.0039	0.0030		0.0020	0.0120
3	0.0022	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 6/17/13; inside spigot**E306F35**

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

1	0.0110	0.0048	0.0510	0.0510	0.0100	0.0076		0.0020	0.1000
2	0.0400	0.0310	0.0510	0.0510	0.0036	0.0030		0.0020	0.0700
3	0.0027	0.0014	0.0510	0.0510	0.0010	0.0010		0.0020	0.0052

Loc #6, 104 Shaw Ave

Two largest concentrations

Below quantitation limits

Date: 1/11/13; inside faucet

E301808

Flow rate = 1.30 gpm

pH = 9.43 / 9.60

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0780	0.0042	0.16	0.051	0.3200	0.0160	0.0051	0.0025	3.3000
2	#02, 1/2 Liter	0.0085	0.0010	0.12	0.051	0.0570	0.0190	0.0051	0.0020	0.0900
3	#03, 1 Liter	0.0086	0.0021	0.11	0.051	0.0550	0.0250	0.0051	0.0020	0.0350
4	#04, 1 Liter	0.0092	0.0023	0.11	0.051	0.0460	0.0220	0.0051	0.0020	0.0160
5	#05, 1 Liter	0.0250	0.0055	0.10	0.051	0.0290	0.0130	0.0051	0.0020	0.0150
6	#06, 1 Liter	0.0360	0.0043	0.11	0.051	0.0140	0.0062	0.0051	0.0020	0.0140
7	#07, 1 Liter	0.0510	0.0087	0.11	0.051	0.0064	0.0029	0.0051	0.0020	0.0340
8	#08, 1 Liter	0.0580	0.0090	0.12	0.051	0.0032	0.0017	0.0051	0.0020	0.0210
9	#09, 1 Liter	0.0580	0.0088	0.14	0.051	0.0034	0.0018	0.0051	0.0020	0.0280
10	#10, 1 Liter	0.0500	0.0065	0.20	0.051	0.0026	0.0014	0.0051	0.0020	0.0060
11	#11, 1 Liter	0.0310	0.0035	0.24	0.051	0.0024	0.0022	0.0051	0.0031	0.0220
12	#12, 1 Liter	0.0100	0.0011	0.29	0.051	0.0021	0.0014	0.0051	0.0042	0.0210
13	#13, 3 min 1 Liter	0.0026	0.0010	0.30	0.058	0.0015	0.0010	0.0051	0.0044	0.0240

Date: 1/17/13; outside spigot**E301C78**

Flow rate = 1.80 gpm pH = 9.61 / 9.78

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#02, 1/2 Liter	0.0078	0.0014	0.36	0.051	0.1000	0.0300	0.0051	0.0033	0.0068
2	#03, 1 Liter	0.0072	0.0032	0.18	0.062	0.0580	0.0350	0.0051	0.0021	0.0051
3	#04, 1 Liter	0.0072	0.0029	0.13	0.051	0.0430	0.0250	0.0051	0.0020	0.0051
4	#05, 1 Liter	0.0082	0.0037	0.13	0.051	0.0470	0.0290	0.0051	0.0020	0.0051
5	#06, 1 Liter	0.0120	0.0014	0.12	0.051	0.0230	0.0100	0.0051	0.0020	0.0210
6	#07, 1 Liter	0.0450	0.0077	0.11	0.051	0.0071	0.0036	0.0051	0.0020	0.0051
7	#08, 1 Liter	0.0550	0.0140	0.12	0.051	0.0036	0.0022	0.0051	0.0020	0.0051
8	#09, 1 Liter	0.0600	0.0190	0.12	0.051	0.0031	0.0020	0.0051	0.0020	0.0200
9	#10, 1 Liter	0.0570	0.0200	0.12	0.051	0.0028	0.0019	0.0051	0.0020	0.0240
10	#11, 1 Liter	0.0240	0.0070	0.21	0.057	0.0025	0.0014	0.0051	0.0030	0.0051
11	#12, 3 min 1 Liter	0.0024	0.0010	0.25	0.051	0.0013	0.0010	0.0051	0.0041	0.0051

Date: 1/22/13; outside spigot**E301F56**

Flow rate = 1.15 gpm pH = 9.55 / 9.74

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	0.1400	0.0024	1.40	0.078	0.1400	0.0310	0.015	0.0065	0.0470
2	#02 1 Liter	0.0100	0.0031	0.32	0.062	0.0610	0.0260	0.0051	0.0025	0.0220
3	#03 1 Liter	0.0059	0.0011	0.32	0.058	0.0220	0.0077	0.0051	0.0034	0.0260
4	#04 1 Liter	0.0046	0.0026	0.31	0.074	0.0150	0.0066	0.0051	0.0037	0.0200
5	#05 1 Liter	0.0049	0.0010	0.30	0.051	0.0110	0.0037	0.0051	0.0033	0.0051
6	#06 1 Liter	0.0130	0.0027	0.30	0.056	0.0058	0.0025	0.0051	0.0035	0.0240
7	#07 1 Liter	0.0240	0.0070	0.30	0.082	0.0036	0.0023	0.0051	0.0034	0.0200
8	#08 1 Liter	0.0260	0.0049	0.29	0.051	0.0025	0.0017	0.0051	0.0035	0.0150
9	#09 1 Liter	0.0260	0.0066	0.29	0.068	0.0025	0.0020	0.0051	0.0034	0.0180
10	#10 1 Liter	0.0210	0.0048	0.27	0.057	0.0022	0.0017	0.0051	0.0034	0.0051
11	#11 3 min 1 Liter	0.0025	0.0010	0.24	0.072	0.0014	0.0010	0.0051	0.0033	0.0051

Date: 1/24/13; outside spigot

E301G91

Flow rate = 1.12 gpm pH = 9.68 / 9.86

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	0.0900	0.0010	3.20	0.051	0.1900	0.0087	0.005	0.0220	0.0680
2	#02 1 Liter	0.0160	0.0031	0.47	0.086	0.0710	0.0310	0.0051	0.0045	0.0250
3	#03 1 Liter	0.0110	0.0039	0.18	0.063	0.0570	0.0290	0.0051	0.0022	0.0120
4	#04 1 Liter	0.0110	0.0056	0.17	0.074	0.0560	0.0360	0.0051	0.0020	0.0091
5	#05 1 Liter	0.0140	0.0061	0.15	0.058	0.0400	0.0250	0.0051	0.0020	0.0053
6	#06 1 Liter	0.0420	0.0080	0.14	0.051	0.0160	0.0095	0.0051	0.0020	0.0051
7	#07 1 Liter	0.0810	0.0160	0.14	0.051	0.0060	0.0041	0.0051	0.0020	0.0051
8	#08 1 Liter	0.0900	0.0210	0.14	0.051	0.0035	0.0025	0.0051	0.0020	0.0051
9	#09 1 Liter	0.0940	0.0140	0.14	0.051	0.0033	0.0019	0.0051	0.0020	0.0051
10	#10 1 Liter	0.0740	0.0260	0.16	0.051	0.0049	0.0031	0.0051	0.0020	0.0051
11	#11 3 min 1 Liter	0.0026	0.0010	0.24	0.051	0.0013	0.0011	0.0051	0.0030	0.0051

Date: 1/29/13; outside spigot

E301I73

Flow rate = 1.35 gpm pH = 9.62 / 9.85

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01 1/2 Liter	0.0620	0.0010	1.60	0.051	0.1400	0.0110	0.005	0.0081	0.0260
2	#02 1 Liter	0.0450	0.0044	0.55	0.064	0.1000	0.0300	0.0051	0.0043	0.0260
3	#03 1 Liter	0.0170	0.0047	0.24	0.066	0.0610	0.0370	0.0051	0.0022	0.0140
4	#04 1 Liter	0.0240	0.0043	0.20	0.053	0.0620	0.0270	0.0051	0.0021	0.0160
5	#05 1 Liter	0.0220	0.0049	0.16	0.051	0.0420	0.0160	0.0051	0.0020	0.0130
6	#06 1 Liter	0.0510	0.0100	0.15	0.051	0.0150	0.0056	0.0051	0.0021	0.0120
7	#07 1 Liter	0.0770	0.0150	0.12	0.051	0.0049	0.0021	0.0051	0.0020	0.0150
8	#08 1 Liter	0.0850	0.0180	0.13	0.051	0.0033	0.0020	0.0051	0.0020	0.0095
9	#09 1 Liter	0.0860	0.0160	0.13	0.051	0.0033	0.0019	0.0051	0.0020	0.0090
10	#10 1 Liter	0.0590	0.0120	0.18	0.051	0.0028	0.0015	0.0051	0.0026	0.0100
11	#11 3 min 1 Liter	0.0025	0.0010	0.29	0.056	0.0013	0.0010	0.0051	0.0046	0.0085

Date: 2/14/13; inside faucet

E302954

Flow rate = 1.24 gpm pH = 9.60 / 9.70

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0089	0.001	0.12	0.051	0.059	0.017	0.0051	0.002	0.0051
2	#02, 1 Liter	0.045	0.0043	0.11	0.051	0.003	0.0029	0.0051	0.002	0.01
3	#03, 3 min 1 Liter	0.0023	0.001	0.23	0.053	0.0015	0.001	0.0051	0.0039	0.0091

Date: 2/15/13; outside spigot

E302999

Flow rate = 1.15 gpm pH = 9.60 / 9.72 temp = 15.5 / 12.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0180	0.0012	1.5000	0.0510	0.1200	0.0220	0.0050	0.0056	0.0150
2	#02, 1 Liter	0.0560	0.0110	0.1200	0.0510	0.0053	0.0030	0.0051	0.0020	0.0120
3	#03, 3 min 1 Liter	0.0021	0.0010	0.2700	0.0510	0.0013	0.0012	0.0051	0.0033	0.0087

Date: 2/19/13; outside spigot

E302C08

Flow rate = 1.08 gpm pH = 9.67 / 9.78 temp = 15.4 / 12.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.015	0.0028	0.71	0.057	0.13	0.032	0.005	0.0031	0.0062
2	#02, 1 Liter	0.039	0.01	0.091	0.051	0.0046	0.0025	0.0051	0.002	0.0091
3	#03, 3 min 1 Liter	0.003	0.001	0.24	0.056	0.002	0.001	0.0051	0.0031	0.0085

Date: 2/22/13; inside faucet**E302F61**

Flow rate = 1.24 gpm pH = 9.60 / 9.70

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1 #01, 1/2 Liter	0.0100	0.0038	0.0930	0.0510	0.0470	0.0260	0.0051	0.0020	0.0051
2 #02, 1 Liter	0.0280	0.0035	0.1600	0.0510	0.0026	0.0012	0.0051	0.0024	0.0110
3 #03, 3 min 1 Liter	0.0021	0.0010	0.2400	0.0580	0.0014	0.0010	0.0051	0.0036	0.0100

Date: 2/25/13; outside spigot**E302G21**

Flow rate = 1.03 gpm pH = 9.79 / 9.95 temp = 15.2 / 12.2

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0081	0.0010	0.7000	0.0510	0.1100	0.0170	0.0050	0.0028	0.0070
2	0.0240	0.0022	0.1200	0.0510	0.0044	0.0028	0.0051	0.0020	0.0095
3	0.0019	0.0019	0.1500	0.0580	0.0013	0.0015	0.0051	0.0025	0.0092

Date: 2/28/13; inside faucet**E303078**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0160	0.0026	0.0970	0.0510	0.0380	0.0150	0.0051	0.0020	0.0051
2	0.0340	0.0110	0.0910	0.0510	0.0030	0.0020	0.0051	0.0020	0.0110
3	0.0022	0.0010	0.1400	0.0510	0.0014	0.0010	0.0051	0.0021	0.0100

Date: 3/4/13; inside faucet**E303184**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0066	0.0030	0.0840	0.0510	0.0440	0.0270	0.0051	0.0020	0.0066
2	0.0480	0.0190	0.0780	0.0510	0.0032	0.0023	0.0051	0.0020	0.0120
3	0.0023	0.0010	0.2300	0.0510	0.0015	0.0010	0.0051	0.0033	0.0100

Date: 3/6/13; outside spigot**E303460**

ATP = 437 ME/mL

Flow rate = 1.31 gpm

pH = 9.83 / 9.96

temp = 14.8 / 11.3

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0079	0.0010	1.3000	0.0510	0.1400	0.0180	0.0050	0.0043	0.0240
2	0.0140	0.0029	0.1600	0.0510	0.0028	0.0019	0.0051	0.0025	0.0110
3	0.0020	0.0010	0.2200	0.0510	0.0012	0.0010	0.0051	0.0033	0.0097

Date: 4/4/13; inside faucet**E304399**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0071	0.0010	0.1100	0.0510	0.0280	0.0140		0.0020	0.0051
2	0.0370	0.0045	0.1400	0.0510	0.0020	0.0012		0.0020	0.0100
3	0.0035	0.0010	0.2000	0.0510	0.0011	0.0010		0.0020	0.0100

Date: 4/10/13; outside spigot**E304901**

ATP = 1453 ME/mL Flow rate = 1.66 gpm pH = 9.97 / 10.15 temp = 16.3 / 11.6

ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	

1	0.0140	0.0038	1.1000	0.1500	0.2800	0.0590		0.1200	0.0062
2	0.0170	0.0034	0.1400	0.0510	0.0026	0.0016		0.0020	0.0095
3	0.0034	0.0010	0.1800	0.0510	0.0015	0.0011		0.0020	0.0130

Date: 5/7/13; outside spigot**E305643**

ATP = ??? ME/mL Flow rate = 1.44 gpm pH = 9.96 / 9.41 temp = 18.5 / 15.9

ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	

1	0.0160	0.0088	0.0510	0.0510	0.0220	0.0095		0.0020	0.0150
2	0.0024	0.0010	0.0510	0.0510	0.0047	0.0025		0.0020	0.0051
3	0.0017	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 5/14/13; inside faucet**E305C69**

ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc	

1	0.0120	0.0038	0.0760	0.0510	0.0250	0.0130		0.0020	0.0051
2	0.0820	0.0300	0.0680	0.0510	0.0019	0.0014		0.0020	0.0051
3	0.0072	0.0016	0.0900	0.0510	0.0012	0.0010		0.0020	0.0051

Date: 6/6/13; inside faucet E306709

	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0130	0.0022	0.0920	0.0510	0.0220	0.0097		0.0020	0.0100
2	0.0840	0.0290	0.0560	0.0510	0.0011	0.0010		0.0020	0.0051
3	0.0088	0.0010	0.0790	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 6/25/13; outside spigot E306D16

	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	0.0120	0.0027	0.2500	0.0510	0.0400	0.0130		0.0020	0.0062
2	0.1100	0.0450	0.0880	0.0510	0.0022	0.0014		0.0020	0.0051
3	0.0096	0.0015	0.1100	0.0510	0.0012	0.0010		0.0020	0.0051

Loc #7, 183 Laurel Hill Ave

Two largest concentrations

Below quantitation limits

Date: 1/15/13; inside faucet

E301A41

Flow rate = 1.24 gpm

pH = 9.29 / 9.33

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
2	#02, 1/2 Liter	0.0068	0.0010	0.097	0.051	0.0400	0.0160	0.0051	0.0030	0.0085
3	#03, 1 Liter	0.0042	0.0010	0.095	0.051	0.0280	0.0150	0.0051	0.0028	0.0200
4	#04, 1 Liter	0.0044	0.0011	0.092	0.051	0.0310	0.0160	0.0051	0.0028	0.0210
5	#05, 1 Liter	0.0054	0.0013	0.090	0.051	0.0300	0.0140	0.0051	0.0027	0.0220
6	#06, 1 Liter	0.0078	0.0019	0.095	0.051	0.0190	0.0098	0.0051	0.0027	0.0370
7	#07, 1 Liter	0.0370	0.0044	0.092	0.051	0.0060	0.0035	0.0051	0.0023	0.0300
8	#08, 1 Liter	0.0480	0.0097	0.090	0.051	0.0028	0.0019	0.0051	0.0024	0.0180
9	#09, 1 Liter	0.0200	0.0064	0.058	0.051	0.0021	0.0020	0.0051	0.0020	0.0180
10	#10, 3 min 1 Liter	0.0013	0.0010	0.051	0.051	0.0013	0.0021	0.0051	0.0020	0.0180

Date: 1/18/13; outside spigot

E301D06

Flow rate = 1.49 gpm

pH = 9.59 / 9.72

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0030	0.0010	0.051	0.051	0.0300	0.0200	0.0051	0.0020	0.0069
2	#02, 1 Liter	0.0034	0.0030	0.051	0.051	0.0310	0.0220	0.0051	0.0020	0.0051
3	#03, 1 Liter	0.0051	0.0029	0.051	0.051	0.0300	0.0180	0.0051	0.0020	0.0340
4	#04, 1 Liter	0.0096	0.0052	0.051	0.051	0.0200	0.0120	0.0051	0.0020	0.0420
5	#05, 1 Liter	0.0280	0.0160	0.051	0.051	0.0044	0.0040	0.0051	0.0020	0.0290
6	#06, 1 Liter	0.0330	0.0150	0.051	0.051	0.0020	0.0019	0.0051	0.0020	0.0220
7	#07, 1 Liter	0.0100	0.0037	0.051	0.051	0.0015	0.0014	0.0051	0.0020	0.0170
8	#08, 3 min 1 Liter	0.0012	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0190

Date: 1/24/13; outside spigot E301G89

Flow rate = 1.56 gpm pH = 9.61 / 9.70

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0120	0.0033	0.051	0.051	0.0360	0.0180	0.0051	0.0020	0.0460
2	#02, 1 Liter	0.0054	0.0030	0.051	0.051	0.0230	0.0180	0.0051	0.0020	0.0210
3	#03, 1 Liter	0.0110	0.0067	0.051	0.051	0.0110	0.0085	0.0051	0.0020	0.0150
4	#04, 1 Liter	0.0200	0.0130	0.051	0.051	0.0040	0.0034	0.0051	0.0020	0.0051
5	#05, 1 Liter	0.0150	0.0079	0.051	0.051	0.0019	0.0019	0.0051	0.0020	0.0051
6	#06, 1 Liter	0.0056	0.0014	0.051	0.051	0.0012	0.0014	0.0051	0.0020	0.0051
7	#07, 1 Liter	0.0024	0.0010	0.051	0.051	0.0016	0.0015	0.0051	0.0020	0.0051
8	#08, 3 min 1 Liter	0.0011	0.0010	0.051	0.051	0.0010	0.0014	0.0051	0.0020	0.0051

Date: 1/25/13; outside spigot E301H00

Flow rate = 2.82 gpm pH = 9.78 / 9.97

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0068	0.0013	0.055	0.051	0.0550	0.0260	0.0051	0.0020	0.0420
2	#02, 1 Liter	0.0057	0.0025	0.051	0.051	0.0320	0.0230	0.0051	0.0020	0.0160
3	#03, 1 Liter	0.0190	0.0088	0.051	0.051	0.0190	0.0120	0.0051	0.0020	0.0200
4	#04, 1 Liter	0.0370	0.0160	0.051	0.051	0.0050	0.0037	0.0051	0.0020	0.0120
5	#05, 1 Liter	0.0280	0.0079	0.051	0.051	0.0019	0.0017	0.0051	0.0020	0.0051
6	#06, 1 Liter	0.0100	0.0023	0.051	0.051	0.0014	0.0012	0.0051	0.0020	0.0051
7	#07, 1 Liter	0.0018	0.0010	0.051	0.051	0.0012	0.0010	0.0051	0.0020	0.0051
8	#08, 3 min 1 Liter	0.0011	0.0010	0.051	0.051	0.0010	0.0011	0.0051	0.0020	0.0051

Date: 1/30/13; outside spigot E301J96

Flow rate = 2.38 gpm pH = 9.58 / 9.68

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0031	0.0010	0.051	0.051	0.0370	0.0220	0.0051	0.0020	0.0092
2	#02, 1 Liter	0.0035	0.0015	0.051	0.051	0.0380	0.0200	0.0051	0.0020	0.0140
3	#03, 1 Liter	0.0043	0.0017	0.051	0.051	0.0320	0.0180	0.0051	0.0020	0.0140
4	#04, 1 Liter	0.0070	0.0030	0.051	0.051	0.0200	0.0120	0.0051	0.0020	0.0450
5	#05, 1 Liter	0.0300	0.0130	0.051	0.051	0.0035	0.0026	0.0051	0.0020	0.0190
6	#06, 1 Liter	0.0330	0.0130	0.051	0.051	0.0020	0.0031	0.0051	0.0020	0.0110
7	#07, 1 Liter	0.0057	0.0013	0.051	0.051	0.0013	0.0014	0.0051	0.0020	0.0110
8	#08, 3 min 1 Liter	0.0010	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0099

Date: 2/11/13; inside faucet E302596

Flow rate = 1.22 gpm pH = 9.43 / 9.51

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0095	0.0043	0.051	0.051	0.03	0.02	0.0051	0.002	0.007
2	#02, 1 Liter	0.03	0.014	0.051	0.051	0.0043	0.0031	0.0051	0.002	0.018
3	#03, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.0012	0.0011	0.0051	0.002	0.0089

Date: 2/12/13; outside spigot E302693

Flow rate = 2.26 gpm pH = 9.54 / 9.60 temp = 13.7 / 11.5

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0032	0.001	0.051	0.051	0.05	0.025	0.0051	0.002	0.012
2	#02, 1 Liter	0.027	0.01	0.051	0.051	0.0039	0.0032	0.0051	0.002	0.016
3	#03, 3 min 1 Liter	0.001	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0094

Date: 2/18/13; inside faucet**E302A73**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0036	0.0020	0.0510	0.0510	0.0380	0.0260	0.0051	0.0020	0.0053
2	#02, 1 Liter	0.0320	0.0130	0.0510	0.0510	0.0047	0.0039	0.0051	0.0020	0.0220
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0012	0.0010	0.0051	0.0020	0.0093

Date: 2/20/13; outside spigot**E302D42**

Flow rate = 2.26 gpm

pH = 9.69 / 9.81

temp = 11.8 / 9.0

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0041	0.0010	0.0510	0.0510	0.0350	0.0190	0.0051	0.0020	0.0110
2	#02, 1 Liter	0.0230	0.0098	0.0510	0.0510	0.0024	0.0018	0.0051	0.0020	0.0190
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0022	0.0110

Date: 2/25/13; inside faucet**E302G20**

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0032	0.0018	0.0510	0.0430	0.0340	0.0510	0.0051	0.0020	0.0063
2		0.0160	0.0097	0.0510	0.0093	0.0080	0.0510	0.0051	0.0020	0.0250
3		0.0010	0.0010	0.0510	0.0011	0.0010	0.0540	0.0051	0.0022	0.0100

Date: 2/26/13; outside spigot**E302H05**

Flow rate = 2.26 gpm

pH = 9.81 / 9.90

temp = 11.5 / 7.6

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0026	0.0010	0.0510	0.0510	0.0360	0.0200	0.0051	0.0020	0.0200
2		0.0260	0.0110	0.0510	0.0510	0.0035	0.0026	0.0051	0.0020	0.0099
3		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0093

Date: 3/4/13; inside faucet**E303186**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0040	0.0018	0.0510	0.0510	0.0320	0.0190	0.0051	0.0020	0.0076
2	0.0200	0.0089	0.0510	0.0510	0.0048	0.0034	0.0051	0.0020	0.0180
3	0.0011	0.0010	0.0510	0.0510	0.0012	0.0010	0.0051	0.0020	0.0099

Date: 3/5/13; outside spigot**E303292**

ATP = 475 ME/mL

Flow rate = 2.54 gpm

pH = 9.96 / 10.03

temp = 10.3 / 8.7

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0036	0.0016	0.0510	0.0510	0.0510	0.0300	0.0051	0.0020	0.0190
2	0.0180	0.0110	0.0510	0.0510	0.0055	0.0048	0.0051	0.0020	0.0170
3	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0096

Date: 4/1/13; inside faucet**E304163**

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0085	0.0023	0.0510	0.0510	0.0160	0.0130		0.0020	0.0060
2	0.0210	0.0130	0.0510	0.0510	0.0028	0.0022		0.0020	0.0170
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0120

Date: 4/8/13; outside spigot**E304641**

ATP = 1042 ME/mL

Flow rate = 2.10 gpm

pH = 10.22 / 10.22

temp = 13.2 / 12.0

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0032	0.0014	0.0510	0.0510	0.0054	0.0042		0.0020	0.0460
2	0.0071	0.0045	0.0510	0.0510	0.0015	0.0015		0.0020	0.0120
3	0.0013	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0097

Date: 5/7/13; outside spigot

E305642

ATP = ??? ME/mL

Flow rate = 2.10 gpm

pH = 9.99 / 9.99

temp = 13.9 / 15.4

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0042	0.0010	0.0510	0.0510	0.0210	0.0110		0.0020	0.0120
2	0.0035	0.0011	0.0510	0.0510	0.0150	0.0096		0.0020	0.0051
3	0.0022	0.0010	0.0650	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 5/15/13; inside faucet

E305D58

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

1	0.0057	0.0027	0.0560	0.0510	0.0190	0.0120		0.0020	0.0072
2	0.0330	0.0230	0.0510	0.0510	0.0029	0.0024		0.0020	0.0095
3	0.0028	0.0010	0.0510	0.0510	0.0011	0.0010		0.0020	0.0051

Date: 6/4/13; inside faucet

E306285

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

1	0.0060	0.0024	0.0670	0.0510	0.0180	0.0110		0.0020	0.0074
2	0.0480	0.0340	0.0510	0.0510	0.0030	0.0026		0.0020	0.0100
3	0.0037	0.0011	0.0510	0.0510	0.0016	0.0012		0.0020	0.0051

Loc #8, 70 Sandringham Ave

Two largest concentrations

Below quantitation limits

Date: 1/10/13; inside faucet

E301688

Flow rate = 1.49 gpm

pH = 9.33 / 9.53

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0110	0.0011	0.230	0.051	0.0780	0.0140	0.0051	0.0089	0.0730
2	#02, 1/2 Liter	0.0073	0.0010	0.160	0.051	0.0095	0.0045	0.0051	0.0056	0.0710
3	#03, 1 Liter	0.0086	0.0014	0.140	0.051	0.0130	0.0063	0.0051	0.0050	0.1000
4	#04, 1 Liter	0.0100	0.0014	0.150	0.051	0.0098	0.0047	0.0051	0.0058	0.0660
5	#05, 1 Liter	0.0310	0.0060	0.120	0.051	0.0041	0.0025	0.0051	0.0041	0.0150
6	#06, 1 Liter	0.0600	0.0077	0.140	0.051	0.0015	0.0010	0.0051	0.0045	0.0055
7	#07, 1 Liter	0.0480	0.0073	0.150	0.051	0.0028	0.0029	0.0051	0.0050	0.0051
8	#08, 1 Liter	0.0260	0.0030	0.170	0.051	0.0020	0.0011	0.0051	0.0057	0.0059
9	#09, 3 min 1 Liter	0.0082	0.0010	0.083	0.051	0.0450	0.0019	0.0051	0.0028	0.0580

Date: 1/11/13; outside spigot

E301807

Flow rate = 1.74 gpm

pH = 9.62 / 9.73

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0430	0.0059	0.150	0.051	0.1500	0.0390	0.0052	0.0043	0.7800
2	#02, 1/2 Liter	0.0099	0.0026	0.051	0.051	0.0120	0.0074	0.0051	0.0020	0.0390
3	#03, 1 Liter	0.0390	0.0170	0.051	0.051	0.0038	0.0024	0.0051	0.0020	0.0270
4	#04, 1 Liter	0.0460	0.0230	0.051	0.051	0.0020	0.0016	0.0051	0.0020	0.0190
5	#05, 1 Liter	0.0310	0.0110	0.051	0.051	0.0023	0.0017	0.0051	0.0020	0.0210
6	#06, 1 Liter	0.0093	0.0016	0.070	0.051	0.0016	0.0010	0.0051	0.0027	0.0190
7	#07, 3 min 1 Liter	0.0016	0.0010	0.062	0.051	0.0010	0.0010	0.0051	0.0032	0.0051

Date: 1/15/13; outside spigot

E301A48

Flow rate = 1.54 gpm pH = 9.48 / 9.60

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0140	0.0071	0.056	0.051	0.0660	0.0420	0.0051	0.0026	0.0380
2	#02, 1/2 Liter	0.0083	0.0016	0.056	0.051	0.0120	0.0079	0.0051	0.0021	0.0550
3	#03, 1 Liter	0.0270	0.0130	0.051	0.051	0.0036	0.0033	0.0051	0.0020	0.0210
4	#04, 1 Liter	0.0420	0.0240	0.051	0.051	0.0012	0.0012	0.0051	0.0020	0.0260
5	#05, 1 Liter	0.0300	0.0130	0.051	0.051	0.0020	0.0016	0.0051	0.0020	0.0180
6	#06, 1 Liter	0.0120	0.0041	0.051	0.051	0.0012	0.0010	0.0051	0.0020	0.0170
7	#07, 3 min 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0150

Date: 1/17/13; outside spigot

E301C74

Flow rate = 1.69 gpm pH = 9.63 / 9.80

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#02, 1/2 Liter	0.0089	0.0012	0.063	0.051	0.0120	0.0075	0.0051	0.0037	0.0470
2	#03, 1 Liter	0.0270	0.0140	0.051	0.051	0.0040	0.0039	0.0051	0.0020	0.0290
3	#04, 1 Liter	0.0420	0.0250	0.051	0.051	0.0014	0.0013	0.0051	0.0020	0.0051
4	#05, 1 Liter	0.0300	0.0150	0.051	0.051	0.0017	0.0015	0.0051	0.0020	0.0051
5	#06, 1 Liter	0.0100	0.0052	0.051	0.051	0.0011	0.0013	0.0051	0.0020	0.0170
6	#07, 3 min1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0160

Date: 1/18/13; outside spigot

E301D08

Flow rate = 1.86 gpm pH = 9.60 / 9.82

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0088	0.0028	0.051	0.051	0.0140	0.0066	0.0051	0.0020	0.0400
2	#02, 1 Liter	0.0330	0.0200	0.051	0.051	0.0036	0.0024	0.0051	0.0020	0.0280
3	#03, 1 Liter	0.0400	0.0230	0.051	0.051	0.0019	0.0015	0.0051	0.0020	0.0051
4	#04, 1 Liter	0.0260	0.0100	0.051	0.051	0.0018	0.0014	0.0051	0.0020	0.0051
5	#05, 1 Liter	0.0067	0.0029	0.051	0.051	0.0012	0.0011	0.0051	0.0020	0.0210
6	#06, 3 min 1 Liter	0.0013	0.0010	0.051	0.051	0.0010	0.0010	0.0051	0.0020	0.0200

Date: 2/12/13; inside spigot

E302846

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0072	0.0015	0.056	0.051	0.01	0.0059	0.0051	0.002	0.075
2	#02, 1 Liter	0.047	0.016	0.051	0.051	0.0052	0.0028	0.0051	0.002	0.016
3	#03, 3 min 1 Liter	0.0013	0.001	0.051	0.051	0.0023	0.001	0.0051	0.002	0.011
4	#04, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.012

Date: 2/13/13; outside spigot

E302846

Flow rate = 2.24 gpm

pH = 9.69 / 9.78

temp = 10.3 / 8.7

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.034	0.003	0.077	0.051	0.025	0.022	0.0051	0.002	0.24
2	#02, 1 Liter	0.043	0.019	0.051	0.051	0.002	0.0015	0.0051	0.002	0.014
3	#03, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.0084
4	#04, 3 min 1 Liter	0.0011	0.001	0.051	0.051	0.001	0.001	0.0051	0.002	0.009

Date: 2/21/13; inside spigot

E302E19

		ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	#01, 1/2 Liter	0.0044	0.0010	0.0560	0.0510	0.0088	0.0052	0.0051	0.0020	0.0530
2	#02, 1 Liter	0.0310	0.0087	0.0520	0.0510	0.0066	0.0022	0.0051	0.0020	0.0210
3	#03, 3 min 1 Liter	0.0012	0.0010	0.0550	0.0510	0.0010	0.0010	0.0051	0.0028	0.0110
4	#04, 3 min 1 Liter	0.0010	0.0010	0.0520	0.0510	0.0010	0.0010	0.0051	0.0029	0.0110

Date: 2/20/13; outside spigot

E302E22

Flow rate = 2.26 gpm

pH = 9.79 / 9.86

temp = 9.7 / 7.3

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1	#01, 1/2 Liter	0.0140	0.0010	0.0900	0.0510	0.0220	0.0066	0.0051	0.0020	0.0880
2	#02, 1 Liter	0.0440	0.0130	0.0510	0.0510	0.0014	0.0013	0.0051	0.0020	0.0110
3	#03, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0110
4	#04, 3 min 1 Liter	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

Date: 2/27/13; inside spigot

E302I58

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0048	0.0016	0.0510	0.0510	0.0100	0.0057	0.0051	0.0020	0.0800
2		0.0320	0.0150	0.0510	0.0510	0.0022	0.0014	0.0051	0.0020	0.0140
3		0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0140
4		0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0099

Date: 2/28/13; outside spigot

E303077

ATP = 96 ME/mL

Flow rate = 1.04 gpm

pH = 9.71 / 9.85

temp = 15.2 / 9.4

		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		Lead	Diss Lead	Iron	Diss Iron	Copper	Diss Copper	Tin	Manganese	Zinc
1		0.0065	0.0014	0.0510	0.0510	0.0110	0.0068	0.0051	0.0020	0.0440
2		0.0350	0.0150	0.0510	0.0510	0.0014	0.0011	0.0051	0.0020	0.0100
3		0.0012	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0093
4		0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0086

Date: 3/5/13; outside spigot

E303456

ATP = 214 ME/mL

Flow rate = 1.87 gpm

pH = 9.85 / 10.02

temp = 14.4 / 9.3

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0099	0.0023	0.0580	0.0510	0.0210	0.0110	0.0051	0.0020	0.0970
2	0.0390	0.0180	0.0510	0.0510	0.0017	0.0012	0.0051	0.0020	0.1900
3	0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0087
4	0.0010	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0090

Date: 3/6/13; inside spigot

E303458

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

ppm

Lead

Diss Lead

Iron

Diss Iron

Copper

Diss Copper

Tin

Manganese

Zinc

1	0.0029	0.0010	0.0510	0.0510	0.0073	0.0056	0.0051	0.0020	0.0520
2	0.0230	0.0140	0.0510	0.0510	0.0038	0.0019	0.0051	0.0020	0.0140
3	0.0012	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0096
4	0.0011	0.0010	0.0510	0.0510	0.0010	0.0010	0.0051	0.0020	0.0100

Date: 4/9/13; outside spigot

E304A25

ATP = 4312 ME/mL

Flow rate = 1.71 gpm

pH = 9.45 / 9.54

temp = 18.6 / 14.1

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0170	0.0026	0.0510	0.0510	0.0083	0.0058		0.0020	0.0520
2	0.0340	0.0220	0.0510	0.0510	0.0012	0.0011		0.0020	0.0084
3	0.0017	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0070

Date: 4/12/13; inside spigot

E304A66

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0016	0.0012	0.0510	0.0510	0.0061	0.0050		0.0020	0.0380
2	0.0260	0.0190	0.0510	0.0510	0.0028	0.0024		0.0020	0.0320
3	0.0014	0.0010	0.0550	0.0510	0.0015	0.0010		0.0020	0.0110

Date: 5/8/13; outside spigot

E305880

ATP = ??? ME/mL

Flow rate = 1.51 gpm

pH = 9.97 / 10.03

temp = 19.5 / 15.4

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0110	0.0019	0.1000	0.0510	0.0093	0.0045		0.0021	0.5400
2	0.0440	0.0310	0.0510	0.0510	0.0011	0.0010		0.0020	0.0100
3	0.0031	0.0015	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 5/15/13; inside spigot

E305D57

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0033	0.0015	0.0510	0.0510	0.0060	0.0041		0.0020	0.0360
2	0.0290	0.0200	0.0510	0.0510	0.0044	0.0021		0.0020	0.0074
3	0.0029	0.0016	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 5/8/13; outside spigot

E305880

ATP = ???? ME/mL

Flow rate = ?? gpm

pH =

temp =

	ppm Lead	ppm Diss Lead	ppm Iron	ppm Diss Iron	ppm Copper	ppm Diss Copper	ppm Tin	ppm Manganese	ppm Zinc
1	0.0056	0.0025	0.0510	0.0510	0.0050	0.0037		0.0020	0.1600
2	0.0590	0.0440	0.0510	0.0510	0.0011	0.0010		0.0020	0.0051
3	0.0041	0.0024	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051

Date: 6/6/13; inside spigot

E306705

ppm
Lead

ppm
Diss Lead

ppm
Iron

ppm
Diss Iron

ppm
Copper

ppm
Diss Copper

ppm
Tin

ppm
Manganese

ppm
Zinc

1	0.0038	0.0019	0.0510	0.0510	0.0046	0.0038		0.0020	0.0270
2	0.0340	0.0240	0.0510	0.0510	0.0010	0.0010		0.0020	0.0071
3	0.0035	0.0010	0.0510	0.0510	0.0010	0.0010		0.0020	0.0051